



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
485 LEXINGTON AVENUE, NEW YORK, N. Y. 10017

AMS 3693

Issued 5-1-68
Revised

ADHESIVE, MODIFIED EPOXY

Moderate Heat Resistant, 250 F (121.1 C) Curing, Film Type

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Unless otherwise specified, the product shall consist of a supported film adhesive with protective liners; uniformly dispersed fillers may be included in the film.
3. **APPLICATION:** Primarily for structural bonding of metallic alloys and rigid nonmetallic surfaces to themselves and to each other and for bonding of internal and external structural honeycomb components operating in the temperature range of -67 to +180 F (-55 to +82 C). A liquid primer suitable for spray or brush application may be required for use with the adhesive.
4. **TECHNICAL REQUIREMENTS:**
 - 4.1 **General:**
 - 4.1.1 **Description:** The weight and/or caliper of the supported film adhesive shall be as specified on the drawing or purchase order.
 - 4.1.2 **Shelf Life:** The adhesive, when stored in airtight or suitable vapor barrier containers, shall be capable of meeting the requirements of this specification after storage for six months at a temperature not higher than 0 F (-18 C).
 - 4.1.3 **Corrosion:** The cured product shall not have a corrosive effect on adherend surfaces when exposed to conditions normally encountered in service. Discoloration of metals shall not be considered objectionable.
 - 4.2 **Properties:** The product shall conform to the following requirements when cured in accordance with the manufacturer's recommendations. Tests shall be performed in accordance with the issue of specified ASTM methods listed in the latest issue of AMS 2350, insofar as practicable. Unless otherwise specified, only the tensile shear strength at $75\text{ F} \pm 5$ ($23.9\text{ C} \pm 2.8$) of 4.2.1.1 need be determined on each batch but the material shall be capable of meeting all requirements of this specification. All reported values shall be the average of results of tests on not less than five specimens per batch.
 - 4.2.1 **Tensile Shear Strength:** All specimens shall be prepared and tested in accordance with ASTM D1002; specimens to determine conformance to 4.2.1.2, 4.2.1.3, and 4.2.1.4 shall be exposed as specified after preparation but before testing.
 - 4.2.1.1 **As Cured:**

Test Temperature	Minimum Average Strength, psi
$75\text{ F} \pm 5$ ($23.9\text{ C} \pm 2.8$)	2,500
$-67\text{ F} \pm 5$ ($-55\text{ C} \pm 2.8$)	2,500
$180\text{ F} \pm 5$ ($82.2\text{ C} \pm 2.8$)	1,250

SAE Technical Board rules provide that: "All technical reports, including standards applications, shall be prepared and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

4.2.1.2 Salt Spray Resistance:ASTM B117
Time: 30 daysMinimum Average Strength at
75 F $\pm$ 5 (23.9 C $\pm$ 2.8), psi 2,2504.2.1.3 Humidity Resistance:ASTM D2247
Temperature: 120 F $\pm$ 5
(48.9 C $\pm$ 2.8)
Time: 30 daysMinimum Average Strength at
75 F $\pm$ 5 (23.9 C $\pm$ 2.8), psi 2,2504.2.1.4 Fuel Resistance:ASTM D471
Medium: ASTM D1665
Jet A Fuel
Temperature: 65 - 85 F
(18.3 - 29.4 C)
Time: 30 daysMinimum Average Strength at
75 F $\pm$ 5 (23.9 C $\pm$ 2.8), psi 2,250

4.2.2 Creep Deformation: Specimens prepared and tested in accordance with ASTM D2294 shall withstand being stressed for 192 hr at the temperature and stress shown below without fracture; the deformation shall be not greater than 0.015 in. at either test temperature.

Test Temperature	Stress, psi
75 F $\pm$ 5 (23.9 C $\pm$ 2.8)	1,600
180 F $\pm$ 5 (82.2 C $\pm$ 2.8)	800

4.2.3 Flatwise Tensile Strength:

ASTM C297

Minimum Average Strength at
Temperature Shown, psi

75 F $\pm$ 5 (23.9 C $\pm$ 2.8)	450
-67 F $\pm$ 5 (-55 C $\pm$ 2.8)	350
180 F $\pm$ 5 (82.2 C $\pm$ 2.8)	270

4.2.4 Flexural Strength:

ASTM C393

Minimum Average Strength at
Temperature Shown, psi

75 F $\pm$ 5 (23.9 C $\pm$ 2.8)	1,750
-67 F $\pm$ 5 (-55 C $\pm$ 2.8)	1,750
180 F $\pm$ 5 (82.2 C $\pm$ 2.8)	1,200
75 F $\pm$ 5 (23.9 C $\pm$ 2.8) after 192 hr in air at 180 F $\pm$ 5 (82.2 C $\pm$ 2.8)	1,000

4.2.5 T Peel Strength

ASTM D1876

Minimum Average Strength at
75 F $\pm$ 5 (23.9 C $\pm$ 2.8), psi 15