

POTTING COMPOUND, EPOXY
Bisphenol A-Type
Filled, Room Temperature Cure, Low Shrinkage

1. SCOPE:

- 1.1 Form: This specification covers a filled, room-temperature-polymerizing epoxy resin formulation, supplied as a two-component system.
- 1.2 Application: Primarily for use as a potting or sealing material where low shrinkage is desired.

2. APPLICABLE DOCUMENTS: See AMS 3731.

3. TECHNICAL REQUIREMENTS:

- 3.1 Basic Specification: The complete requirements for procuring the product described herein shall consist of this document and the latest issue of the basic specification, AMS 3731.
- 3.2 Material: Shall be an epoxy-based polymer with a curing agent.
- 3.3 Properties: The compound shall conform to the following requirements:
- 3.3.1 Mixed Uncured Compound: The compound, mixed in accordance with manufacturer's instructions, shall exhibit the following properties:
- 3.3.1.1 Viscosity: Shall be not greater than 10,000 centipoise (10.0 Pa·s) at 23°C (73°F), determined within 5 min. after mixing, using a Brookfield Model LVF viscometer and No. 3 spindle at 6 revolutions per minute.
- 3.3.1.2 Pot Life: Usable life of the compound, defined as the time to attain double the initial viscosity determined in 3.3.1.1, shall be not less than 30 min. at 23°C (73°F).

REAFFIRMED

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3.3.1.3 Curing Time: The time required to develop the cured product properties specified in 3.3.2 shall be not more than 5 days at 23°C (73°F) or not more than 2 hr at 95°C (200°F).

3.3.1.4 Demold Time: The time required before the part can be removed from the mold and retain its integrity shall be not more than 24 hr at 23°C (73°F).

3.3.2 Cured Product: The compound, mixed and cured in accordance with manufacturer's instructions, shall exhibit the following properties, determined in accordance with test methods listed in AMS 3731:

3.3.2.1	Flexural Strength, min	9600 psi (52.5 MPa)
3.3.2.2	Izod Impact Strength, per unit of notch, min	0.27 ft-lb per in. (14.5 J/m)
3.3.2.3	Compressive Strength, min	14,000 psi (97 MPa)
3.3.2.4	Insulation Resistance	
3.3.2.4.1	At 23°C (73°F), min	1×10^6 megohms
3.3.2.4.2	At 120°C (250°F), min	1×10^3 megohms
3.3.2.4.3	After hydrolytic stability conditioning, min	1×10^4 megohms
3.3.2.5	Dielectric Constant at 1 KHz, max	5.5
3.3.2.6	Dissipation Factor at 1 KHz, max	0.04
3.3.2.7	Heat Deflection Temperature at 264 psi (1.8 MPa), min	77°C (170°F)
3.3.2.8	Coefficient of Linear Thermal Expansion, max	
3.3.2.8.1	From -54°C to +23°C (-65°F to +73°F)	35×10^{-6} mm/mm per deg C (20×10^{-6} in./in. per deg F)
3.3.2.8.2	From 23°C to 75°C (73°F to 165°F)	50×10^{-6} mm/mm per deg C (27×10^{-6} in./in. per deg F)
3.3.2.9	Water Absorption after 24 hr immersion, max	0.1%
3.3.2.10	Specific Gravity, max	1.8