



400 Commonwealth Drive, Warrendale, PA 15096-0001

# AEROSPACE MATERIAL SPECIFICATION



AMS 3796/1A

Issued 1 JAN 1987  
Revised 1 JAN 1993  
Superseding AMS 3796/1

Submitted for recognition as an American National Standard

WEBBING, NYLON, AIRCRAFT ARRESTING  
105,000 Pounds (467 kN)

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of July, 1992. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the initial issue of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "CP".

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.



400 Commonwealth Drive, Warrendale, PA 15096

# AEROSPACE MATERIAL SPECIFICATION

an American National Standard

AMS 3796/1

Issued 1-1-87

## WEBBING, NYLON, AIRCRAFT ARRESTING 105,000 lb (467 kN)

### 1. SCOPE:

1.1 Form: This specification covers one type of nylon in the form of webbing.

1.2 Application: Primarily for use in land-based aircraft arresting systems.

1.3 Classification: Nylon webbing having average breaking strength of 105,000 lb (467 kN).

2. APPLICABLE DOCUMENTS: See AMS 3796.

### 3. TECHNICAL REQUIREMENTS:

3.1 Basic Specification: The complete requirements for procuring the webbing described herein shall consist of this document and the latest issue of the basic specification, AMS 3796.

#### 3.2 Construction and Properties:

3.2.1 Yarn: Shall be as specified in Table I and the following:

3.2.1.1 Fiber Identification: Shall be nylon, prepared from hexamethylene diamine and adipic acid, or its derivatives.

3.2.1.2 Melting Point: Shall be not lower than 245°C (475°F).

3.2.1.3 Denier: Shall be 840 or 1260.

3.2.2 Webbing: Shall be as specified in Table II and as follows:

3.2.2.1 Weave: Shall be as shown in Fig. 1.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

3.2.2.2 Edge Wear Markers: There shall be two yellow marker ends in the center of each selvage stuffer as shown in Fig. 1. The marker shall be an 840 denier 7-ply yarn.

3.2.2.3 Length: Shall be as specified by purchaser.

4. QUALITY ASSURANCE PROVISIONS: See AMS 3796.

5. PREPARATION FOR DELIVERY: See AMS 3796.

6. ACKNOWLEDGMENT: See AMS 3796.

7. REJECTIONS: See AMS 3796.

8. NOTES: See AMS 3796.

TABLE I

Characteristics of Yarn

Requirements

|                                |                                       |
|--------------------------------|---------------------------------------|
| Ply, min                       |                                       |
| Ground                         | 3 (840 denier) or<br>2 (1,260 denier) |
| Binder                         | 3 (840 denier) or<br>2 (1,260 denier) |
| Stuffer                        | 5 (840 denier) or<br>4 (1,260 denier) |
| Filling                        | 6 (840 denier) or<br>4 (1,260 denier) |
| Twist, turns per in. (25.4 mm) |                                       |
| Ground                         | 2.0 to 3.0                            |
| Binder                         | 2.0 to 3.0                            |
| Stuffer                        | 1.0 to 2.0                            |
| Filling                        | 1.0 to 2.0                            |

TABLE II

## Properties

| Requirements                           |                                                         |
|----------------------------------------|---------------------------------------------------------|
| Width <u>1</u> / <u>2</u> / <u>3</u> / | 8.500 in., + 0.125, - 0.062<br>(216.0 mm, + 3.0, - 1.5) |
| Thickness                              | 0.225 in. $\pm$ 0.010<br>(5.70 mm $\pm$ 0.25)           |
| Weight, max                            | 37 oz per linear yd<br>(1,147 g/m)                      |
| Breaking Strength, min                 |                                                         |
| Average                                | 105,000 lb (467 kN)                                     |
| Single Determination                   | 95,000 lb (422.5 kN)                                    |
| Ends in Warp, min                      |                                                         |
| Ground                                 | 149                                                     |
| Binder                                 | 160                                                     |
| Stuffer                                | 6190 (840 denier) or 991 (1260 denier)                  |
| Yellow Marker                          | 4                                                       |
| Filling Yarns per in. (25.4 mm), min   | 14                                                      |
| Extractable Matter                     | 3.1 to 8.5% by wt.                                      |
| Stiffness (angle subtended), max       | 35 deg                                                  |
| Color (after resin treatment)          | Black                                                   |

1/ Nonconformance shall be based on a length greater than 12 in. (305 mm).

2/ Single determination.

3/ A maximum of two single determinations per roll may deviate to -1/8 in. (-3 mm).