



AEROSPACE MATERIAL

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

SPECIFICATION

AMS 4012C

Superseding AMS 4012B

Issued 1/15/58

Revised 5/1/70

ALUMINUM SHEET, LAMINATED Edge Bonded

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for shims of special shapes in which thickness is to be adjusted by removal of laminations as required.
3. **COMPOSITION:**
 - 3.1 **Laminations:** Shall be 1100, 1145, 3003, or 5052 aluminum alloy foil. Unless otherwise specified, the choice of alloy shall be at the discretion of the producer.
 - 3.2 **Solid Base:** Shall be AMS 4041 aluminum alloy sheet.
 - 3.3 **Adhesive:** Shall be a composition which will meet the fabrication and quality requirements of this specification.

4. **FABRICATION:**

- 4.1 Laminated shim stock shall be fabricated from hard or extra hard laminations, in combination with a solid base when required, pre-cut to the desired shape, stacked to the desired thickness, and then bonded on the outside edge with adhesive. Laminations shall be 0.003 in. $\pm$ 0.0003 thick unless 0.002 in. $\pm$ 0.0002 laminations are specified or required to produce the nominal laminate thickness.
- 4.2 Unless otherwise specified, the product shall be of the following thicknesses and combinations of laminations and solid base:

Nominal Thickness of Shim Stock Inch			
	All Laminated	Half Solid Half Laminated	Three Quarters Solid One Quarter Laminated
0.006	X		
0.008	X		
0.010	X		
0.016	X		
0.020	X		
0.032	X		
0.047	X		
0.062	X	X	
0.094	X	X	
0.125	X	X	X
0.190	X	X	X

5. **QUALITY:**

- 5.1 Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."