

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS4015B

Issued 12-5-39

Revised 4-1-46

### ALUMINUM ALLOY SHEET Magnesium Chromium (52S-0)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. **COMPOSITION:**

|                         |             |
|-------------------------|-------------|
| Magnesium               | 2.2 - 2.8   |
| Chromium                | 0.15 - 0.35 |
| Iron plus Silicon       | 0.45 max    |
| Manganese               | 0.10 max    |
| Copper                  | 0.10 max    |
| Zinc                    | 0.10 max    |
| Other Impurities, each  | 0.05 max    |
| Other Impurities, total | 0.15 max    |
| Aluminum                | remainder   |

3. **CONDITION:** (a) Annealed and unless otherwise specified, mill finish.

(b) Physical properties shall conform to the values in the following table. Test specimens shall conform to ASTM E-8, except from sheet less than 3/4 inch in width. Elongation requirements apply only to sheet 3/4 inch and over in width.

| Thickness<br>Inch    | Tensile Strength<br>psi max | Elongation<br>% in 2 in. min |
|----------------------|-----------------------------|------------------------------|
| 0.008 - 0.019, incl. | 31,000                      | 15                           |
| 0.020 - 0.031, incl. | 31,000                      | 18                           |
| 0.032 - 0.249, incl. | 31,000                      | 20                           |

(c) Sheet shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to direction of rolling.

4. **QUALITY:** (a) Sheet shall be uniform in quality and condition, clean, sound, and free from foreign material and from internal and external defects detrimental to fabrication or to the appearance and performance of parts. Sheet revealing defects during fabrication shall be subject to rejection.

(b) Sheet and parts made therefrom shall be subjected to inspection by any method which will reveal defects.

5. **TOLERANCES:** Unless otherwise specified, tolerances shall conform to the latest revision of AMS 2202 as applicable. Thickness tolerances shall conform to Table II.

6. **REPORTS:** (a) Unless otherwise specified, the vendor of sheet shall furnish three copies of a notarized report stating that the sheet meets all the requirements of this specification. This report shall include the purchase order number, material specification number, size and quantity.