

Section 8.3 of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no requirement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

AMS 4015E

Issued 12-5-39
Revised 1-31-64

ALUMINUM ALLOY SHEET AND PLATE 2.5Mg - 0.25Cr (5052-0)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for formed parts where welding, moderate strength, and good resistance to corrosion are required.
3. **COMPOSITION:**

	min	max
Magnesium	2.2	2.8
Chromium	0.15	0.35
Iron + Silicon	--	0.45
Zinc	--	0.10
Manganese	--	0.10
Copper	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

4. **CONDITION:** Annealed and, unless otherwise specified, mill finish.
5. **TECHNICAL REQUIREMENTS:** When ASTM methods are specified for determining conformance to the following requirements, tests shall be conducted in accordance with the issue of the ASTM method listed in the latest issue of AMS 2350.
 - 5.1 **Tensile Properties:** Test specimens shall conform to ASTM E8 and shall be taken parallel to the direction of rolling. Sheet type specimens shall be used for material less than 0.5 in. thick and 0.75 in. and over in width. Round specimens shall be used for material 0.5 in. and over in thickness and 0.75 in. and over in width. Material under 0.75 in. wide and under 0.5 in. thick may be tested in either full section or by use of round specimens; for such sizes, elongation requirements apply only when round specimens are used.

Nominal Thickness Inches	Tensile Strength psi	Elongation % in 2 in. or 4D, min
0.006 to 0.007, incl	25,000 - 31,000	--
Over 0.007 to 0.019, incl	25,000 - 31,000	15
Over 0.019 to 0.031, incl	25,000 - 31,000	18
Over 0.031 to 0.249, incl	25,000 - 31,000	20
Over 0.249 to 3.000, incl	25,000 - 31,000	18

- 5.2 Bending: Material 0.249 in. and under in thickness shall be capable of withstanding, without cracking, bending at room temperature flat on itself with axis of bend parallel to direction of rolling.
6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
7. TOLERANCES: Unless otherwise specified, tolerances shall conform to all applicable requirements of the latest issue of AMS 2202.
8. REPORTS:
- 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number, thickness, size, and quantity.
- 8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
9. IDENTIFICATION: Unless otherwise specified, each sheet and plate shall be marked on one face, in the respective location indicated below. Symbols shall be applied using a suitable marking fluid and shall be sufficiently stable to withstand normal handling.
- 9.1 Flat Sheet and Plate 0.375 In. and Under Thick, 6 - 60 In., Incl. Wide, and 36 - 200 In., Incl. Long: Shall be marked in rows of symbols not less than 3/8 in. in height and recurring at intervals not greater than 3 feet. Rows shall run parallel to the direction of rolling of the piece and shall be spaced approximately 6 in. on centers across the width. Every third row shall show the manufacturer's identification and nominal thickness in inches. The other rows shall show the alloy number and temper, or AMS 4015, and shall be staggered.
- 9.2 Flat Sheet and Plate Over 0.375 In. Thick, or Over 60 In. Wide, or Over 200 In. Long: Shall be marked as in 9.1 above or, at vendor's discretion, shall be marked in one or two rows of symbols not less than 3/8 in. in height and running around the perimeter of the piece. If one row is used, it shall show the alloy number and temper, or AMS 4015, manufacturer's identification, and nominal thickness in inches. If two rows are used, one row shall show the alloy number and temper, or AMS 4015; the second row shall show the manufacturer's identification and nominal thickness in inches.