

AERONAUTICAL MATERIAL SPECIFICATIONS

AMS 4029

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 8-15-58
Revised

ALUMINUM ALLOY SHEET AND PLATE 4.5Cu - 0.8Si - 0.8Mn - 0.5Mg (2014-T6)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for parts requiring high strength.

3. COMPOSITION:

Copper	3.9 - 5.0
Silicon	0.50 - 1.2
Manganese	0.40 - 1.2
Magnesium	0.20 - 0.8
Iron	1.0 max
Zinc	0.25 max
Titanium	0.15 max
Chromium	0.10 max
Other Impurities, each	0.05 max
Other Impurities, total	0.15 max
Aluminum	remainder

4. CONDITION: Solution and precipitation heat treated.

5. TECHNICAL REQUIREMENTS:

5.1 Tensile Properties: Test specimens shall conform to ASTM E8-54T except from material less than 3/4 in. wide, and shall be cut across the direction of rolling except from material less than 9 in. wide. Elongation requirements apply only to material 3/4 in. and over in width.

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 10,400,000)		Elongation % in 2 in. min
		psi, min	in. in 2 in.	
0.020 to 0.039, incl	64,000	57,000	0.0150	6
Over 0.039 to 0.499, incl	67,000	59,000	0.0153	8
Over 0.499 to 1.000, incl	67,000	59,000	0.0153	6
Over 1.000 to 1.500, incl	67,000	59,000	0.0153	4
Over 1.500 to 2.000, incl	65,000	59,000	0.0153	3
Over 2.000 to 3.000, incl	63,000	57,000	0.0150	2

5.1.1 When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.

- 5.2 Bending: Material 0.499 in. and under in thickness shall be capable of withstanding, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of material, with axis of bend parallel to direction of rolling.

Nominal Thickness Inch	Bend Factor
0.020 to 0.039, incl	5
Over 0.039 to 0.050, incl	6
Over 0.050 to 0.124, incl	8
Over 0.124 to 0.249, incl	10
Over 0.249 to 0.499 incl	12

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
7. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2202 as applicable. Thickness tolerances shall conform to Table II.
8. REPORTS:
- 8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number, thickness, size, and quantity.
- 8.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.
9. IDENTIFICATION: Unless otherwise specified, each sheet and plate shall be marked, in the respective location indicated below, with the manufacturer's identification, and, in addition, the alloy number and temper, or AMS 4029, and nominal thickness in inches. The characters shall be not less than 3/8 in. in height, shall be applied using a suitable marking fluid, and shall not be obliterated by normal handling or heat treatment.
- 9.1 Flat Sheet and Plate: The alloy number and temper, or AMS 4029, shall be marked in rows of recurring characters from one edge to the opposite edge with rows spaced such that no piece larger than 12 in. square could be cut from the sheet without bearing the alloy identification. The manufacturer's identification and thickness shall be marked in rows not more than 20 in. apart.
- 9.2 Coiled Sheet: Shall be marked near the outside end of the coil.