

AEROSPACE

MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

AMS 4045C

Issued 6-1-49

Revised 6-30-64

ALUMINUM ALLOY SHEET AND PLATE

5.6Zn - 2.5Mg - 1.6Cu - 0.25Cr (7075-T6)

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. **APPLICATION:** Primarily for structural parts which will be painted or otherwise protected from corrosion. Certain design and processing procedures may cause this material to be susceptible to stress corrosion cracking; ARP 823 recommends practices to minimize such conditions.

3. **COMPOSITION:**

	min	max
Zinc	5.1	6.1
Magnesium	2.1	2.9
Copper	1.2	2.0
Chromium	0.18	0.40
Iron	--	0.7
Silicon	--	0.50
Manganese	--	0.30
Titanium	--	0.20
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

4. **CONDITION:** Solution and precipitation heat treated.
5. **TECHNICAL REQUIREMENTS:** When ASTM methods are specified for determining conformance to the following requirements, tests shall be conducted in accordance with the issue of the ASTM method listed in the latest issue of AMS 2350.

- 5.1 **Tensile Properties:** Test specimens shall conform to ASTM E8 and shall be taken across the direction of rolling from widths 9 in. and over and parallel to the direction of rolling from widths less than 9 inches. Sheet type specimens shall be used for material less than 0.5 in. thick and 0.75 in. and over in width. Round specimens shall be used for material 0.5 in. and over in thickness and 0.75 in. and over in width. Material under 0.75 in. wide and under 0.5 in. thick may be tested in either full section or by use of round specimens; for such sizes, elongation requirements apply only when round specimens are used.

Nominal Thickness Inches	Tensile Strength psi, min	Yield Strength at 0.2% Offset or at Extension Indicated (E = 10,300,000)		Elongation % in 2 in. or 4D, min
		Extension Under Load		
		psi, min	in. in 2 in.	
0.015 to 0.039, incl	76,000	65,000	0.0166	7
Over 0.039 to 0.499, incl	77,000	66,000	0.0168	8
Over 0.499 to 1.000, incl	77,000	66,000	0.0168	6
Over 1.000 to 2.000, incl	77,000	66,000	0.0168	4
Over 2.000 to 2.500, incl	73,000	62,000	0.0160	3
Over 2.500 to 3.000, incl	70,000	60,000	0.0157	3
Over 3.000 to 3.500, incl	70,000	57,000	0.0151	3
Over 3.500 to 4.000, incl	67,000	53,000	0.0143	2

5.1.1 When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.

5.1.2 Properties of plate over 4.000 in. in thickness shall be as agreed upon by purchaser and vendor.

5.2 Bending: Material shall be capable of withstanding, without cracking, bending at room temperature through an angle of 180 deg around a diameter equal to the bend factor times the nominal thickness of the material, with axis of bend parallel to direction of rolling.

Ø	Nominal Thickness Inch	Bend Factor
	0.015 to 0.020, incl	7
	Over 0.020 to 0.062, incl	8
	Over 0.062 to 0.091, incl	9
	Over 0.091 to 0.125, incl	10
	Over 0.125 to 0.249, incl	11
	Over 0.249 to 0.499, incl	14

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2202 as applicable. Flatness tolerances for material over 3.000 in. thick shall be as agreed upon by purchaser and vendor.

8. REPORTS:

8.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a report stating that the product conforms to the chemical composition and technical requirements of this specification. This report shall include the purchase order number, material specification number, thickness, size, and quantity.