



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
485 LEXINGTON AVENUE, NEW YORK, N. Y. 10017

AMS 4064

Issued 5-1-68
Revised

ALUMINUM ALLOY SHEET, CLAD TWO SIDES 1.25Mn (No. 12-0 Brazing Sheet)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for brazed assemblies which are not subject to heat treatment after brazing.
3. COMPOSITION:

	Core (3003)			Cladding (4343)	
	min	max		min	max
Manganese	1.0	- 1.5	Silicon	6.8	- 8.2
Iron	--	0.7	Iron	--	0.8
Silicon	--	0.6	Copper	--	0.25
Copper	0.05	- 0.20	Zinc	--	0.20
Zinc	--	0.10	Manganese	--	0.10
Other Impurities, each	--	0.05	Other Impurities, each	--	0.05
Other Impurities, total	--	0.15	Other Impurities, total	--	0.15
Aluminum	remainder		Aluminum	remainder	

4. CONDITION: Annealed.
5. TECHNICAL REQUIREMENTS: The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.
 - 5.1 Cladding: Material shall be clad on both sides.
 - 5.2 Cladding Thickness: After rolling, the average cladding thickness shall be as shown. Routine measurements are not required.

Total Thickness of Composite Product Inch	Cladding Thickness Per Side % of Total Thickness min
Up to 0.063, incl	8
Over 0.063 to 0.250, excl	4

- 5.3 Tensile Properties:

Nominal Thickness Inch	Tensile Strength psi, max	Elongation % in 2 in., min
Over 0.006 to 0.007, incl	20,000	12
Over 0.007 to 0.012, incl	20,000	15
Over 0.012 to 0.031, incl	20,000	18
Over 0.031 to 0.050, incl	20,000	20
Over 0.050 to 0.249, incl	20,000	23

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."