



AEROSPACE MATERIAL SPECIFICATION

AMS4079™**REV. J**

Issued 1959-06
Reaffirmed 2007-04
Revised 2023-08

Superseding AMS4079H

Aluminum Alloy, Drawn, Round, Seamless, Tubing
1.0Mg - 0.60Si - 0.28Cu - 0.20Cr (6061-O)
Close Tolerance, Annealed
(Composition similar to UNS A96061)

RATIONALE

AMS4079J results from a Five-Year Review and update of this specification with changes to update wording to prohibit unauthorized exceptions (see 3.3.3, 3.6, 4.4.1, 5.1.1, and 8.4), relocate Definitions (see 2.4), update Applicable Documents (see Section 2) and Ordering Information (see 8.6), and allow the use of the immediate prior specification revision (see 8.5).

1. SCOPE

1.1 Form

This specification covers an aluminum alloy in the form of drawn, round, seamless tubing with wall thickness of 0.018 to 0.500 inch (0.46 to 12.70 mm), inclusive (see 8.6).

1.2 Application

This tubing has been used typically for ducts requiring small radius bends and moderate strength after solution and precipitation heat treatment, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or +1 724-776-4970 (outside USA), www.sae.org.

AMS2355 Quality Assurance, Sampling and Testing, Aluminum Alloys and Magnesium Alloy, Wrought Products (Except Forging Stock), and Rolled, Forged, or Flash Welded Rings

AMS2772 Heat Treatment of Aluminum Alloy Raw Materials

AS7766 Terms Used in Aerospace Metals Specifications

SAE Executive Standards Committee Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2023 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

For more information on this standard, visit

<https://www.sae.org/standards/content/AMS4079J/>

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM B660 Packaging/Packing of Aluminum and Magnesium Products

ASTM B666/B666M Identification Marking of Aluminum and Magnesium Products

ASTM E18 Rockwell Hardness of Metallic Materials

2.3 ANSI Accredited Publications

Copies of these documents are available online at <https://webstore.ansi.org/>.

ANSI H35.1/H35.1M American National Standard Alloy and Temper Designation Systems for Aluminum

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products

ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

2.4 Definitions

Terms used in AMS are defined in AS7766.

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS2355.

Table 1 - Composition

Element	Min	Max
Silicon	0.40	0.8
Iron	--	0.7
Copper	0.15	0.40
Manganese	--	0.15
Magnesium	0.8	1.2
Chromium	0.04	0.35
Zinc	--	0.25
Titanium	--	0.15
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition

Annealed in accordance with AMS2772, and drawn to meet dimensional tolerances of 3.5.

3.2.1 Tubing shall be supplied unground with an as-drawn surface finish, unless otherwise specified.

3.3 Properties

Tubing shall conform to the following requirements, determined in accordance with AMS2355 on the mill produced size.

3.3.1 As Annealed

3.3.1.1 Tensile Properties

Shall be shown in Table 2 for tubing having nominal wall thickness of 0.018 to 0.500 inch (0.46 to 12.70 mm), inclusive.

Table 2 - Tensile properties

Property	Value
Tensile Strength, Max	22.0 ksi (152 MPa)
Yield Strength at 0.2% Offset, Max	14.0 ksi (97 MPa)
Elongation in 2 Inches (50.8 mm) or 4D, Min	
Strip	15%
Full Section	15%

3.3.1.2 Flattening

Tubing, having nominal wall thickness less than 10% of the nominal OD, shall withstand, without cracking, flattening sideways under a load applied gradually at room temperature until the outside dimension under load is equal to the flattening factor shown in Table 3 times the nominal wall thickness.

Table 3 - Flattening factor

Nominal Wall Thickness Inches	Nominal Wall Thickness Millimeters	Factor
Up to 0.120, incl	Up to 3.05, incl	3
Over 0.120 to 0.238, incl	Over 3.05 to 6.05, incl	4
Over 0.238 to 0.500, incl	Over 6.05 to 12.70, incl	6

3.3.1.2.1 If tubing does not pass the flattening test of 3.3.1.2, a section of tube not less than 1/2 inch (12.7 mm) in length and including one-third to one-half the circumference of the tube shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 4 times the nominal wall thickness of the tubing with axis of bend parallel to axis of tube and with inside of tube on inside of bend.

Table 4 - Bending parameters

Nominal Wall Thickness Inches	Nominal Wall Thickness Millimeters	Factor
Up to 0.120, incl	Up to 3.05, incl	1
Over 0.120 to 0.238, incl	Over 3.05 to 6.05, incl	2
Over 0.238 to 0.500, incl	Over 6.05 to 12.70, incl	4

3.3.2 Response to Heat Treatment (-T62)

Tubing shall have the properties shown in Table 5 after being solution and precipitation heat treated in accordance with AMS2772 to the -T62 temper (refer to ANSI H35.1).

Table 5A - Minimum tensile properties, inch/pound units

Nominal Wall Thickness Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches or 4D % Strip	Elongation in 2 Inches or 4D % Full Section
0.025 to 0.049, incl	42.0	35.0	8	10
Over 0.049 to 0.259, incl	42.0	35.0	10	12
Over 0.259 to 0.500, incl	42.0	35.0	12	14

Table 5B - Minimum tensile properties, SI units

Nominal Wall Thickness Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 Millimeters or 4D % Strip	Elongation in 50.8 Millimeters or 4D % Full Section
0.64 to 1.24, incl	290	241	8	10
Over 1.24 to 6.58, incl	290	241	10	12
Over 6.58 to 12.70, incl	290	241	12	14

3.3.3 Mechanical property requirements for product outside the ranges covered by Tables 2, 3, 4, and 5 shall be agreed upon between the purchaser and producer and reported per 4.4.1 (see 8.6).

3.4 Quality

Tubing, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the tubing.

Detrimental imperfections include, but are not limited to, cracks, folds, splits, seams, inclusions, or severe cross-hatching (surface breaks) that cannot be removed by light hand-sanding, using 180 grit or finer sandpaper. The requirements of 3.5 shall be met after sanding.

3.5 Tolerances

Except as specified in 3.5.1 for mean diameter and 3.5.2 for wall thickness, tolerances shall conform to all applicable requirements of ANSI H35.2 or ANSI H.35.2M.

3.5.1 Mean Diameter

Shall be shown in Table 6.

Table 6A - Tolerances, mean diameter, inch/pound units

Nominal OD Inches	Tolerance, Inches Plus and Minus
0.500 to 1.000, incl	0.002
Over 1.000 to 3.000, incl	0.003
Over 3.000 to 5.000, incl	0.004
Over 5.000 to 6.000, incl	0.005
Over 6.000 to 8.000, incl	0.008
Over 8.000 to 10.000, incl	0.010
Over 10.000 to 12.000, incl	0.013

Table 6B - Tolerances, mean diameter, SI units

Nominal OD Millimeters	Tolerance, Millimeters Plus and Minus
12.70 to 25.40, incl	0.05
Over 25.40 to 76.20, incl	0.08
Over 76.20 to 127.00, incl	0.10
Over 127.00 to 152.40, incl	0.13
Over 152.40 to 203.20, incl	0.20
Over 203.20 to 254.00, incl	0.25
Over 254.00 to 304.80, incl	0.33

3.5.1.1 Mean diameter is the average of two measurements taken at right angles to each other at the same longitudinal location on the tube.

3.5.2 Wall Thickness

Should be $\pm 7\%$ or ± 0.002 inch (± 0.05 mm), whichever is greater, for wall thicknesses under 0.035 inch (0.89 mm); $\pm 7\%$ or ± 0.003 inch (± 0.08 mm), whichever is greater, for wall thicknesses of 0.035 inch (0.89 mm) and over.

3.6 Exceptions

Any exceptions shall be authorized by the purchaser and reported as in 4.4.1.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The producer of tubing shall supply all samples for the producer's tests and shall be responsible for the performance of all required tests. The purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (see 3.1), tensile properties as annealed (see 3.3.1.1) and after solution heat treatment and aging (see 3.3.2.1), quality (see 3.4), and tolerances (see 3.5) are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.2 Periodic Tests

Flattening tests (see 3.3.1.2) are periodic tests and shall be performed at a frequency selected by the producer unless frequency of testing is specified by the purchaser.

4.3 Sampling and Testing

Shall be in accordance with AMS2355 and as specified herein.

4.4 Reports

The producer of the product shall furnish with each shipment a report stating that the product conforms to the composition and tolerances and showing the results of tests to determine conformance to the other acceptance test requirements. This report shall include the product form, purchase order number, inspection lot number, AMS4079J, size, and quantity. The report shall also include the producer, producer lot number, and the size of the mill product.