

# AEROSPACE MATERIAL SPECIFICATION



**AMS 4095B**

Issued NOV 1969  
Revised OCT 1993  
Reaffirmed SEP 2000

Superseding AMS 4095A

Aluminum Alloy, Alclad Sheet and Plate  
6.3Cu - 0.30Mn - 0.18Zr - 0.10V - 0.06Ti  
Alclad 2219-T31; Sheet, Solution Heat Treated and Cold Worked  
Alclad 2219-T351; Plate, Solution Heat Treated and Stress Relieved

UNS A82219

## 1. SCOPE:

### 1.1 Form:

This specification covers an aluminum alloy in the form of alclad sheet and plate.

### 1.2 Application:

These products have been used typically for parts requiring high strength up to 600 °F (316 °C) and are also well suited for cryogenic applications and where welding and maximum corrosion resistance are required, but usage is not limited to such applications.

- 1.2.1 Certain design and processing procedures may cause these products to become susceptible to stress-corrosion cracking after heat treatment; ARP823 recommends practices to minimize such conditions.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:  
TO PLACE A DOCUMENT ORDER:  
SAE WEB ADDRESS:

(724) 772-7161  
(724) 776-4970  
<http://www.sae.org>

FAX: (724) 776-0243  
FAX: (724) 776-0790

## 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

|          |                                                                                                                                                                                    |
|----------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| AMS 2202 | Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate                                                                                                                     |
| MAM 2202 | Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate                                                                                                             |
| AMS 2355 | Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings                    |
| MAM 2355 | Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units |
| AMS 2770 | Heat Treatment of Wrought Aluminum Alloy Parts                                                                                                                                     |
| AMS 2811 | Identification, Aluminum and Magnesium Alloy Wrought Products                                                                                                                      |
| ARP823   | Minimizing Stress-Corrosion Cracking in Wrought Heat-Treatable Aluminum Alloy Products                                                                                             |

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

## 2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-H-6088 Heat Treatment of Aluminum Alloys

## 3. TECHNICAL REQUIREMENTS:

### 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1 and Table 2, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition Core (2219)

| Element                 | Min       | Max  |
|-------------------------|-----------|------|
| Copper                  | 5.8       | 6.8  |
| Manganese               | 0.20      | 0.40 |
| Zirconium               | 0.10      | 0.25 |
| Vanadium                | 0.05      | 0.15 |
| Titanium                | 0.02      | 0.10 |
| Iron                    | --        | 0.30 |
| Silicon                 | --        | 0.20 |
| Zinc                    | --        | 0.10 |
| Magnesium               | --        | 0.02 |
| Other Impurities, each  | --        | 0.05 |
| Other Impurities, total | --        | 0.15 |
| Aluminum                | remainder |      |

TABLE 2 - Composition Cladding (7072)

| Element                 | Min       | Max  |
|-------------------------|-----------|------|
| Zinc                    | 0.08      | 1.3  |
| Silicon + Iron          | --        | 0.7  |
| Magnesium               | --        | 0.10 |
| Copper                  | --        | 0.10 |
| Manganese               | --        | 0.10 |
| Other Impurities, each  | --        | 0.05 |
| Other Impurities, total | --        | 0.15 |
| Aluminum                | remainder |      |

## 3.2 Condition:

The product shall be supplied in the following condition; heat treatment shall be performed in accordance with MIL-H-6088.

## 3.2.1 Sheet: Solution heat treated and cold worked.

## 3.2.2 Plate: Solution heat treated and stress relieved by stretching to produce a permanent set of 1-1/2 to 3%.

## 3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

### 3.3.1 As Solution Heat Treated and Cold Worked or Stress Relieved:

#### 3.3.1.1 Tensile Properties: Shall be as specified in Table 3.

TABLE 3A - Minimum Tensile Properties, Inch/Pound Units

| Nominal Thickness<br>Inch | Tensile<br>Strength<br>ksi | Yield Strength<br>at 0.2% Offset<br>ksi | Elongation<br>in 2 Inches<br>or 4D<br>% |
|---------------------------|----------------------------|-----------------------------------------|-----------------------------------------|
| 0.040 to 0.099, incl      | 42.0                       | 25.0                                    | 10                                      |
| Over 0.099 to 0.499, incl | 44.0                       | 26.0                                    | 10                                      |

TABLE 3B - Minimum Tensile Properties, SI Units

| Nominal Thickness<br>mm  | Tensile<br>Strength<br>MPa | Yield Strength<br>at 0.2% Offset<br>MPa | Elongation<br>in 50.8 mm<br>or 4D, % |
|--------------------------|----------------------------|-----------------------------------------|--------------------------------------|
| 1.02 to 2.51, incl       | 290                        | 172                                     | 10                                   |
| Over 2.51 to 12.67, incl | 303                        | 179                                     | 10                                   |

#### 3.3.1.2 Bending: Product shall withstand, without cracking, bending at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 4 times the nominal thickness of the product with axis of bend parallel to the direction of rolling.

TABLE 4 - Bending Parameters

| Nominal Thickness<br>Inch | Nominal Thickness<br>mm  | Bend<br>Factor |
|---------------------------|--------------------------|----------------|
| 0.006 to 0.020, incl      | 0.15 to 0.51, incl       | 8              |
| Over 0.020 to 0.249, incl | Over 0.51 to 6.32, incl  | 12             |
| Over 0.249 to 0.500, excl | Over 6.32 to 12.70, excl | 16             |

### 3.3.2 After Precipitation Heat Treatment: Product 0.020 to 0.499 inch (0.57 to 12.67 mm), inclusive, in nominal thickness shall have the following properties after being precipitation heat treated in accordance with AMS 2770.

#### 3.3.2.1 Tensile Properties: The product shall have the properties shown in Table 5.

TABLE 5A - Minimum Tensile Properties, Inch/Pound Units

| Nominal Thickness<br>Inch | Tensile<br>Strength<br>ksi | Yield Strength<br>at 0.2% Offset<br>ksi | Elongation<br>in 2 Inches<br>or 4D<br>% |
|---------------------------|----------------------------|-----------------------------------------|-----------------------------------------|
| 0.020 to 0.039, incl      | 49.0                       | 37.0                                    | 6                                       |
| Over 0.039 to 0.099, incl | 55.0                       | 41.0                                    | 7                                       |
| Over 0.099 to 0.249, incl | 58.0                       | 43.0                                    | 7                                       |
| Over 0.249 to 0.499, incl | 58.0                       | 42.0                                    | 8                                       |

TABLE 5B - Minimum Tensile Properties, SI Units

| Nominal Thickness<br>mm  | Tensile<br>Strength<br>ksi | Yield Strength<br>at 0.2% Offset<br>ksi | Elongation<br>in 50.8 mm<br>or 4D<br>% |
|--------------------------|----------------------------|-----------------------------------------|----------------------------------------|
| 0.51 to 0.99, incl       | 338                        | 255                                     | 6                                      |
| Over 0.99 to 2.51, incl  | 379                        | 283                                     | 7                                      |
| Over 2.51 to 6.32, incl  | 400                        | 296                                     | 7                                      |
| Over 6.32 to 12.67, incl | 400                        | 290                                     | 8                                      |

- 3.3.3 Cladding Thickness: After rolling, the average cladding thickness shall conform to the requirements shown in Table 5.

TABLE 6 - Average Cladding Thickness

| Nominal Thickness<br>Inch | Nominal Thickness<br>mm  | Cladding<br>Thickness<br>Per Side,<br>% of<br>Total<br>Thickness<br>Min | Cladding<br>Thickness<br>Per Side,<br>% of<br>Total<br>Thickness<br>Max |
|---------------------------|--------------------------|-------------------------------------------------------------------------|-------------------------------------------------------------------------|
| 0.020 to 0.039, incl      | 0.51 to 0.99, incl       | 8                                                                       | --                                                                      |
| 0.039 to 0.099, incl      | Over 0.99 to 2.51, incl  | 4                                                                       | --                                                                      |
| Over 0.099 to 0.499, incl | Over 2.51 to 12.67, incl | 2                                                                       | --                                                                      |
| Over 0.499                | Over 12.67               | 2                                                                       | 3                                                                       |

### 3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

### 3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

## 4. QUALITY ASSURANCE PROVISIONS:

### 4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for composition (3.1), tensile properties as solution heat treated and cold worked or stress relieved (3.3.1.1), and tolerances (3.5) are acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests for bending as solution heat treated and cold worked or stress relieved (3.3.1.2), tensile properties after precipitation heat treatment (3.3.2.1) and cladding thickness (3.3.3) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

### 4.3 Sampling and Testing:

Shall be in accordance with AMS 2355 or MAM 2355.

### 4.4 Reports:

The vendor of the product shall furnish with each shipment a report stating that the product conforms to the chemical composition and showing the results of tests on each lot to determine conformance to the other acceptance test requirements and, when performed, to the periodic test requirements. This report shall include the purchase order number, lot number, AMS 4095B, size, and quantity.

### 4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355 or MAM 2355.