



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AMS 4108

Issued 6-15-75

Revised

ALUMINUM ALLOY HAND FORGINGS

6.2Zn - 2.3Cu - 2.2Mg - 0.12Zr (7050-T73652)

Solution Heat Treated, Compression Stress-Relieved, and Precipitation Heat Treated

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of high-strength hand forgings with thicknesses to 8 in. (203 mm) and of forging stock.

1.2 Application: Primarily for structural, machined parts subject to warpage during machining and requiring superior strength and resistance to stress-corrosion cracking.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, Pennsylvania 15096.

2.1.1 Aerospace Material Specifications:

AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Drawn

AMS 2350 - Standards and Test Methods

AMS 2375 - Approval and Control of Critical Forgings

AMS 2630 - Ultrasonic Inspection

AMS 2645 - Fluorescent Penetrant Inspection

AMS 2808 - Identification, Forgings

2.2 ASTM Publications: Available from American Society of Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

ASTM B342 - Electrical Conductivity by Use of Eddy Currents

ASTM B557 - Tension Testing Wrought and Cast Aluminum and Magnesium Alloy Products

ASTM E10 - Brinell Hardness of Metallic Materials

ASTM E34 - Chemical Analysis of Aluminum and Aluminum-Base Alloys

2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, Pennsylvania 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

SAE Technical Board rules provide that: "All technical reports, including standards, approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

	min	max
Zinc	5.7	- 6.7
Copper	2.0	- 2.6
Magnesium	1.9	- 2.6
Zirconium	0.08	- 0.15
Iron	--	0.15
Silicon	--	0.12
Manganese	--	0.10
Titanium	--	0.06
Chromium	--	0.04
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Forgings: Solution heat treated, stress-relieved by compressing, and precipitation heat treated.

3.2.2 Forging Stock: As ordered by the forging manufacturer.

3.3 Heat Treatment: Hand forgings shall be solution heat treated by heating to $890^{\circ}\text{F} \pm 10$ ($476.7^{\circ}\text{C} \pm 5.6$), holding at heat for a time commensurate with section thickness but not less than 60 min., and quenching in water at 140°F to 160°F (60°C to 71.1°C), stress-relieved by compressing to produce a permanent set of 1-5%, and precipitation heat treated by heating to $250^{\circ}\text{F} \pm 10$ ($121.1^{\circ}\text{C} \pm 5.6$), holding at heat for 24 hr ± 1 , heating to $350^{\circ}\text{F} \pm 10$ ($176.7^{\circ}\text{C} \pm 5.6$), holding at heat for 8 hr ± 1 , and cooling in air.

- 3.4 Properties: The product shall conform to the following requirements:

3.4.1 Forgings:

3.4.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B557. Test specimens machined from hand forgings having essentially a rectangular or square section heat treated in the indicated thickness shall conform to the requirements shown in Table I, provided that the as-forged thickness does not exceed 8.0 in. (203 mm). The direction of long transverse for squares shall be as identified by the vendor.

TABLE I

Nominal Thickness At Time Of Heat Treatment Inches	Direction	Tensile Strength psi, min	Yield Strength at 0.2% Offset psi, min	Elongation in 2 in. or 4D %, min
Up to 2, incl	Longitudinal	72,000	63,000	9
	Long Trans.	71,000	61,000	5
Over 2 to 3, incl	Longitudinal	72,000	62,000	9
	Long Trans.	70,000	60,000	5
	Short Trans.	67,000	55,000	4
Over 3 to 4, incl	Longitudinal	71,000	61,000	9
	Long Trans.	70,000	59,000	5
	Short Trans.	67,000	55,000	4
Over 4 to 5, incl	Longitudinal	70,000	60,000	9
	Long Trans.	69,000	58,000	4
	Short Trans.	66,000	54,000	3
Over 5 to 6, incl	Longitudinal	69,000	59,000	9
	Long Trans.	68,000	56,000	4
	Short Trans.	66,000	53,000	3
Over 6 to 7, incl	Longitudinal	68,000	58,000	9
	Long Trans.	67,000	54,000	4
	Short Trans.	65,000	51,000	3
Over 7 to 8, incl	Longitudinal	67,000	57,000	9
	Long Trans.	66,000	52,000	4
	Short Trans.	64,000	50,000	3

TABLE I (SI)

Nominal Thickness At Time Of Heat Treatment Millimetres	Direction	Tensile Strength MPa, min	Yield Strength at 0.2% Offset MPa, min	Elongation in 50.8 mm or 4D %, min
Up to 51, incl	Longitudinal	496	434	9
	Long Trans.	490	421	5
Over 51 to 76, incl	Longitudinal	496	427	9
	Long Trans.	483	414	5
	Short Trans.	462	379	4
Over 76 to 102, incl	Longitudinal	490	421	9
	Long Trans.	483	407	5
	Short Trans.	462	379	4
Over 102 to 127, incl	Longitudinal	483	414	9
	Long Trans.	476	400	4
	Short Trans.	455	372	3
Over 127 to 152, incl	Longitudinal	476	407	9
	Long Trans.	469	386	4
	Short Trans.	455	365	3
Over 152 to 178, incl	Longitudinal	469	400	9
	Long Trans.	462	372	4
	Short Trans.	448	352	3
Over 178 to 203, incl	Longitudinal	462	393	9
	Long. Trans.	455	359	4
	Short Trans.	441	345	3

3.4.1.1.1 **Special Purpose Forgings:** Tensile specimens cut from special purpose forgings or forgings beyond the size and configuration limits covered by this specification shall conform to the tensile property requirements specified on the drawing or agreed upon by purchaser and vendor.

3.4.1.2 **Hardness:** Should be not lower than 135 HB/10/500 or 135 HB/14.3/1000, or not lower than 140 HB/10/1000, determined in accordance with ASTM E10, but forgings shall not be rejected on the basis of hardness if the tensile property requirements are met.

3.4.1.3 **Conductivity:** Shall be as follows, determined in accordance with ASTM B342:

3.4.1.3.1 If the conductivity is 40% IACS (International Annealed Copper Standard) or higher and the yield strength in the parallel grain direction does not exceed the minimum specified in Table I by more than 9000 psi (62.1 MPa), the forgings are considered satisfactory.

3.4.1.3.2 If the conductivity is 40% IACS or higher and the yield strength in the parallel grain direction exceeds the minimum specified in Table I by more than 9000 psi (62.1 MPa), the forgings shall be subjected to additional precipitation heat treatment to meet the requirements of 3.4.1.3.1.