

AEROSPACE

MATERIAL SPECIFICATIONS

AMS 4110

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N.Y. 10017

Issued 2-15-65

Revised

ALUMINUM ALLOY BARS, ROLLED, OR COLD FINISHED

4.0Cu - 0.7Mn - 0.50Mg (2017-T451)

Stress-Relief Stretched

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Bars and rods.
3. **APPLICATION:** Primarily for machined parts subject to excessive warpage during machining due to residual stresses, and for parts requiring good strength and whose fabrication does not involve welding. Certain design and processing procedures may cause this material to be susceptible to stress corrosion cracking; ARP 823 recommends practices to minimize such conditions.

4. **COMPOSITION:**

	min	max
Copper	3.5	4.5
Manganese	0.40	1.0
Magnesium	0.20	0.8
Iron		1.0
Silicon	--	0.8
Zinc	--	0.25
Chromium	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

5. **CONDITION:** Rolled or cold finished, solution heat treated, and stress-relieved by stretching.
 - 5.1 Material shall be stretched in the solution heat treated condition to produce a nominal permanent set of 1-1/2%, but not less than 1% nor more than 3%.
 - 5.2 Material shall receive no further straightening operations after stretching, unless specifically authorized.

6. **TECHNICAL REQUIREMENTS:**

- 6.1 **Tensile Properties:** Except as specified in 6.1.2, the following requirements apply to bars 0.500 in. and over in least distance between parallel sides and to rods 0.500 in. and over in diameter:

Tensile Strength, psi	55,000 min
Yield Strength at 0.2% Offset or at 0.0102 in.	
in 2 in. Extension Under Load (E = 10,400,000), psi	32,000 min
Elongation, % in 2 in. or 4D	12 min

- 6.1.1 When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.
- 6.1.2 Tensile properties shall be as agreed upon by purchaser and vendor for rounds over 8.000 in. in diameter and for squares, hexagons, octagons, and rectangles having a cross sectional area over 50 sq inches.