



AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N.Y. 10017

AMS 4115A

Issued 1-15-60
Revised 3-15-66

ALUMINUM ALLOY BARS, ROLLED, DRAWN, OR COLD FINISHED 1.0Mg - 0.60Si - 0.30Cu - 0.20Cr (6061-0)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. FORM: Bars, rods, and wire.
3. APPLICATION: Primarily for parts requiring moderate strength, especially where such parts and assemblies require brazing or welding during fabrication.
4. COMPOSITION:

	min	max
Magnesium	0.8	- 1.2
Silicon	0.40	- 0.8
Copper	0.15	- 0.40
Chromium	0.04	- 0.35
Iron	--	0.7
Zinc	--	0.25
Manganese	--	0.15
Titanium	--	0.15
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

5. CONDITION: Rolled, drawn, or cold finished, as ordered, and annealed.
6. TECHNICAL REQUIREMENTS: The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.
- 6.1 Tensile Properties: Except as specified in 6.1.1 and 6.1.2, the following requirements apply to all sizes:

Tensile Strength, psi	22,000 max
Elongation, % in 2 in. or 4D	18 min

- 6.1.1 Elongation requirements do not apply to material under 0.125 inch.
- 6.1.2 Tensile properties of material over 8.0 in. in diameter or distance between parallel sides shall be as agreed upon by purchaser and vendor.
- 6.2 Hardness: Material should have hardness not higher than Brinell 40 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or not higher than Brinell 45 using 1000 kg load and 10 mm ball, but shall not be rejected on the basis of hardness if the tensile property requirements are met.

SAE Technical Board rules provide that: "All technical reports, including standards, specifications, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."