



Society of Automotive Engineers, Inc.
400 COMMONWEALTH DRIVE, WARRENDALE, PA. 15096

AEROSPACE MATERIAL SPECIFICATION

AMS 4127D

Superseding AMS 4127C

Issued 5-1-54
Revised 7-1-76

UNS A96061

ALUMINUM ALLOY FORGINGS
1.0Mg - 0.60Si - 0.28Cu - 0.20Cr (6061-T6)

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of die forgings, rolled rings, and forging stock.
- 1.2 Application: Primarily for complex shaped parts requiring moderate strength and good forgeability of the material. Corrosion resistance of this alloy is superior to that of alloys having copper as the principal alloying element.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Drawn
AMS 2350 - Standards and Test Methods
AMS 2375 - Approval and Control of Critical Forgings
AMS 2630 - Ultrasonic Inspection
AMS 2645 - Fluorescent Penetrant Inspection
AMS 2808 - Identification, Forgings

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM B557 - Tension Testing Wrought and Cast Aluminum and Magnesium Alloy Products
ASTM E10 - Brinell Hardness of Metallic Materials
ASTM E34 - Chemical Analysis of Aluminum and Aluminum-Base Alloys

- 2.3 Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

2.3.3 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

SAE Technical Board rules provide that: "All technical reports, including standards approved, and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods:

		min	max
Ø	Magnesium	0.80	1.2
	Silicon	0.40	0.8
	Copper	0.15	0.40
	Chromium	0.04	0.35
	Iron	--	0.7
	Zinc	--	0.25
	Manganese	--	0.15
	Titanium	--	0.15
	Other Impurities, each	--	0.05
	Other Impurities, total	--	0.15
	Aluminum	remainder	

- 3.2 Condition: The product shall be supplied in the following condition:

- Ø 3.2.1 Die Forgings and Rolled Rings: Solution and precipitation heat treated in accordance with MIL-H-6088.

- 3.2.2 Forging Stock: As ordered by the forging manufacturer.

- 3.3 Properties: The product shall conform to the following requirements:

- 3.3.1 Die Forgings and Rolled Rings:

- Ø 3.3.1.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B557:

- 3.3.1.1.1 Test Specimens: Test specimens, machined from separately-forged coupons or from forging stock representing the forgings and, in either case, heat treated with the forgings or machined from prolongations on heat treated forgings, shall have the following properties:

Tensile Strength, min	38,000 psi (262 MPa)
Yield Strength at 0.2% Offset, min	35,000 psi (241 MPa)
Elongation in 2 in. (50.8 mm) or 4D, min	10%

- 3.3.1.1.2 Forgings, With Grain Flow: Test specimens, machined from forgings not over 4 in. (102 mm) in nominal thickness with the axis of specimen in the area of gage length within 15 deg (0.262 rad) of parallel to the forging flow lines, shall have properties as specified in 3.3.1.1.1 except that elongation may be as low as 7%, unless otherwise agreed upon by purchaser and vendor.

- 3.3.1.1.3 Forgings, Across Grain Flow: Test specimens, machined from die forgings not over 4 in. (102 mm) in nominal thickness with axis of specimen in the area of gage length varying more than 15 deg (0.262 rad) from parallel to the forging flow lines, shall have properties as specified in 3.3.1.1.1 except that elongation may be as low as 5%, unless otherwise agreed upon by purchaser and vendor.

- 3.3.1.1.4 Rings, Tangential: Test specimens, machined from rings not over 2.5 in. (64 mm) in nominal thickness with axis of specimen tangential to ring OD (axis parallel to direction of rolling), shall have properties as specified in 3.3.1.1.1, unless otherwise agreed upon by purchaser and vendor.

- 3.3.1.1.5 Rings, Axial: Test specimens, machined from rings not over 2.5 in. (64 mm) in nominal thickness with axis of specimen parallel to axis of the ring (axis transverse to direction of rolling), shall have properties as specified in 3.3.1.1.1 except that elongation may be as low as 8%, unless otherwise agreed upon by purchaser and vendor.
- 3.3.1.2 Hardness: Should be not lower than 80 HB/10/500, 80 HB/14.3/1000, or 85 HB/10/1000, determined in accordance with ASTM E10, but the product shall not be rejected on the basis of hardness if the tensile property requirements are met.
- 3.3.2 Forging Stock: When a sample of stock is forged to a test coupon and heat treated in the same manner as forgings, specimens taken from the heat treated coupon shall conform to the requirements of 3.3.1.1.1 and 3.3.1.2. If specimens taken from the stock after heat treatment in the same manner as forgings conform to the requirements of 3.3.1.1.1 and 3.3.1.2, the tests shall be accepted as equivalent to tests of a forged coupon. The forging stock supplier, however, shall not be required to conduct such tests.
- 3.4 Quality: The product, as received by the purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the product.
- 3.4.1 When specified, forgings and rolled rings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645 and/or to ultrasonic inspection in accordance with AMS 2630. Standards for acceptance shall be as agreed upon by purchaser and vendor.
- 3.5 Tolerances: Unless otherwise specified, tolerances for forging stock shall conform to all applicable requirements of AMS 2201.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of the product shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to ensure that the product conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Acceptance Tests: Tests of the product to determine conformance to composition (3.1) requirements and of forgings and rings to determine conformance to tensile property (3.3.1.1) requirements are classified as acceptance tests.
- 4.2.2 Periodic Tests: Tests of forgings and rings to determine conformance to hardness (3.3.1.2) requirements and of forging stock to determine ability to develop required properties (3.3.2) are classified as periodic tests.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.
- 4.3 Sampling: Shall be as follows; a lot shall be all forgings or rings of the same part number, size, or nominal cross-section and configuration heat treated in the same batch furnace load or in a continuous furnace consecutively during an 8-hr period.
- 4.3.1 Composition: At least one sample shall be taken by the producer from each group of ingots poured simultaneously from the same source of molten metal.

- 4.3.1.1 Unless compliance with 4.3.1 is established, an analysis shall be made for each 6000 lb (2724 kg) or less of material comprising the lot except that not more than one analysis shall be required per piece.

4.3.2 Tensile Properties:

- 4.3.2.1 Forgings: At least one separately-forged coupon or one forging prolongation, heat treated with each lot of forgings, shall be tested.

- 4.3.2.1.1 In lieu of a prolongation or separately-forged coupon, tensile tests shall be conducted on specimens cut, in locations designated on the drawing, from a forging representing each lot.

- 4.3.2.2 Rolled Rings: At least two tensile test specimens, taken from a ring or ring prolongation representing the lot, shall be tested. One specimen shall be taken tangential to the ring OD and the other parallel to the axis of the ring.

- 4.4 Approval: When specified, approval and control of forgings shall be in accordance with AMS 2375.

4.5 Reports:

- 4.5.1 The vendor of forgings or rings shall furnish with each shipment three copies of a report stating that the chemical composition conforms to the requirements of this specification and showing the results of tests on each lot to determine conformance to the other acceptance test requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, size or part number, and quantity.

- 4.5.2 The vendor of forging stock shall furnish with each shipment three copies of a report stating that the chemical composition of the stock conforms to the requirements of this specification. This report shall include the purchase order number, material specification number and its revision letter, size, and quantity.

- 4.5.3 The vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number and its revision letter, contractor or other direct supplier of material, part number, and quantity. When material for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of material to determine conformance to the requirements of this specification, and shall include in the report a statement that the material conforms, or shall include copies of laboratory reports showing the results of tests to determine conformance.

- 4.6 Resampling and Retesting: If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing two additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented and no additional testing shall be permitted. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

- 5.1 Identification: The product shall be identified as follows:

- 5.1.1 Forgings and Rings: In accordance with AMS 2808.

- 5.1.2 Forging Stock: As agreed upon by purchaser and vendor.