

# AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.  
29 West 39th Street  
New York City

## AMS 4130 A

Issued 3-13-40

Revised 8-1-42

### ALUMINUM ALLOY FORGINGS Copper Silicon Manganese (25S-T)

1. ACKNOWLEDGMENT: A vendor must mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

|                         |                         |           |
|-------------------------|-------------------------|-----------|
| 2. <u>COMPOSITION</u> : | Copper                  | 3.9 - 5.0 |
|                         | Silicon                 | 0.5 - 1.2 |
|                         | Manganese               | 0.4 - 1.2 |
|                         | Magnesium               | 0.03 max  |
|                         | Iron                    | 1.0 max   |
|                         | Zinc                    | 0.25 max  |
|                         | Chromium                | 0.10 max  |
|                         | Other Impurities, each  | 0.05 max  |
|                         | Other Impurities, total | 0.15 max  |
|                         | Aluminum                | remainder |

3. CONDITION: (a) Quenched and aged. The quenching rate shall be fast enough for the material to meet the following requirements, but must be as slow as practicable in order to keep the internal stresses at a minimum.

(b) Tensile test bars may be machined from a portion of the purchased material parallel to the direction of metal flow, or from separately forged coupons made from the same lot of material and heat treated with the forgings which they represent. These test bars representing forgings up to 4 inches in diameter or least thickness shall conform to the following minimum physical properties:

|                                                |        |
|------------------------------------------------|--------|
| Tensile Strength, lb per sq inch.              | 55,000 |
| Yield Strength (0.2% Set), lb per sq in.       | 30,000 |
| Equivalent Extension Under Load, inch in 2 in. | 0.0098 |
| Elongation, % in 2 in.                         | 16     |
| Brinell Hardness                               | 100    |

(c) Forgings shall have a hardness of not less than Brinell 100, or the equivalent.

4. QUALITY: The material shall be uniform in quality and temper, free from blisters, fins, seams, laps, segregations, and other defects which adversely affect its strength, use, or machinability. It is subject to coarse etching and any other tests necessary to insure high quality. If material defects are revealed while machining the parts, the material is subject to rejection.
5. REPORTS: The manufacturer shall furnish three copies of a notarized report stating that the physical properties and chemical composition of the material are within the requirements specified. This report shall include the purchase order number, material specification number, size or part number, and quantity.
6. IDENTIFICATION: Forgings shall be identified in accordance with AMS 2808.