

AEROSPACE MATERIAL SPECIFICATION

SAE AMS4140J

Issued	1942-01
Revised	2001-06
Reaffirmed	2006-04
Noncurrent	2009-08

Superseding AMS4140H

Aluminum Alloy Die Forgings
4.0Cu – 2.0Ni – 0.68Mg (2018-T61)
Solution and Precipitation Heat Treated

(Composition similar to UNS A92018)

RATIONALE

AMS4140J has been designated for Non-Current based on results of a survey to aerospace users and producers.

NONCURRENCY NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of August 2009. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which may have been widely used previously and which may be required for production or processing of existing designs in the future. The Aerospace Materials Division, however, does not recommend these specifications for future use in new designs.

"NONCURRENT" specifications are available from SAE upon request.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2009 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4140J>**

 SAE The Engineering Society For Advancing Mobility Land Sea Air and Space® 400 Commonwealth Drive, Warrendale, PA 15096-0001	AEROSPACE MATERIAL SPECIFICATION	 AMS 4140H												
<table> <tr> <td>Issued</td> <td>JAN 1942</td> </tr> <tr> <td>Revised</td> <td>JUN 2001</td> </tr> <tr> <td>Reaffirmed</td> <td>APR 2006</td> </tr> <tr> <td colspan="2">Superseding AMS 4140G</td> </tr> </table>		Issued	JAN 1942	Revised	JUN 2001	Reaffirmed	APR 2006	Superseding AMS 4140G						
Issued	JAN 1942													
Revised	JUN 2001													
Reaffirmed	APR 2006													
Superseding AMS 4140G														
Aluminum Alloy Die Forgings 4.0Cu - 2.0Ni - 0.68Mg (2018-T61) Solution and Precipitation Heat Treated (Composition similar to UNS A92018)														
1. SCOPE: 1.1 Form: This specification covers an aluminum alloy in the form of die forgings and forging stock. 1.2 Application: This product has been used typically for small, forged parts for aircraft engines, but usage is not limited to such applications. 2. APPLICABLE DOCUMENTS: The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply. 2.1 SAE Publications: <table style="margin-left: 40px;"> <tr> <td colspan="2">Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or http://www.sae.org.</td> </tr> <tr> <td style="vertical-align: top;">AMS 2355</td> <td>Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings</td> </tr> <tr> <td style="vertical-align: top;">MAM 2355</td> <td>Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units</td> </tr> <tr> <td style="vertical-align: top;">AMS 2772</td> <td>Heat Treatment of Aluminum Alloy Raw Materials</td> </tr> <tr> <td style="vertical-align: top;">AMS 2808</td> <td>Identification, Forgings</td> </tr> <tr> <td style="vertical-align: top;">ARP823</td> <td>Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products</td> </tr> </table>			Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or http://www.sae.org .		AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings	MAM 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units	AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials	AMS 2808	Identification, Forgings	ARP823	Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products
Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or http://www.sae.org .														
AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings													
MAM 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units													
AMS 2772	Heat Treatment of Aluminum Alloy Raw Materials													
AMS 2808	Identification, Forgings													
ARP823	Minimizing Stress Corrosion Cracking in Wrought Heat Treatable Aluminum Alloy Products													

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

AMS 4140H**SAE****AMS 4140H****2.2 ASTM Publications:**

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM B 594 Ultrasonic Inspection of Aluminum-Alloy Products for Aerospace Applications
 ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products
 ASTM E 1417 Liquid Penetrant Examination

2.3 ANSI Publications:

Available from ANSI, 11 West 42nd Street, New York, NY 10036-8002.

ANSI H35.2 Dimensional Tolerances for Aluminum Mill Products
 ANSI H35.2M Dimensional Tolerances for Aluminum Mill Products (Metric)

3. TECHNICAL REQUIREMENTS:**3.1 Composition:**

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	min	max
Silicon	--	0.9
Iron	--	1.0
Copper	3.5	4.5
Manganese	--	0.20
Magnesium	0.45	0.9
Chromium	--	0.10
Nickel	1.7	2.3
Zinc	--	0.25
Other Elements, each	--	0.05
Other Elements, total	--	0.15
Aluminum	remainder	

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Forgings: Solution and precipitation heat treated in accordance with AMS 2772 to the T61 temper.

AMS 4140H**SAE****AMS 4140H**

3.2.2 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355 on the mill produced size and as specified herein.

3.3.1 Forgings:

3.3.1.1 Tensile Properties: Shall be as follows:

3.3.1.1.1 Test Specimens: Specimens, machined from separately-forged coupons or from forging stock representing the forgings and, in either case, heat treated with the forgings or machined from prolongations on heat treated forgings, shall have the properties shown in Table 2:

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	55 ksi (379 MPa)
Yield Strength at 0.2% Offset	40.0 ksi (276 MPa)
Elongation in 4D	10%

3.3.1.1.2 Forgings With Grain Flow: Specimens, machined from forgings, with axis of specimen in area of gage length varying not more than 15 degrees from parallel to the forging flow lines, shall have properties as specified in Table 2.

3.3.1.2 Hardness: Shall be not lower than 100 HB/10/500 or 106 HB/10/1000, or equivalent, but forgings shall not be rejected on the basis of hardness if the tensile property requirements are met. Piston forgings shall also meet the requirements of 3.3.1.2.1.

3.3.1.2.1 Piston forgings shall retain hardness not lower than 90 HB/10/500 or 93 HB/10/1000, or equivalent, after being heated to 450 °F ± 10 (232 °C ± 6), held at heat for 5 hours ± 0.2, and cooled in air.

3.3.1.3 Grain Flow: Except in areas of forgings which contain flash-line end grain, grain flow shall follow the general contour of the forging showing no evidence of re-entrant grain flow.

3.3.2 Forging Stock: When a sample of stock is forged to a test coupon having a degree of mechanical working not greater than the forging and heat treated in the same manner as forgings, specimens taken from the heat treated coupon shall conform to the requirements of 3.3.1.1.1. If specimens taken from the stock after heat treatment in the same manner as forgings conform to the requirements of 3.3.1.1.1, the tests shall be accepted as equivalent to tests of a forged coupon.

AMS 4140H**SAE****AMS 4140H****3.4 Quality:**

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from conditions detrimental to usage of the product.

3.4.1 When specified, forgings shall be subjected to ultrasonic inspection in accordance with ASTM B 594 and/or to fluorescent penetrant inspection in accordance with ASTM E 1417. Standards for acceptance shall be as agreed upon by purchaser and vendor.

3.4.2 When specified, each forging shall be etched to produce a surface suitable for visual inspection. Surfaces shall be evaluated for conditions such as seams, laps, bursts, and quench cracks. Surface conditions which can be removed so that they do not reappear on re-etching and the required section thickness can be maintained are acceptable.

3.5 Tolerances:

Forging stock shall conform to all applicable requirements of ANSI H35.2 or ANSI H35.2M.

4. QUALITY ASSURANCE PROVISIONS:**4.1 Responsibility for Inspection:**

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition 3.1) and testing of forgings for tensile properties (3.3.1.1), hardness (3.3.1.2), quality (3.4) and, when specified, ultrasonic and/or fluorescent penetrant inspection (3.4.1), etching and visual inspection (3.4.2), are acceptance tests and, except for composition, shall be performed on each lot.

4.2.2 Periodic Tests: Tests of forgings for grain flow (3.3.1.3) and, when applicable, hardness retention (3.3.1.2.1) and of forging stock to determine ability to develop required properties (3.3.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2355 or MAM 2355 and the following:

4.3.1 Ultrasonic and Fluorescent Penetrant Inspection (3.4.1): All die forgings, when specified.

4.3.2 Surface Conditions (3.4.2): All die forgings, when specified.