



AEROSPACE MATERIAL

AMS 4148

Society of Automotive Engineers, Inc.

SPECIFICATION

TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

Issued 5-15-71
Revised

ALUMINUM ALLOY DIE FORGINGS
5.6Zn - 2.5Mg - 1.6Cu - 0.24Cr (7175-T66)
Solution and Precipitation Heat Treated

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of high strength die forgings and forging stock.

1.2 Application: Primarily for parts requiring a high level of mechanical properties.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply; the applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from Society of Automotive Engineers, Inc., Two Pennsylvania Plaza, New York, New York 10001.

2.1.1 Aerospace Material Specifications:

AMS 2201 - Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire
and Forging Stock, Rolled or Drawn

AMS 2350 - Standards and Test Methods

AMS 2375 - Approval and Control of Critical Forgings

AMS 2808 - Identification, Forgings

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.

ASTM E8 - Tension Testing of Metallic Materials

ASTM E10 - Brinell Hardness of Metallic Materials

ASTM E34 - Chemical Analysis of Aluminum and Aluminum Base Alloys

2.3 Government Publications: Available from Superintendent of Documents, Government Printing Office, Washington, D. C. 20402.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E34, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other approved analytical methods.

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."

	min	max
Zinc	5.1	6.1
Magnesium	2.1	2.9
Copper	1.2	2.0
Chromium	0.18	0.30
Iron	--	0.20
Silicon	--	0.15
Manganese	--	0.10
Titanium	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition: The product shall be supplied in the following condition:

3.2.1 Die Forgings: Solution and precipitation heat treated to develop the required mechanical properties.

3.2.2 Forging Stock: As ordered by the forging manufacturer.

3.3 Properties:

3.3.1 Tensile Properties: Test specimens and testing procedures shall be in accordance with ASTM E8.

3.3.1.1 Die Forgings, Parallel to Grain Flow: Test specimens machined from forgings not over 3 in. (76.2 mm) in thickness, or from prolongations on such forgings, with the specimen axis approximately parallel to the forging flow lines shall conform to the following requirements:

Tensile Strength, min	86,000 psi (593 MN/m ²)
Yield Strength at 0.2% Offset, min	76,000 psi (524 MN/m ²)
Elongation in 2 in. (50.8 mm) or 4D, min	7 %

3.3.1.2 Die Forgings, Across Grain Flow: Test specimens machined from forgings not over 3 in. (76.2 mm) in thickness, or from prolongations on such forgings, so that the specimen axis is transverse to the forging flow lines shall conform to the following requirements:

Tensile Strength, min	77,000 psi (531 MN/m ²)
Yield Strength at 0.2% Offset, min	66,000 psi (455 MN/m ²)
Elongation in 2 in. (50.8 mm) or 4D, min	4 %

3.3.1.3 If the section thickness of the forging is greater than 3 in. (76.2 mm), the tensile properties (parallel and transverse to grain flow) shall be as agreed upon by purchaser and vendor.

3.3.1.4 The elongation requirement shall not apply to test specimens having a gage length diameter less than 0.25 in. (6.35 mm) or located in immediate proximity to an abrupt change in section thickness, or located so that any part of the specimen gage length is located within 1/8 in. (3.2 mm) of the trimmed flashline.

3.3.2 Hardness: Should be not lower than 140 HB/10/500 or HB/14.3/1000, or not lower than 145 HB/10/1000, determined in accordance with ASTM E10, but forgings shall not be rejected on the basis of hardness if the tensile properties are met.

3.3.3 Forging Stock: When a sample of stock is forged to a test coupon and heat treated in the same manner as forgings, tensile test specimens taken from the heat treated coupon shall have properties not lower than those specified in 3.3.1.1, 3.3.1.2, and 3.3.2. If test specimens taken from the stock after heat treatment in the same manner as forgings have properties not lower than those specified in 3.3.1.1, 3.3.1.2, and 3.3.2, the tests shall be accepted as equivalent to tests of a forged coupon.

- 3.4 Quality: The product shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.
- 3.5 Tolerances: Unless otherwise specified, tolerances for forging stock shall conform to all applicable requirements of AMS 2201.

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor shall supply all samples and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to perform such confirmatory testing as he deems necessary to assure that material conforms to the requirements of this specification.
- 4.2 Classification of Tests:
- 4.2.1 Routine Control Tests: Tests of die forgings to determine conformance to all technical requirements of this specification and of forging stock to determine conformance to composition (3.1) requirements of this specification are classified as routine control tests.
- 4.2.2 Periodic Control Tests: Tests of forging stock to determine conformance to the requirements of 3.3.3 are classified as qualification and/or periodic control tests.
- 4.3 Sampling:
- 4.3.1 At least one sample shall be taken from each group of ingots poured simultaneously from the same source of molten metal by the producer and analyzed to determine conformance to 3.1. Ingots not conforming to this specification shall be rejected. Complete ingot analysis records shall be available to the purchaser.
- 4.3.1.1 Unless compliance with 4.3.1 is established, an analysis shall be made for each 6000 lb (2724 kg) or less of material comprising the lot, except that not more than one analysis shall be required per piece.
- 4.3.2 Unless otherwise specified, at least two specimens shall be taken from a forging in each lot or from a forging prolongation representative of forgings in each lot to determine conformance to 3.3.1. One specimen shall be taken with axis parallel to grain flow and one with axis across grain flow.
- 4.3.3 A lot shall consist of all forgings of the same configuration heat treated and aged together. For forgings heat treated in a continuous furnace maximum lot size shall be 2000 lb (908 kg) of forgings weighing 5 lb (2.3 kg) or less, or 6000 lb (2724 kg) of forgings weighing over 5 lb (2.3 kg), and charged consecutively during continuous furnace operation.
- 4.4 Approval: When specified, approval and control of critical forgings shall be in accordance with AMS 2375.
- 4.5 Reports:
- 4.5.1 The vendor of forgings shall furnish with each shipment three copies of a report stating that the chemical composition conforms to the requirements specified in 3.1 and showing the results of tests on each lot to determine conformance to all other technical requirements of this specification. This report shall include the purchase order number, material specification number, size or part number, and quantity.