

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS4154A

Issued 10-1-45

Revised 11-1-46

ALUMINUM ALLOY BARS (EXTRUDED) Zinc Magnesium Copper (75S-T)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. FORM: Bars, rods, and shapes.

3. COMPOSITION:

Zinc	5.10 - 6.10
Magnesium	2.10 - 2.90
Copper	1.20 - 2.00
Chromium	0.15 - 0.40
Manganese	0.10 - 0.30
Iron	0.70 max
Silicon	0.50 max
Titanium	0.20 max
Other impurities, each	0.05 max
Other impurities, total	0.15 max
Aluminum	remainder

4. CONDITION: (a) Solution and precipitation heat treated conforming to the following minimum physical properties:

Diameter or Least Thickness or Area	Tensile Strength	Yield Strength at 0.2% Offset or at Extension Indicated		Elongation
			Extension Under Load	
Inches	psi	psi	Inch in 2 in.	% in 4D
Under 0.250	78,000	70,000	0.0175	6
0.250 to 4.00, incl				
20 sq. in. max	80,000	70,000	0.0175	6
Over 4.00 to 5.00 incl				
and over 20 sq. in. to				
25 sq. in., incl	78,000	68,000	0.0171	6
Over 25 sq. in. to				
32 sq. in., incl	75,000	65,000	0.0165	5

Note: The physical properties shall be based on the thickness of the portion of the extrusion from which the test specimens are taken and the physical properties of such specimens shall be in accordance with the values shown above.

(b) If sizes other than those shown under (a) are ordered, physical properties shall be as agreed between vendor and purchaser.