



AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc.

485 Lexington Ave., New York, N. Y. 10017

AMS 4160A

Issued 1-15-60
Revised 3-15-66

ALUMINUM ALLOY EXTRUSIONS 1. 0Mg - 0. 60Si - 0. 30Cu - 0.20Cr (6061-0)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. FORM: Bars, rods, wire, shapes, and tubing.

3. APPLICATION: Primarily for parts requiring moderate strength, especially where such parts and assemblies require brazing or welding during fabrication.

4. COMPOSITION:

	min	max
Magnesium	0. 8	- 1. 2
Silicon	0. 40	- 0. 8
Copper	0. 15	- 0. 40
Chromium	0. 04	- 0. 35
Iron	--	0. 7
Zinc	--	0. 25
Manganese	--	0. 15
Titanium	--	0. 15
Other Impurities, each	--	0. 05
Other Impurities, total	--	0. 15
Aluminum	remainder	

5. CONDITION: Annealed.

5. 1 Unless otherwise specified, extrusions shall be supplied with an as-extruded surface finish; light polishing to remove minor surface imperfections is permissible provided such imperfections can be removed within the dimensional tolerances.

6. TECHNICAL REQUIREMENTS: The product shall conform to the following requirements; tensile properties shall be determined in accordance with the latest issue of AMS 2355.

6. 1 Tensile Properties:

Tensile Strength, psi	22,000 max
Yield Strength at 0. 2% Offset or at 0. 0072 in. in 2 in. Extension Under Load (E = 9,900,000), psi	16,000 max
Elongation, % in 2 in. or 4D	16 min

6. 1. 1 When a dispute occurs between purchaser and vendor over the yield strength values, yield strength determined by the offset method shall apply.

6. 2 Hardness: Material should have hardness not higher than Brinell 40 using 500 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or not higher than Brinell 45 using 1000 kg load and 10 mm ball, but shall not be rejected on the basis of hardness if the tensile property requirements are met.

SAE Technical Board rules provide that: "All technical reports, including standards approved by the Board, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."