

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE AMS 4182E

Issued 1 SEP 1948
Revised 1 OCT 1993
Superseding AMS 4182D

Submitted for recognition as an American National Standard

ALUMINUM ALLOY, WIRE
5.0Mg - 0.12Mn - 0.12Cr(5056-0)
Annealed

UNS A95056

1. SCOPE:

1.1 Form:

This specification covers an aluminum alloy in the form of wire.

1.2 Application:

This wire has been used typically for the manufacture of screen for reinforcement of, and to provide electrical conductivity through, rubber gaskets, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2201	Tolerances, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled or Cold Finished
MAM 2201	Tolerances, Metric, Aluminum and Aluminum Alloy Bar, Rod, Wire, and Forging Stock, Rolled, Drawn, or Cold Finished
AMS 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings
MAM 2355	Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 4182E

SAE

AMS 4182E

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition

Element	Min	Max
Magnesium	4.5	5.6
Manganese	0.05	0.20
Chromium	0.05	0.20
Iron	--	0.40
Silicon	--	0.30
Copper	--	0.10
Zinc	--	0.10
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

3.2 Condition:

Annealed

- 3.2.1 When wire is supplied as screen, wire in one direction may be in a condition other than annealed.

3.3 Properties:

Wire shall conform to the following requirements; tensile properties shall be determined in accordance with AMS 2355 or MAM 2355:

AMS 4182E

SAE

AMS 4182E

3.3.1 Tensile Properties: Shall be as shown in Table 2.

TABLE 2 - Tensile Properties

Property	Value
Tensile Strength, max	46.0 ksi (317 MPa)
Elongation in 2 Inches (50.8 mm) or 4D, min	
Nominal Diameter	
0.125 to 0.375 inch, excl	20%
(3.18 to 9.52 mm, excl)	

3.3.2 Bending: Wire shall withstand, without cracking, bending at room temperature flat on itself.

3.4 Quality:

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the wire.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2201 or MAM 2201.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R)

The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each lot.

4.3 Sampling and Testing:

(R)

Shall be in accordance with AMS 2355 or MAM 2355.

4.4 Reports:

(R)

The vendor of wire shall furnish with each shipment a report stating that the wire conforms to the chemical composition and showing the results of tests on each lot to determine conformance to the other technical requirements. This report shall include the purchase order number, lot number, AMS 4182E, size, and quantity.

AMS 4182E

SAE

AMS 4182E

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2355 or MAM 2355.

5. PREPARATION FOR DELIVERY:

5.1 Packaging and Identification:

Wire shall be identified as follows:

- 5.1.1 Wire, supplied on spools, shall contain 5, 10, 15, or 30 pounds (2.27, 4.54, 6.80, or 13.6 kg), as ordered. Each spool shall be legibly marked, on one flange of the spool or on a durable tag attached to each spool, with not less than the nominal size, alloy number and temper, lot number, AMS 4182E, and manufacturer's identification.
- 5.1.2 Straight wire shall be bundled, boxed, or secured on lifts and identified by two durable tags legibly marked with the information of 5.1.1 and attached, not farther than 2 feet (610 mm) from each end, to the wire in each bundle, box, or lift.
- 5.1.3 Coiled wire shall be identified with the information of 5.1.1, legibly marked on a durable tag attached to each coil or directly on one flange of each spool.
- 5.1.4 (R) Wire shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the wire to ensure carrier acceptance and safe delivery.
- 5.1.5 For direct U.S. Military procurement, packaging shall be in accordance with ASTM B 660, Commercial Level, unless Level A is specified in the request for procurement.

6. ACKNOWLEDGMENT:

A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS:

Wire not conforming to this specification, or to modifications authorized by purchaser, will be subject to rejection.

8. NOTES:

8.1 Revision Indicator:

The (R) symbol is for the convenience of the user in locating areas where technical revisions, not editorial changes, have been made to the previous issue of this specification. If the symbol is next to the specification title, it indicates a complete revision of the specification.