

SAE-AMS4184

ADOPTION NOTICE

SAE-AMS4184, "Filler Metal, Aluminum Brazing, 10SI 4.0CU, was adopted on October 3, 1994, for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commanding Officer, Naval Air Warfare Center Aircraft Division, Systems Requirements Department, Highway 547, Lakehurst, NJ 08733-5100. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

Custodians:

Army - MR
Navy - AS
Air Force - 99

Adopting Activity
Navy - AS

SAENORM.COM : Click to view the full PDF of SAE-AMS4184

FSC 3439

DISTRIBUTION STATEMENT A. Approved for public release;
distribution is unlimited.

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE AMS-4184

REV
D

Issued 1948-05-01

Revised 1990-10-01

Superseding AMS-4184C

FILLER METAL, ALUMINUM BRAZING
10Si - 4.0Cu (4145)

UNS A94145

1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of wire, sheet, pig, grains, shot, and chips.

1.2 Application: Primarily for joining aluminum by brazing.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS-2202 - Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate

MAM-2202 - Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 - Packaging/Packing of Aluminum and Magnesium Products

ASTM E 34 - Chemical Analysis of Aluminum and Aluminum Alloys

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

SAE AMS-4184 Revision D

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 34, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Silicon	9.3 -	10.7
Copper	3.3 -	4.7
Iron	--	0.8
Zinc	--	0.20
Chromium	--	0.15
Manganese	--	0.15
Magnesium	--	0.15
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 3.2 Condition: Filler metal shall be furnished in the following condition:

3.2.1 Round Wire, Flattened and Slit Wire, and Sheet: Annealed.

3.2.2 Pig, Grains, Shot, and Chips: As fabricated.

3.3 Quality: Filler metal, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the filler metal.

3.4 Standard Sizes and Tolerances: Shall conform to the following:

3.4.1 Round Wire:

<u>Nominal Diameters</u>		<u>Tolerances, Plus and Minus</u>	
<u>Inch</u>	<u>Millimetres</u>	<u>Inch</u>	<u>Millimetre</u>
1/32	0.8	0.001	0.025
1/16	1.6	0.001	0.025
3/32	2.4	0.0015	0.038
1/8	3.2	0.0015	0.038
3/16	4.8	0.0015	0.038
1/4	6.4	0.0015	0.038

3.4.2 Flattened and Slit Wire: Cross-section 0.020 inch $\pm$ 0.001 x 2 inches $\pm$ 0.006 (0.51 mm $\pm$ 0.03 x 51 mm $\pm$ 0.15).

3.4.3 Sheet: Tolerances for nominal thicknesses 0.010, 0.015, and 0.020 inch (0.25, 0.38, and 0.51 mm) shall be as specified in AMS-2202 or MAM-2202.

SAE AMS-4184 Revision D

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of filler metal shall supply all
Ø samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the filler metal conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests for all technical requirements are
Ø acceptance tests and shall be performed on each lot.
- 4.3 Sampling and Testing: Shall be in accordance with the following; a lot
Ø shall be all filler metal produced from a single furnace charge:
- 4.3.1 Composition: At least one sample from each group of ingots poured simultaneously from the same source of molten metal.
- 4.3.1.1 Unless compliance with 4.3.1 is established, an analysis shall be made for each 6000 pounds (2722 kg) or less of filler metal comprising a lot.
- 4.4 Reports: The vendor of filler metal shall furnish with each shipment a report stating that the filler metal conforms to the chemical composition and other technical requirements. This report shall include the purchase order number, lot number, AMS-4184D, form and size or part number, and quantity.

5. PREPARATION FOR DELIVERY:5.1 Identification:

- 5.1.1 Filler metal shall be identified as agreed upon by purchaser and vendor.
- 5.1.2 Each container or package shall be permanently and legibly marked with not less than the following information:

FILLER METAL, ALUMINUM BRAZING

AMS-4184D

LOT NUMBER _____

MANUFACTURER'S IDENTIFICATION _____

NOMINAL DIMENSIONS _____

WEIGHT _____

5.2 Packaging:

- 5.2.1 Filler metal shall be suitably wrapped, sealed, and boxed or otherwise packaged for protection against injury and contamination, during shipment and storage, under normal dry storage conditions.
- 5.2.2 Packages of filler metal shall be prepared for shipment in accordance with
Ø commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the filler metal to ensure carrier acceptance and safe delivery.