

# AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

SAE AMS 4201A

Issued 1-15-80  
Revised 7-1-86

Superseding AMS 4201

ALUMINUM ALLOY PLATE  
6.2Zn - 2.3Cu - 2.2Mg - 0.12Zr (7050-T7651)  
Solution Heat Treated, Stress Relieved and Overaged

UNS A97050

## 1. SCOPE:

1.1 Form: This specification covers an aluminum alloy in the form of plate.

1.2 Application: Primarily for parts requiring a high level of mechanical properties and resistance to exfoliation corrosion and moderate resistance to stress-corrosion cracking.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications and Aerospace Recommended Practices shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

### 2.1.1 Aerospace Material Specifications:

AMS 2202 - Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate

MAM 2202 - Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate

AMS 2350 - Standards and Test Methods

AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings

MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units

### 2.1.2 Aerospace Recommended Practices:

ARP 1704 - Short-Bar Fracture Toughness of Metallic Materials

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

- 2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM E399 - Plane-Strain Fracture Toughness of Metallic Materials  
ASTM E602 - Sharp-Notch Tension Testing with Cylindrical Specimens

- 2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Specifications:

MIL-H-6088 - Heat Treatment of Aluminum Alloys

2.3.2 Military Standards:

MIL-STD-649 - Aluminum and Magnesium Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

|                         | min       | max    |
|-------------------------|-----------|--------|
| Zinc                    | 5.7       | - 6.7  |
| Copper                  | 2.0       | - 2.6  |
| Magnesium               | 1.9       | - 2.6  |
| Zirconium               | 0.08      | - 0.15 |
| Iron                    | -         | 0.15   |
| Silicon                 | -         | 0.12   |
| Manganese               | -         | 0.10   |
| Titanium                | -         | 0.06   |
| Chromium                | -         | 0.04   |
| Other Impurities, Each  | -         | 0.05   |
| Other Impurities, Total | -         | 0.15   |
| Aluminum                | remainder |        |

- 3.2 Condition: Solution heat treated, stretched to produce a nominal permanent  $\epsilon$  set of 2% but not less than 1-1/2% nor more than 3%, and overaged. Solution heat treatment shall be performed in accordance with MIL-H-6088.

- 3.2.1 Plate shall receive no further straightening operations after stretching.

3.3 Properties: Plate shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355 except as specified in 3.3.4.1 and 3.3.5:

3.3.1 Tensile Properties: Shall be as specified in Table I and 3.3.1.1.

Ø

TABLE I

| Nominal Thickness<br>Inches | Specimen Orientation | Tensile Strength<br>psi, min | Yield Strength<br>at 0.2% Offset<br>psi, min | Elongation<br>in 2 in. or<br>4D<br>%, min |
|-----------------------------|----------------------|------------------------------|----------------------------------------------|-------------------------------------------|
| 0.250 to 1.000, incl        | Longitudinal         | 76,000                       | 66,000                                       | 9                                         |
|                             | Long-Trans.          | 76,000                       | 66,000                                       | 8                                         |
| Over 1.000 to 1.500, incl   | Longitudinal         | 77,000                       | 67,000                                       | 9                                         |
|                             | Long-Trans.          | 77,000                       | 67,000                                       | 8                                         |
| Over 1.500 to 2.000, incl   | Longitudinal         | 76,000                       | 66,000                                       | 9                                         |
|                             | Long-Trans.          | 76,000                       | 66,000                                       | 8                                         |
| Over 2.000 to 3.000, incl   | Longitudinal         | 76,000                       | 66,000                                       | 8                                         |
|                             | Long-Trans.          | 76,000                       | 66,000                                       | 7                                         |
|                             | Short-Trans.         | 70,000                       | 60,000                                       | 1.5                                       |

TABLE I (SI)

| Nominal Thickness<br>Millimetres | Specimen Orientation | Tensile Strength<br>MPa, min | Yield Strength<br>at 0.2% Offset<br>MPa, min | Elongation<br>in 50 mm or<br>4D<br>%, min |
|----------------------------------|----------------------|------------------------------|----------------------------------------------|-------------------------------------------|
| 6.25 to 25.00, incl              | Longitudinal         | 525                          | 455                                          | 9                                         |
|                                  | Long-Trans.          | 525                          | 455                                          | 8                                         |
| Over 25.00 to 37.50, incl        | Longitudinal         | 530                          | 460                                          | 9                                         |
|                                  | Long-Trans.          | 530                          | 460                                          | 8                                         |
| Over 37.50 to 50.00, incl        | Longitudinal         | 525                          | 455                                          | 9                                         |
|                                  | Long-Trans.          | 525                          | 455                                          | 8                                         |
| Over 50.00 to 75.00, incl        | Longitudinal         | 525                          | 455                                          | 8                                         |
|                                  | Long-Trans.          | 525                          | 455                                          | 7                                         |
|                                  | Short-Trans.         | 485                          | 415                                          | 1.5                                       |

3.3.1.1 Tensile property requirements for plate over 3.000 in. (75.00 mm) in nominal thickness shall be as agreed upon by purchaser and vendor.

3.3.2 Corrosion Resistance: Resistance to exfoliation corrosion and stress-corrosion cracking shall be demonstrated by meeting the following criteria:

3.3.2.1 Stress-Corrosion Resistance: Will be acceptable if plate meets the following requirements:

3.3.2.1.1 If the electrical conductivity (E.C.) is not lower than 37.0% IACS (International Annealed Copper Standard) (21.5 MS/m), the plate is acceptable.

3.3.2.1.2 Stress-corrosion susceptibility factor, SCF, determined by deducting electrical conductivity, XX.X% IACS (12 times XX.X MS/m), from long transverse yield strength, XX.X ksi (XXX MPa), shall not be greater than 36.0 (248).

Examples: for 1.250 in. (31.25 mm) nominal thickness:

Inch/Pound Units    74.4 ksi - 37.3% IACS = 37.1    Unacceptable.  
69.4 ksi - 38.2% IACS = 31.2    Acceptable.

SI Units                513 MPa - 12 X 21.6 MS/m = 254    Unacceptable.  
480 MPa - 12 X 22.2 MS/m = 214    Acceptable.

3.3.2.1.3 Plate not meeting the requirements of 3.3.1, 3.3.2.1.1 and 3.3.2.1.2 may be given additional overaging heat treatment after which it shall be retested to determine conformance to requirements of 3.3.1 and 3.3.2.1.

3.3.2.2 Exfoliation Corrosion Resistance: Plate shall show exfoliation corrosion not greater than that pictured in Photo B, Fig. 2, of ASTM G34-72 at a T/10 plane.

3.3.2.3 Stress-Corrosion Resistance: Specimens cut from plate 0.750 in. (18.75 mm) and over in nominal thickness and stressed in the short-transverse direction to 25,000 psi (170 MPa) shall show no evidence of stress-corrosion cracking.

3.3.3 Fracture Toughness: Plate shall meet the values of  $K_{Ic}$  specified in Table II, determined using specimen configurations conforming to ASTM E399. For T-L and L-T test directions on plate 2 in. (50 mm) and under in nominal thickness, use full thickness specimens; for plate over 2 to 4 in. (50 to 100 mm), incl, in nominal thickness, use 2-in. (50-mm) thick specimens centered at T/2; and for plate over 4 in. (100 mm) in nominal thickness, use 2-in. (50-mm) thick specimens centered at T/4. For the S-L test direction, the test specimens shall be centered at T/2. Required specimen orientation(s) shall be specified by purchaser.

TABLE II

| Specimen<br>Orientation | Nominal Thickness         |                           | Minimum $K_{Ic}$ |                 |
|-------------------------|---------------------------|---------------------------|------------------|-----------------|
|                         | Inches                    | Millimetres               | ksi $\sqrt{in}$  | MPa $\sqrt{mm}$ |
| L-T                     | 1.000 to 2.000, incl      | 25.00 to 50.00, incl      | 26               | 28              |
|                         | Over 2.000 to 3.000, incl | Over 50.00 to 75.00, incl | 24               | 26              |
| T-L                     | 1.000 to 2.000, incl      | 25.00 to 50.00, incl      | 24               | 26              |
|                         | Over 2.000 to 3.000, incl | Over 50.00 to 75.00, incl | 23               | 25              |
| S-L                     | 2.000 to 3.000, incl      | 50.00 to 75.00, incl      | 20               | 22              |

3.3.4 Notch Tensile Strength/Tensile Yield Strength (NTS/TYS) Ratio: The producer may guarantee that plate meets the fracture toughness ( $K_{Ic}$ ) requirements based on correlation with notch tensile strength/tensile yield strength (NTS/TYS) ratio, determined in accordance with 3.3.4.1, or correlation with the short-bar fracture toughness results, determined in accordance with 3.3.5 in lieu of determining fracture toughness (3.3.3) provided that he has established correlation between the two tests for his plate.

3.3.4.1 NTS/TYS Ratio: For plate 0.750 to 3.000 in. (18.75 to 75.00 mm), incl, in nominal thickness, notch tensile strength shall be determined in accordance with ASTM E602 on specimens taken in both the longitudinal and long-transverse directions. The values for each direction shall be divided by the tensile yield strength, determined for the same direction, to obtain the NTS/TYS ratios.

3.3.5 Short-Bar Fracture Toughness: Shall be not lower than the values for  $K_{Ic}$  specified in Table II, determined in accordance with ARP 1704 on specimens from plate 1.000 to 3.000 in. (25.00 to 75.00 mm), incl, in nominal thickness.

3.4 Quality: Plate, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the plate.

3.4.1 Each plate shall be ultrasonically inspected in accordance with ASTM B594 and shall meet the following requirements:

3.4.1.1 Plates weighing 2000 lb (900 kg) and under shall meet the following requirements for ultrasonic class:

| Nominal Thickness    |                      | Ultrasonic<br>Class |
|----------------------|----------------------|---------------------|
| Inches               | Millimetres          |                     |
| 0.500 to 1.500, excl | 12.50 to 37.50, excl | B                   |
| 1.500 to 3.000, incl | 37.50 to 75.00, incl | A                   |

3.4.1.2 The ultrasonic class for plates under 0.500 in. (12.50 mm) or over  
Ø 3.000 in. (75.00 mm) in nominal thickness or weighing over 2000 lb  
(900 kg) shall be as agreed upon by purchaser and vendor.

3.5 Tolerances: Shall conform to all applicable requirements of AMS 2202 or  
MAM 2202.

#### 4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of plate shall supply all samples  
for vendor's tests and shall be responsible for performing all required  
Ø tests. Results of such tests shall be reported to the purchaser as required  
by 4.4. Purchaser reserves the right to sample and to perform any  
confirmatory testing deemed necessary to ensure that the plate conforms to  
the requirements of this specification.

#### 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests to determine conformance to requirements for  
composition (3.1), long-transverse tensile properties (3.3.1), corrosion  
Ø resistance (3.3.2.1), fracture toughness (3.3.3), ultrasonic soundness  
(3.4.1), tolerances (3.5) and, when specified, longitudinal, short-  
transverse, or both, tensile properties (3.3.1) are classified as  
acceptance tests and shall be performed on each lot.

4.2.2 Periodic Tests: Tests to determine conformance to requirements for  
exfoliation resistance (3.3.2.2) and stress-corrosion resistance (3.3.2.3)  
Ø are classified as periodic tests and shall be performed at a frequency  
selected by the vendor unless frequency of testing is specified by  
purchaser.

4.3 Sampling: Shall be in accordance with AMS 2355 or MAM 2355 and the  
Ø following:

4.3.1 Tensile specimens shall be taken with the axis of specimens in the long-  
Ø transverse direction and, when specified, in the longitudinal, short-  
transverse, or both, directions.

4.3.2 Specimens for conductivity testing shall be taken from the samples used  
Ø for long-transverse tensile testing.

#### 4.4 Reports:

4.4.1 The vendor of plate shall furnish with each shipment a report stating that  
the plate conforms to the chemical composition, showing the results of  
tests on each inspection lot to determine conformance to the other  
acceptance test requirements, and stating that the plate conforms to the  
other technical requirements of this specification. This report shall  
include the purchase order number, inspection lot number, AMS 4201A, size,  
and quantity.