

AEROSPACE

MATERIAL SPECIFICATIONS

AMS4238

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

Issued 1-15-63
Revised

ALUMINUM ALLOY CASTINGS, SAND
6.8Mg - 0.2Ti - 0.2Mn
As Cast

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for parts requiring high ductility and operating at temperatures up to 250 F (120 C).

3. COMPOSITION:

Magnesium	6.2 - 7.5
Titanium	0.10 - 0.25
Manganese	0.10 - 0.25
Iron	0.25 max
Silicon	0.20 max
Iron + Silicon	0.40 max
Copper	0.10 max
Other Impurities, Each	0.05 max
Other Impurities, Total	0.15 max
Aluminum	remainder

4. CONDITION: As cast.

5. TECHNICAL REQUIREMENTS:

5.1 Casting: Castings shall be produced in lots from metal conforming to Section 3. Metal remelted from previously analyzed ingot may be poured directly into castings. Unless otherwise agreed upon by purchaser and vendor, molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or until the composition of a sample taken after the last addition to the melt has been found to conform to Section 3.

5.1.1 A melt shall be the metal withdrawn from a batch furnace charge of 2000 lb or less as melted for pouring castings or, when permitted by the purchaser, a melt shall be 4000 lb or less of metal withdrawn from one continuous furnace in not more than 8 consecutive hours.

5.1.2 Unless otherwise specified, a lot shall consist of castings poured from a single melt in not more than 8 consecutive hours.

5.2 Cast Test Specimens: Tensile test specimens, and chemical analysis specimens when required, shall be cast as follows and, when requested, shall be supplied with the castings.

- 5.2.1 Tensile Test Specimens: Shall be cast with each lot of castings, shall be standard (0.5 in. diameter at the reduced parallel section), and shall be cast to size in molds made with the regular foundry mix of green sand, without using chills. Metal for the specimens shall be part of the melt which is used for the castings. If the metal for castings is given any treatment such as fluxing or cooling and reheating, the metal for the specimens shall be a portion of the metal so treated, and during such treatment shall be heated to the same maximum temperature and held for approximately the same length of time as the molten metal for the castings.
- 5.2.2 Chemical Analysis Specimens: When required by purchaser, shall be cast from each melt and shall be of size and shape agreed upon by purchaser and vendor.
- 5.3 Tensile Properties:
- 5.3.1 Cast Test Specimens:
- | | |
|--|------------|
| Tensile Strength, psi | 35,000 min |
| Yield Strength at 0.2% Offset or at 0.0075 in. in | |
| 2 in. Extension Under Load ($E = 10,300,000$), psi | 18,000 min |
| Elongation, % in 2 in. | 9 min |
- 5.3.2 Specimens Cut from Castings:
- 5.3.2.1 When tensile properties of actual castings are determined for acceptance, not less than 4, and preferably 10, tensile test specimens shall be cut from thick and thin sections. The average value of all specimens selected shall conform to the following:
- | | |
|---|------------|
| Tensile Strength, psi | 26,500 min |
| Yield Strength at 0.2% Offset or at 0.0066 in. | |
| in 2 in. Extension Under Load ($E = 10,300,000$), psi | 13,500 min |
| Elongation, % in 4D (Round Specimens) | 2.5 min |
- 5.3.2.2 Conformance to these requirements may be used as basis for acceptance of castings.
- 5.3.2.3 When specified on the order, tensile test specimens taken in locations indicated on the drawing, from a casting chosen at random to represent the lot, shall have the properties indicated on the drawing for each specimen.
- 5.3.3 When a dispute occurs between purchaser and vendor over the yield strength value, yield strength determined by the offset method shall apply.
- 5.4 Hardness of Castings: Except at sprues and risers, the castings shall have hardness not lower than Brinell 70 using 50 kg load and 10 mm ball or 1000 kg load and 9/16 in. ball, or Brinell 75 using 1000 kg load and 10 mm ball.
6. QUALITY:
- 6.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned.

- 6.2 Radiographic and other quality standards shall be as agreed upon by purchaser and vendor.
- 6.3 Unless otherwise specified, castings shall be produced under radiographic control. This shall consist of radiographic examination of castings until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number, and of production castings as necessary to ensure maintenance of satisfactory quality.
- 6.4 Castings shall not be repaired by plugging, welding, or other methods, without written permission from purchaser.
- 6.5 Castings shall not be impregnated, chemically treated, or coated to prevent leaking, unless specified or allowed by written permission which states the method to be used. Impregnated castings shall be marked IMP.

7. REPORTS:

- 7.1 Unless otherwise specified, the vendor of castings shall furnish with each shipment three copies of a report of the results of tensile tests on test specimens from each lot and a statement that the chemical composition of castings conforms to the requirements of this specification. This report shall include the purchase order number, lot number, material specification number, part number, and quantity.
 - 7.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of castings, part number, and quantity. When castings for making parts are produced or purchased by the parts vendor, that vendor shall inspect each shipment or lot of castings to determine conformance to the requirements of this specification, and shall include in the report a statement that the castings conform, or shall include copies of laboratory reports showing the results of tests to determine conformance.
8. IDENTIFICATION: Unless otherwise specified, castings shall be identified in accordance with the latest issue of AMS 2804, including lot number and heat treatment batch number.

9. APPROVAL:

- 9.1 To assure uniformity of quality, sample castings from new or reworked patterns shall be approved by purchaser, unless such approval be waived.
 - 9.2 Vendor shall use the same foundry practices and the same heat treating procedures for production castings as for approved sample castings. If necessary to make any change in processing which could unfavorably affect any characteristics of the castings, vendor shall obtain written permission from purchaser prior to the first shipment of castings incorporating such change.
10. REJECTIONS: Castings not conforming to this specification or to authorized modification will be subject to rejection.