

**AEROSPACE
MATERIAL
SPECIFICATION**

Submitted for recognition as an American National Standard



AMS 4238D

Issued JAN 1963

Revised SEP 1996

Superseding AMS 4238C

**ALUMINUM ALLOY CASTINGS, SAND
6.8Mg - 0.18Ti - 0.18Mn (535.0-F)
As Cast**

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of September 1996. It is recommended, therefore, that this specification not be specified for new designs.

This cover sheet should be attached to the "C" revision of the subject specification.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE upon request.

PREPARED UNDER THE JURISDICTION OF AMS COMMITTEE "D"

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1996 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 4238C

Issued 15 JAN 1963
Revised 1 JUL 1991

Superseding AMS 4238B

Submitted for recognition as an American National Standard

ALUMINUM ALLOY CASTINGS, SAND
6.8Mg - 0.18Ti - 0.18Mn (535.0-F)
As Cast

UNS A05350

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of sand castings.
- 1.2 Application: Primarily for parts requiring high ductility and operating in service up to 250°F (121°C).

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

2.1.1 Aerospace Material Specifications:

AMS 2360 - Room Temperature Tensile Properties of Castings
AMS 2635 - Radiographic Inspection
AMS 2645 - Fluorescent Penetrant Inspection
AMS 2646 - Contrast Dye Penetrant Inspection
AMS 2694 - Repair Welding of Aerospace Castings
AMS 2804 - Identification, Castings

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

REAFFIRMED
5/15

- 2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 557 - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
 ASTM B 557M - Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)
 ASTM B 660 - Packaging/Packing of Aluminum and Magnesium Products
 ASTM E 10 - Brinell Hardness of Metallic Materials
 ASTM E 34 - Chemical Analysis of Aluminum and Aluminum Alloys
 ASTM E 155 - Reference Radiographs for Inspection of Aluminum and Magnesium Castings

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 34, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Magnesium	6.2	- 7.5
Titanium	0.10	- 0.25
Manganese	0.10	- 0.25
Beryllium	0.003	- 0.007
Iron	--	0.15
Silicon	--	0.15
Copper	--	0.05
Boron	--	0.002
Other Impurities, each	--	0.05
Other Impurities, total		0.15
Aluminum	remainder	

- 3.2 Condition: As cast.

- 3.3 Casting: Castings shall be produced in lots from metal conforming to 3.1. Metal remelted from previously analyzed Ingot may be poured directly into castings. Furnace or ladle additions of grain-refining elements or alloys are permissible. Molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or unless the composition of a sample taken after the last addition to the melt conforms to 3.1.

- 3.3.1 A melt shall be the metal withdrawn from a batch furnace charge of 2000 pounds (907 kg) or less as melted for pouring castings or, when permitted by purchaser, a melt shall be 4000 pounds (1814 kg) or less of metal withdrawn from one continuous furnace in not more than eight consecutive hours.
- 3.3.2 A lot shall be all castings poured from a single melt in not more than eight consecutive hours.

3.4 Cast Test Specimens: Chemical analysis specimens and tensile specimens shall be cast as follows:

3.4.1 Chemical Analysis Specimens: Shall be cast from each melt and shall be of any convenient size, shape, and form.

3.4.2 Tensile Specimens: Shall be cast with each lot of castings, shall be of standard proportions conforming to ASTM B 557 or ASTM B 557M with 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, and shall be cast to size in molds made of the regular foundry mix of sand without using chills. Metal for the specimens shall be part of the melt which is used for the castings. If the metal for castings is given any treatment, such as fluxing or cooling and reheating, the metal for the specimens shall be a portion of the metal so treated and, during such treatment, shall be heated to the same maximum temperature and held for approximately the same time as the molten metal for the castings. The temperature of the metal during pouring of the specimens shall be not lower than that during pouring of the castings.

3.5 Properties: Castings 1.0 inch (25 mm) and under in nominal wall thickness and 50 pounds (23 kg) and under in weight and representative tensile specimens produced in accordance with 3.4.2 shall conform to the following requirements; properties of castings over 1.0 inch (25 mm) in nominal wall thickness or over 50 pounds (23 kg) in weight shall be as agreed upon by purchaser and vendor:

3.5.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B 557 or ASTM B 557M; conformance to the requirements of 3.5.1.1 shall be used as the basis for acceptance of castings except when purchaser specifies that the requirements of 3.5.1.2 apply:

3.5.1.1 Separately-Cast Specimens:

Tensile Strength, minimum	35.0 ksi (241 MPa)
Yield Strength at 0.2% Offset, minimum	18.0 ksi (124 MPa)
Elongation in 40, minimum	9%

3.5.1.2 Specimens Cut from Castings or from Integrally-Cast Specimens: Specimens as in 4.3.4 shall meet the following requirements:

Tensile Strength, minimum	26.5 ksi (183 MPa)
Yield Strength at 0.2% Offset, minimum	13.5 ksi (93 MPa)
Elongation in 40, minimum	2.5%

3.5.1.2.1 When properties other than those of 3.5.1.2 are required, tensile specimens as in 4.3.4 machined from locations indicated on the drawing, from a casting or castings chosen at random to represent the lot, shall have the properties indicated on the drawing for such specimens. Property requirements may be designated in accordance with AMS 2360.

3.5.2 Hardness: Castings, except at gate and riser locations, should have hardness not lower than 70 HB/10/500 or 75 HB/10/1000, determined in accordance with ASTM E 10, but castings shall not be rejected on the basis of hardness if the tensile property requirements of 3.5.1.2 are met.

3.6 Quality:

3.6.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.6.1.1 Castings shall have smooth surfaces and shall be well cleaned.

3.6.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.6.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645, to contrast dye penetrant inspection in accordance with AMS 2646, or both.

3.6.4 Radiographic, fluorescent penetrant, contrast dye penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E 155 may be used to define radiographic acceptance standards.

3.6.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission of purchaser.

3.6.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings reworked by welding in accordance with AMS 2694.

3.6.6 Castings shall not be impregnated, chemically treated, or coated to prevent leakage unless specified or allowed by written permission of purchaser designating the method to be used.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests for composition (3.1), tensile properties of separately-cast specimens (3.5.1.1) or, when specified by purchaser, of specimens cut from castings or from integrally-cast coupons (3.5.1.2), and quality (3.6) are acceptance tests and shall be performed on each melt or lot as applicable.

- 4.2.1.1 Tensile properties of specimens cut from castings or from Integrally-cast coupons shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings or from integrally-cast coupons are determined.
- 4.2.2 Periodic Tests: Tests for hardness (3.5.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.2.3 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.
- 4.3 Sampling and Testing: Shall be in accordance with the following:
- Ø
- 4.3.1 At least one chemical analysis specimen in accordance with 3.4.1 from each melt, a casting from each lot, or both.
- Ø
- 4.3.2 One separately-cast tensile specimen in accordance with 3.4.2 from each lot except when purchaser requires properties of specimens cut from castings or from integrally-cast specimens.
- Ø
- 4.3.3 At least one preproduction casting in accordance with 4.4.1 of each part number.
- Ø
- 4.3.4 Except as permitted by 4.3.4.1, one or more castings from each lot when properties machined from castings are required. Size, location, and number of specimens machined from castings shall be as specified on the drawing or as agreed upon by purchaser and vendor. When size, location, and number of specimens are not specified, four tensile specimens, two from the thickest section and two from the thinnest section, shall be cut from a casting or castings from each lot.
- Ø
- 4.3.4.1 When permitted by purchaser, tensile specimens conforming to ASTM B 557 or ASTM B 557M excised from integrally-cast coupons may be used in lieu of separately-cast specimens (4.3.2) or specimens cut from a casting or castings (4.3.4). Size, number, and location of integrally-cast coupons shall be as specified by purchaser.