



ACCEPTANCE NOTICE

This non-Government document was adopted on 29 April 1988, and is approved for use by the DoD. The indicated industry group has furnished the clearance required by existing regulations. Copies of the document are stocked by the DoD Single Stock Point, U.S. Naval Publications and Forms Center, Philadelphia, PA 19120, for issue to DoD activities only. Contractors and industry groups must obtain copies directly from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

Title of Document: Aluminum Alloy Welding Wire 4.6Cu-0.35Mn-0.25Mg-0.22Ti
For Welding 206 Type Alloys

Date of Specific Issue Adopted: 1 January 1987

Releasing Industry Group: Society of Automotive Engineers, Inc.

NOTICE: When reaffirmation, amendment, revision or cancellation of this standard is initially proposed, the industry group responsible for this standard shall inform the military coordinating activity of the proposed change and request their participation.

Custodians:

Navy - AS
Air Force - 11
Army - MR

Military Coordinating Activity:

Navy - AS
(Project No. 3439-0690)

Review Activity:

DLA - IP

THIS DOCUMENT CONTAINS 1 PAGES.

AMSC N/A

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.



N-02-22



400 Commonwealth Dr., Warrendale, PA 15096

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 4244

Issued 1-1-87

ALUMINUM ALLOY WELDING WIRE 4.6Cu - 0.35Mn - 0.25Mg - 0.22Ti For Welding 206 Type Alloys

1. SCOPE:

- 1.1 Form: This specification covers an aluminum alloy in the form of welding wire.
- 1.2 Application: Primarily for use as filler metal for gas-metal-arc and gas-tungsten-arc welding of aluminum alloy castings having similar composition (206.0 and A206.0) and requiring in the weld zone response to heat treatment, properties, and corrosion resistance comparable to those of the castings.
- 1.3 Classification: Wire supplied to this specification is classified as follows:
- Type 1 - As Extruded and Sized
Type 2 - As Drawn

1.3.1 Unless a specific type is ordered, either type may be supplied.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.1.1 Aerospace Material Specifications:

- AMS 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings
- MAM 2355 - Quality Assurance Sampling and Testing of Aluminum Alloys and Magnesium Alloys, Wrought Products (Except Forging Stock) and Flash Welded Rings, Metric (SI) Units
- AMS 2813 - Packaging of Welding Wire, Standard Method
- AMS 2815 - Identification, Welding Wire, Line Code System
- AMS 2816 - Identification, Welding Wire, Color Code System

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined in accordance with AMS 2355 or MAM 2355:

	min	max
Copper	4.2	5.0
Manganese	0.20	0.50
Magnesium	0.15	0.35
Titanium	0.15	0.30
Iron	--	0.10
Zinc	--	0.10
Silicon	--	0.05
Nickel	--	0.05
Tin	--	0.05
Other Impurities, each	--	0.05
Other Impurities, total	--	0.15
Aluminum	remainder	

- 3.2 Condition: Wire may be made by any method unless a specific method is specified but shall be in a temper which will provide proper feeding of the wire in machine welding equipment.
- 3.2.1 Wire shall be furnished on disposable spools for machine welding or in cut lengths for manual welding, as ordered.
- 3.2.2 Oxides, dirt, and drawing compounds shall be removed by cleaning processes which will neither result in pitting nor cause gas absorption by the wire or deposition of substances harmful to welding operations.
- 3.3 Properties: Wire shall conform to the following requirements:
- 3.3.1 Weldability: Melted wire shall flow smoothly and evenly during welding and shall produce acceptable welds, determined by a procedure agreed upon by purchaser and vendor.

3.4 Quality: Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to welding operations, operation of welding equipment, or properties of the deposited weld metal.

3.5 Sizes and Tolerances: Wire shall be supplied in the sizes and to the tolerances of Table I unless drawn wire is specified, in which case wire shall conform to the tolerances of Table II.

3.5.1 Diameter:

3.5.1.1 Extruded Wire:

TABLE I

Form	Nominal Diameter Inch	Tolerance, Inch	
		plus	minus
Cut Lengths	0.045, 0.062, 0.078, 0.094, 0.125	0.007	0.007
Spools	0.030, 0.035, 0.045, 0.062, 0.094	0.002	0.002

TABLE I (SI)

Form	Nominal Diameter Millimetres	Tolerance, Millimetre	
		plus	minus
Cut Lengths	1.15, 1.55, 1.95, 2.35, 3.10	0.18	0.18
Spools	0.75, 0.90, 1.15, 1.55, 2.35	0.05	0.05

3.5.1.2 Drawn Wire:

TABLE II

Form	Nominal Diameter Inch	Tolerance, Inch	
		plus	minus
Cut Lengths	0.045, 0.062, 0.078, 0.094, 0.125	0.003	0.003
Spools	0.030, 0.035, 0.045	0.001	0.002
Spools	0.062, 0.094	0.002	0.002

TABLE II (SI)

Form	Nominal Diameter Millimetres	Tolerance, Millimetre	
		plus	minus
Cut Lengths	1.15, 1.55, 1.95, 2.35, 3.10	0.08	0.08
Spools	0.75, 0.90, 1.15	0.02	0.05
Spools	1.55, 2.35	0.05	0.05

3.5.2 Length: Cut lengths shall be furnished in 36-in. (900-mm) lengths and shall not vary more than +0, -1 in. (-25 mm) from the length ordered.

4. QUALITY ASSURANCE PROVISIONS: