

# AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

Issued JAN 1990

Revised SEP 1995

Superseding AMS 4255

ALUMINUM ALLOY, CLAD ONE SIDE SHEET  
0.6Mg - 0.35Si - 0.28Cu (No. 21 Brazing Sheet)  
As Fabricated

UNS A86951

## 1. SCOPE:

### 1.1 Form:

This specification covers an aluminum alloy in the form of sheet, clad on one side.

### 1.2 Application:

This sheet has been used typically for brazed assemblies which are subjected to heat treatment after joining, but usage is not limited to such applications.

## 2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

### 2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

|          |                                                                                                                                                                                    |
|----------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| AMS 2202 | Tolerances, Aluminum Alloy and Magnesium Alloy Sheet and Plate                                                                                                                     |
| MAM 2202 | Tolerances, Metric, Aluminum Alloy and Magnesium Alloy Sheet and Plate                                                                                                             |
| AMS 2770 | Heat Treatment of Wrought Aluminum Alloy Parts                                                                                                                                     |
| AMS 2355 | Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings                    |
| MAM 2355 | Quality Assurance Sampling and Testing, Aluminum Alloys and Magnesium Alloys, Wrought Products, Except Forging Stock, and Rolled, Forged, or Flash Welded Rings, Metric (SI) Units |
| AMS 2811 | Identification, Aluminum and Magnesium Alloy Wrought Products                                                                                                                      |

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 1995 Society of Automotive Engineers, Inc.  
All rights reserved.

Printed in U.S.A.

## 2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

## 3. TECHNICAL REQUIREMENTS:

## 3.1 Composition:

Shall conform to the percentages by weight shown in Table 1 and Table 2, determined in accordance with AMS 2355 or MAM 2355.

TABLE 1 - Composition, Core (6951)

| Element                 | min       | max  |
|-------------------------|-----------|------|
| Magnesium               | 0.40      | 0.8  |
| Silicon                 | 0.20      | 0.50 |
| Copper                  | 0.15      | 0.40 |
| Iron                    | --        | 0.8  |
| Zinc                    | --        | 0.20 |
| Manganese               | --        | 0.10 |
| Other Impurities, each  | --        | 0.05 |
| Other Impurities, total | --        | 0.15 |
| Aluminum                | remainder |      |

TABLE 2 - Composition, Cladding (4343)

| Element                 | min       | max  |
|-------------------------|-----------|------|
| Silicon                 | 6.8       | 8.2  |
| Iron                    | --        | 0.8  |
| Copper                  | --        | 0.25 |
| Zinc                    | --        | 0.20 |
| Manganese               | --        | 0.10 |
| Other Impurities, each  | --        | 0.05 |
| Other Impurities, total | --        | 0.15 |
| Aluminum                | remainder |      |

## 3.2 Condition:

As fabricated (F).

## 3.3 Properties:

The product shall conform to the following requirements, determined in accordance with AMS 2355 or MAM 2355:

3.3.1 After Solution and Aging Heat Treatment: Sheet shall have the following properties after being solution and aging heat treated to the -T62 temper in accordance with AMS 2770 for 6951 alloy.

3.3.1.1 Tensile Properties: Shall be as shown in Table 3.

TABLE 3A - Minimum Tensile Properties, Inch/Pound Units

| Nominal Thickness<br>Inch | Tensile<br>Strength<br>ksi | Yield Strength<br>at 2% Offset<br>ksi | Elongation in<br>2 inches or 4D<br>% |
|---------------------------|----------------------------|---------------------------------------|--------------------------------------|
| Over 0.010 to 0.019, incl | 35.0                       | 30.0                                  | 6                                    |
| Over 0.019 to 0.249, incl | 35.0                       | 30.0                                  | 8                                    |

TABLE 3B - Minimum Tensile Properties, SI Units

| Nominal Thickness<br>Millimeters | Tensile<br>Strength<br>MPa | Yield Strength<br>At 2% Offset<br>MPa | Elongation in<br>50.8 mm or 4D<br>% |
|----------------------------------|----------------------------|---------------------------------------|-------------------------------------|
| Over 0.25 to 0.48, incl          | 241                        | 207                                   | 6                                   |
| Over 0.48 to 6.32, incl          | 241                        | 207                                   | 8                                   |

3.3.1.2 Bending: Sheet shall withstand, without cracking, bending with the clad side out (convex side) at room temperature through an angle of 180 degrees around a diameter equal to the bend factor shown in Table 4 times the nominal thickness of the sheet with axis of bend parallel to the direction of rolling.

TABLE 4 - Bending Parameters

| Nominal Thickness<br>Inch | Nominal Thickness<br>Millimeters | Bend<br>Factor |
|---------------------------|----------------------------------|----------------|
| 0.010 to 0.036, incl      | 0.25 to 0.91, incl               | 3              |
| Over 0.036 to 0.064, incl | Over 0.91 to 1.63, incl          | 4              |
| Over 0.064 to 0.128, incl | Over 1.63 to 3.25, incl          | 5              |
| Over 0.128 to 0.249, incl | Over 3.25 to 6.32, incl          | 6              |

## 3.4 Cladding:

Shall be applied to only one face of the core.

## 3.4.1 Cladding Thickness: After rolling, the average cladding thickness shall be as shown in Table 4.

TABLE 4 - Average Cladding Thickness

| Total Thickness of<br>Composite Product<br>Inch | Total Thickness of<br>Composite Product<br>Millimeters | Cladding Thickness<br>Percent of<br>Total Thickness<br>min, average | Cladding Thickness<br>Percent of<br>Total Thickness<br>max, average |
|-------------------------------------------------|--------------------------------------------------------|---------------------------------------------------------------------|---------------------------------------------------------------------|
| 0.010 to 0.090, incl                            | 0.25 to 2.29, incl                                     | 8                                                                   | 12                                                                  |
| Over 0.090 to 0.249, incl                       | Over 2.29 to 6.32, incl                                | 4                                                                   | 6                                                                   |

## 3.5 Quality:

Sheet, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the sheet.

## 3.6 Tolerances:

Shall conform to all applicable requirements of AMS 2202 or MAM 2202.

## 4. QUALITY ASSURANCE PROVISIONS:

## 4.1 Responsibility for Inspection:

The vendor of sheet shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the sheet conforms to the requirements of this specification.

## 4.2 Classification of Tests:

4.2.1 Acceptance Tests: Composition (3.1), tensile properties after solution and aging heat treatment (3.3.1.1), and tolerances (3.6) are acceptance tests and, except for composition, shall be performed on each inspection lot.

4.2.2 Periodic Tests: Bending after solution and aging heat treatment (3.3.1.2) and cladding thickness (3.4.1) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

## 4.3 Sampling and Testing:

(R) Shall be in accordance with AMS 2355 or MAM 2355.