

ADOPTION NOTICE

AMS 4418, "Magnesium Alloy, Sand Castings 2.5Ag - 2. 1Di - 0.70Zr (QE22A-T6) Solution and Precipitation Heat Treated" was adopted on 19 December 1994 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Air Force, ASC/ENOSD, Building 125, 2335 Seventh Street, Suite 6, Wright-Patterson AFB OH 45433-7809. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers Inc., 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Custodians:

Army - MR

Navy - AS

Air Force - 11

Adopting Activity:

Air Force - 11

(Proj No. MECA - 0558)

Review activities:

AF - 99

AMSC N/A

MECA

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

AEROSPACE MATERIAL SPECIFICATION

An American National Standard

Issued JUL 1961

Revised DEC 1994

Superseding AMS 4418E

MAGNESIUM ALLOY, SAND CASTINGS
2.5Ag - 2.1Di - 0.70Zr (QE22A-T6)
Solution and Precipitation Heat Treated

UNS M18220

1. SCOPE:

1.1 Form:

This specification covers a magnesium alloy in the form of sand castings.

1.2 Application:

These castings have been used typically for parts requiring high yield Strength up to 400 °F (204 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2360 Room Temperature Tensile Properties of Castings
AMS 2361 Elevated Temperature Tensile Properties of Castings
AMS 2475 Protective Treatments, Magnesium Alloys
AMS 2635 Radiographic Inspection
AMS 2645 Fluorescent Penetrant Inspection
AMS 2694 Repair Welding of Aerospace Castings
AMS 2804 Identification, Castings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 557 Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products

ASTM B 557M Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)

ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products

ASTM E 21 Elevated Temperature Tension Tests of Metallic Materials

ASTM E 35 Chemical Analysis of Magnesium and Magnesium Alloys

ASTM E 155 Reference Radiographs for Inspection of Aluminum and Magnesium Castings

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-M-6857 Magnesium Alloy Castings, Heat Treatment of

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

(R)

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 35, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Silver	2.0	3.0
Didymium (Total Rare Earths)	1.75	2.5
Zirconium, total	0.40	1.0
Copper (3.1.1)	--	0.10
Nickel (3.1.1)	--	0.01
Other Impurities, total	--	0.30
Magnesium	remainder	

3.1.1 Determination not required for routine acceptance.

3.2 Condition:

Solution and precipitation heat treated.

3.3 Casting:

(R)

Castings shall be produced from metal conforming to 3.1. Furnace or ladle additions of grain-refining elements or alloys are permissible. Molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted or unless the composition of a sample taken after the last addition to the melt conforms to 3.1.

3.3.1 A melt shall be the metal withdrawn from a batch-furnace charge of 2000 pounds (907 kg) or less as melted for pouring castings or, when permitted by purchaser, a melt shall be 4000 pounds (1814 kg) or less of metal withdrawn from one continuous furnace in not more than eight consecutive hours.

3.3.2 A lot shall be all castings poured from a single melt in not more than eight consecutive hours and solution and precipitation heat treated in the same heat treatment batch.

3.4 Cast Test Specimens:

(R)

Chemical analysis specimens and tensile specimens shall be cast as follows:

3.4.1 Chemical Analysis Specimens: Shall be cast from each melt and shall be of any suitable size, shape, and form.

(R)

3.4.2 Tensile Specimens: Shall be cast with each lot of castings, shall be of standard proportions conforming to ASTM B 557 or ASTM B 557M with 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, and shall be cast to size in molds made of the regular foundry mix of sand without using chills. Metal for the specimens shall be part of the melt which is used for the castings and shall be subjected to the same grain refining or alloying treatment given the alloy for the castings. The temperature of the metal during pouring of the specimens shall be not lower than that during pouring of the castings.

(R)

3.5 Heat Treatment:

Castings and representative tensile specimens shall be solution and precipitation heat treated in accordance with MIL-M-6857. At least one set of tensile specimens shall, during each stage of heat treatment, be placed into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than three hours.

3.6 Properties:

Castings and representative separately-cast tensile specimens produced in accordance with 3.4.2 shall conform to the following requirements:

3.6.1 Tensile Properties: Conformance to the requirements of 3.6.1.1.1 shall be used as basis for acceptance of castings except when purchaser specifies that the requirements of 3.6.1.1.2 apply:

3.6.1.1 At Room Temperature: Shall be as follows, determined in accordance with ASTM B 557 or ASTM B 557M:

3.6.1.1.1 Separately-Cast Specimens: Shall meet the requirements shown in Table 2.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	35.0 ksi (241 MPa)
Yield Strength at 0.2% Offset	25.0 ksi (172 MPa)
Elongation in 4D	2%

3.6.1.1.2 Specimens Cut from Castings or Integrally-Cast Coupons: Specimens (R) as in 4.3.4 shall meet the requirements shown in Table 3:

TABLE 3 - Minimum Tensile Properties

Property	Value
Tensile Strength	32.0 ksi (221 MPa)
Yield Strength at 0.2% Offset	23.0 ksi (159 MPa)
Elongation in 4D	2%

3.6.1.2 At 400 °F (204 °C): Shall be as shown in Tables 4 and 5, determined in accordance with ASTM E 21 on specimens heated to 400 °F ± 5 (204 °C ± 3), held at heat for 10 minutes ± 1 before testing, and tested at 400 °F ± 5 (204 °C ± 3):

3.6.1.2.1 Separately-Cast Specimens:

TABLE 4 - Minimum Tensile Properties

Property	Value
Tensile Strength	25.0 ksi (172 MPa)
Yield Strength at 0.2% Offset	19.0 ksi (131 MPa)

3.6.1.2.2 Specimens Cut from Castings or From Integrally-Cast Coupons:

TABLE 5 - Minimum Tensile Properties

Property	Value
Tensile Strength	24.0 ksi (165 MPa)
Yield Strength at 0.2% Offset	18.0 ksi (124 MPa)

- 3.6.1.3 When properties other than those specified in 3.6.1.1.2 and 3.6.1.2.2 are required, tensile specimens as in 4.3.4, machined from locations indicated on the drawing, from a casting or castings chosen at random to represent the lot shall have the properties indicated on the drawing for such specimens. Property requirements for such specimens may be designated in accordance with AMS 2360, AMS 2361, or both.
- 3.7 Quality:
- 3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.
- 3.7.1.1 Castings shall have smooth surfaces and shall be sufficiently cleaned to permit fluorescent penetrant inspection.
- 3.7.1.2 Castings cleaned by blasting shall be pickled in a sulfuric or sulfuric-nitric acid solution to remove not less than 0.002 inch (0.05 mm) of metal before protective treatment as in 5.2.1.
- 3.7.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of castings in accordance with AMS 2635 or other radiographic procedure acceptable to purchaser, until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.
- 3.7.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645.
- 3.7.4 Radiographic, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E 155 may be used to define radiographic standards.
- 3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.
- 3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.
- 3.7.6 Castings shall not be impregnated, chemically treated, or coated to prevent leakage unless specified or allowed by written permission of purchaser, designating the method to be used.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R)

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests for composition (R) (3.1), tensile properties at room temperature (3.6.1.1), and quality (3.7) are acceptance tests and shall be performed to represent each lot or melt as applicable.

4.2.1.1 Tensile properties of specimens cut from castings or from integrally-cast (R) coupons shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings or from integrally-cast coupons are determined.

4.2.2 Periodic Tests: Tests for tensile properties at 400 °F (204 °C) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing: Shall be in accordance with the following:

(R)

4.3.1 One chemical analysis specimen in accordance with 3.4.1 from each melt or a (R) casting from each lot.

4.3.2 One separately-cast tensile specimen in accordance with 3.4.2 from each lot (R) except when purchaser requires properties of specimens cut from castings or from integrally-cast coupons.

4.3.3 Sufficient castings of each part number in accordance with 4.4.1 to satisfy dimensional, property, and quality evaluations.

4.3.4 One or more castings from each lot when tensile properties are required from specimens machined from castings. Specimens shall conform to ASTM B 557 or ASTM B 557M and shall be either 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, subsize specimens proportional to the standard, or standard sheet-type specimens. For determining conformance to the requirements of 3.6.1.3, if specimen locations are not shown on the drawing, not less than four tensile specimens, two from the thickest section and two from the thinnest section, shall be cut from a casting or castings from each lot.

4.3.4.1 When permitted by purchaser, tensile specimens conforming to ASTM B 557 (R) or ASTM B 557M excised from integrally-cast coupons may be used in lieu of separately-cast specimens (4.3.2) or specimens cut from a casting or castings (4.3.4). Size, number, and location of integrally-cast coupons shall be as specified by purchaser.

4.4 Approval:

4.4.1 Sample castings from new or reworked patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall establish, for production of sample castings of each part number, parameters for the process control factors which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, test specimens, sample castings, or both. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.

4.4.2.1 Process control factors for producing castings include, but are not (R) limited to, the following:

- Type of furnace
- Furnace atmosphere
- Ladle addition or grain refining practice
- Sand formulation
- Fluxing or oxide removal procedure
- Gating and risering practices
- Metal pouring temperature; variation of ± 50 F (± 28 C) degrees is permissible
- Solidification and cooling procedures
- Solution and precipitation heat treatment cycles
- Cleaning operations
- Methods of inspection

4.4.2.1.1 Any of the above process control factors for which parameters are considered proprietary by the vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.