

SAE The Engineering Society
For Advancing Mobility
Land Sea Air and Space®
INTERNATIONAL

400 Commonwealth Drive, Warrendale, PA 15096-0001

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 4439D

Issued 1 NOV 1970
Revised 1 JUL 1992
Superseding AMS 4439C

Submitted for recognition as an American National Standard

MAGNESIUM ALLOY CASTINGS, SAND
4.2Zn - 1.2Ce - 0.7Zr (ZE41A-T5)
Precipitation Heat Treated

UNS M16410

1. SCOPE:

1.1 Form:

This specification covers a magnesium alloy in the form of sand castings.

1.2 Application:

These castings have been used typically for components requiring uniform medium strength up to 320 °F (160 °C), pressure tightness, good fatigue and creep characteristics, and which may require welding during fabrication, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2360 Room Temperature Tensile Properties of Castings
AMS 2475 Protective Treatments, Magnesium Alloys
AMS 2635 Radiographic Inspection
AMS 2645 Fluorescent Penetrant Inspection
AMS 2694 Repair Welding of Aerospace Castings
AMS 2804 Identification, Castings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

AMS 4439D

SAE

AMS 4439D

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

- ASTM B 557 Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
 ASTM B 557M Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)
 ASTM B 660 Packaging/Packing of Aluminum and Magnesium Products
 ASTM E 10 Brinell Hardness of Metallic Materials
 ASTM E 35 Chemical Analysis of Magnesium and Magnesium Alloys
 ASTM E 155 Reference Radiographs for Inspection of Aluminum and Magnesium Castings

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

(R)

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 35, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Zinc	3.5	5.0
Cerium (Total Rare Earths)	0.75	1.75
Zirconium, total	0.40	1.0
Zirconium, soluble (3.1.1, 3.1.2)	0.40	--
Manganese (3.1.2)	--	0.15
Copper (3.1.2)	--	0.10
Nickel (3.1.2)	--	0.01
Other Impurities, each (3.1.2)	--	0.10
Other Impurities, total (3.1.2)	--	0.30
Magnesium	remainder	

3.1.1 Soluble zirconium is that portion of the zirconium which is soluble in 1:4 hydrochloric acid held below its boiling point.

3.1.2 Determination not required for routine acceptance.

3.2 Condition:

Precipitation heat treated.

AMS 4439D

SAE

AMS 4439D

3.3 Casting:

(R)

Castings shall be produced in lots from metal conforming to 3.1. Furnace or ladle additions of grain-refining elements or alloys shall be added to the melt. Molten metal taken from alloying furnaces, with or without additions of foundry operating scrap (gates, sprues, risers, and rejected castings), shall not be poured into castings unless first converted to ingot, analyzed, and remelted, or unless the composition of a sample taken after the last addition to the melt conforms to 3.1.

3.3.1 A melt shall be the metal withdrawn from a batch-furnace charge of 2000 pounds (907 kg) or less as melted for pouring castings or, when permitted by purchaser, a melt shall be 4000 pounds (1814 kg) or less of metal withdrawn from one continuous furnace in not more than eight consecutive hours.

3.3.2 A lot shall be all castings poured from a single melt in not more than eight consecutive hours and precipitation heat treated in the same heat treatment batch.

3.4 Cast Test Specimens:

(R)

Chemical analysis specimens and tensile specimens shall be cast as follows:

3.4.1 Chemical Analysis Specimens: Shall be cast from each melt and shall be of any suitable size, shape, and form.

3.4.2 Tensile Specimens: Shall be cast with each lot of castings, shall be of standard proportions conforming to ASTM B 557 or ASTM B 557M with 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, and shall be cast to size in molds made with the regular foundry mix of sand without using chills. Metal for the specimens shall be part of the melt which is used for the castings and shall be subjected to the same grain-refining or alloying treatment given the metal for the castings. Temperature of the metal during pouring of the specimen shall be not lower than that during pouring of the castings.

3.5 Heat Treatment:

(R)

No specific heat treating instructions are specified but castings and representative tensile specimens shall be precipitation heat treated to produce the properties specified in 3.6.1 and 3.6.2. At least one set of tensile specimens shall be put into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than three hours.

3.6 Properties:

Castings and separately-cast tensile specimens produced in accordance with 3.4.2 shall conform to the following requirements:

3.6.1 Tensile Properties: Shall be as shown in Table 2 or Table 3, determined in accordance with ASTM B 557 or ASTM B 557M; conformance to the requirements of 3.6.1.1 shall be used as the basis for acceptance of castings except when purchaser specifies that requirements of 3.6.1.2 apply:

AMS 4439D

SAE

AMS 4439D

3.6.1.1 Separately-Cast Specimens: Shall have the properties shown in Table 2.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	29.0 ksi (200 MPa)
Yield Strength at 0.2% Offset	19.5 ksi (134 MPa)
Elongation in 4D	2.5%

3.6.1.2 Specimens Cut From Castings Or From Integrally-Cast Coupons: Specimens (R) as in 4.3.4 shall meet the properties shown in Table 3 except as specified in 3.6.1.2.1.

TABLE 3 - Minimum Tensile Properties

Property	Value
Tensile Strength	26.0 ksi (179 MPa)
Yield Strength at 0.2% Offset	17.5 ksi (121 MPa)
Elongation in 4D	2.0%

3.6.1.2.1 Tensile property requirements for castings over 100 pounds in weight (R) shall be as agreed upon by purchaser and vendor.

3.6.1.2.2 When properties other than those specified in Table 3 are required, tensile specimens as in 4.3.4 taken from locations indicated on the drawing, from a casting or castings chosen at random to represent the lot, shall have properties indicated on the drawing for such specimens. Property requirements may be designated in accordance with AMS 2360.

3.6.2 Hardness: Castings, except at gate and riser locations, should have hardness of 55 to 70 HB/10/500 or 60 to 75 HB/10/1000, determined in accordance with ASTM E 10, but the castings shall not be rejected on the basis of hardness if the tensile property requirements of 3.6.1.2 are met.

3.7 Quality:

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.7.1.1 Castings shall have smooth surfaces sufficiently cleaned to permit (R) fluorescent penetrant inspection.

AMS 4439D

SAE

AMS 4439D

- 3.7.1.2 Castings cleaned by blasting shall be pickled in a sulfuric or sulfuric/nitric acid solution to remove not less than 0.002 inch (0.05 mm) of metal prior to protective treatment as in 5.2.
(R)
- 3.7.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of castings in accordance with AMS 2635 or other method acceptable to purchaser until proper foundry technique which will produce castings free from harmful internal imperfections is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.
(R)
- 3.7.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645.
(R)
- 3.7.4 Radiographic, fluorescent penetrant, and other quality standards shall be as established by purchaser. ASTM E 155 may be used to define radiographic acceptance standards.
(R)
- 3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.
- 3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.
- 3.7.6 Castings shall not be impregnated, chemically treated, or coated to prevent leakage unless specified or allowed by written permission of purchaser designating the method to be used.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection: (R)

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests for composition (3.1), tensile properties of separately-cast specimens (3.6.1.1), or, when specified, tensile properties of specimens cut from castings or integrally-cast coupons (3.6.1.2) and quality (3.7) are acceptance tests and shall be performed to represent each melt or lot as applicable.
- 4.2.1.1 Tensile properties of specimens cut from castings or from integrally-cast coupons shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings or from integrally-cast coupons are determined.
- 4.2.2 Periodic Tests: Tests for hardness (3.6.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
(R)

AMS 4439D

SAE

AMS 4439D

4.2.3 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:

Shall be in accordance with the following:

4.3.1 One chemical analysis specimen in accordance with 3.4.1 from each melt or a casting from each lot.

4.3.2 One separately-cast tensile specimen in accordance with 3.4.2 from each lot.

4.3.3 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.4 Except as permitted by 4.3.4.1, one or more castings from each lot when tensile properties of specimens machined from castings are required. Specimens shall conform to ASTM B 557 or ASTM B 557M and shall be either 0.500 inch (12.70 mm) diameter at the reduced parallel gage section, subsize specimens proportional to the standard, or standard sheet-type specimens. For determining conformance to the requirements of 3.6.1.2, if specimen locations are not shown on the drawing, not less than four tensile specimens, two from the thickest section and two from the thinnest section, shall be cut from a casting or castings from each lot.

4.3.4.1 When permitted by purchaser, tensile specimens conforming to ASTM B 557 or ASTM B 557M excised from integrally-cast coupons may be used in lieu of separately-cast specimens (4.3.2) or specimens cut from a casting or casting (4.3.4). Size, number, and location of integrally-cast coupons shall be as specified by purchaser.

4.4 Approval:

4.4.1 Sample castings from new or reworked patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall establish, for production of sample castings of each part number, parameters for the process control factors which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, test specimens, sample castings, or both. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.