

ADOPTION NOTICE

AMS4455,"Magnesium Alloy, Investment Castings 10Al (AM 100A-T6) Solution and Precipitation Heat Treated" was adopted on 17 November 1994 for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Air Force, ASC/ENOSD, Building 125, 2335 Seventh Street, Suite 6, Wright-Patterson AFB OH 45433-7809. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers Inc., 400 Commonwealth Drive, Warrendale, PA 15096-0001.

Custodians:

Army - MR

Navy - AS

Air Force - 11

Adopting Activity:

Air Force - 11

(Proj No. MECA 0556)

Review activities:

AF - 99

SAENORM.COM : Click to view the full PDF of AMS4455d

AMSC N/A

MECA

DISTRIBUTION STATEMENT A. Approved for public release; distribution is unlimited.

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

Issued JUL 1961
Revised NOV 1994

Superseding AMS 4455C

MAGNESIUM ALLOY, INVESTMENT CASTINGS
10A1 (AM100A-T6)
Solution and Precipitation Heat Treated

UNS M10100

1. SCOPE:

1.1 Form:

This specification covers a magnesium alloy in the form of investment castings.

1.2 Application:

These castings have been used typically for small intricate parts, which may operate up to 300 °F (149 °C) and are cast to approximate final dimensions, where the intricacy of the part is such that high fluidity of the molten metal is required, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2360 Room Temperature Tensile Properties of Castings
AMS 2475 Protective Treatment, Magnesium Alloys
AMS 2635 Radiographic Inspection
AMS 2645 Fluorescent Penetrant Inspection
AMS 2694 Repair Welding of Aerospace Castings
AMS 2804 Identification, Castings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM B 557	Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products
ASTM B 557M	Tension Testing Wrought and Cast Aluminum- and Magnesium-Alloy Products (Metric)
ASTM B 660	Packaging/Packing of Aluminum and Magnesium Products
ASTM E 35	Chemical Analysis of Magnesium and Magnesium Alloys

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-M-6857 Magnesium Alloy Castings, Heat Treatment of

MIL-STD-2175 Castings, Classification and Inspection of

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

(R)

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 35, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Aluminum	9.3	10.7
Manganese	0.10	--
Zinc	--	0.30
Silicon	--	0.30
Copper	--	0.10
Nickel	--	0.01
Other Impurities, each (3.1.1)	--	0.10
Other Impurities, total (3.1.1)	--	0.30
Magnesium	remainder	

3.1.1 Determination not required for routine acceptance.

(R)

3.2 Condition:

Solution and precipitation heat treated.

3.3 Casting:

Castings shall be poured either from remelted metal from a master heat or directly from a master heat. In either case, metal for casting shall be qualified as in 3.4.

3.3.1 A master heat is refined metal of a single furnace charge or is metal (R) blended as in 3.3.2. Gates, sprues, risers, and rejected castings shall be used only in preparation of master heats; they shall not be remelted directly, without refining, for pouring of castings. Furnace or ladle additions of grain-refining elements or alloys are permissible.

3.3.2 Metal **from two or** more master heats may be blended provided the composition (R) of each master heat to be blended is within the limits of 3.1 and the total weight of metal blended does not exceed 15,000 pounds (6804 kg). When two or more master heats are blended, the resultant blend shall be considered a master heat.

3.4 Master Heat Qualification:

Each master heat shall be qualified by evaluation of chemical analysis and tensile specimens conforming to 3.4.1 and 3.4.2, respectively. A master heat may be considered conditionally qualified if vendor's test results show conformance to all applicable requirements of this specification. However, except when purchaser waives confirmatory testing, final qualification shall be based on purchaser's test results. Conditional qualification of a master heat shall not be construed as a guarantee of acceptance of castings poured therefrom.

3.4.1 Chemical Analysis Specimens: Shall be of any suitable size, shape, and (R) form.

3.4.2 Tensile Specimens: Shall be cast from remelted metal from each master heat except that when castings are poured directly from a master heat, the specimens shall also be poured directly from the master heat. Specimens shall be of standard proportions in accordance with ASTM B 557 or ASTM B 557M with 0.250 inch (6.35 mm) diameter at the reduced parallel gage section. They shall be cast to size or shall be cast oversize and subsequently machined to 0.250 inch (6.35 mm) diameter. Center gating may be used.

3.5 Heat Treatment:

Castings and representative separately-cast tensile specimens shall be solution and precipitation heat treated in accordance with MIL-M-6857. At least one set of tensile specimens shall, during each stage of heat treatment, be placed into a batch-type furnace with each load of castings or into a continuous furnace at intervals of not longer than three hours.

3.6 Properties:

Castings and separately-cast tensile specimens produced in accordance with 3.4.2 shall conform to the following requirements:

3.6.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM B 557 or ASTM B 557M; conformance to the requirements of 3.6.1.1 shall be used as basis for acceptance of castings except when purchaser specifies that the requirements of 3.6.1.2 apply:

3.6.1.1 Separately-Cast Specimens: Shall be as shown in Table 2.

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	34.0 ksi (234 MPa)
Yield Strength at 0.2% Offset	20.0 ksi (138 MPa)
Elongation in 4D	2%

3.6.1.2 Specimens Cut From Castings or From Integrally-Cast Coupons: Shall be as (R) shown in Table 3.

TABLE 3 - Minimum Tensile Properties

Property	Value
Tensile Strength	17.0 ksi (117 MPa)
Yield Strength at 0.2% Offset	9.5 ksi (66 MPa)
Elongation in 4D	1%

3.6.1.2.1 When properties other than those of 3.6.1.2 are required, tensile (R) specimens as in 4.3.4 taken from locations indicated on the drawing, from a casting or castings chosen at random to represent the lot, shall have the properties indicated on the drawing for such specimens. Property requirements for such specimens may be designated in accordance with AMS 2360.

3.7 Quality:

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.7.1.1 Castings shall have smooth surfaces and shall be sufficiently cleaned to (R) permit penetrant examination.

3.7.2 Castings shall be produced under radiographic control. This control shall
(R) consist of radiographic examination of castings in accordance with AMS 2635, or other method acceptable to purchaser, until proper foundry technique, which will produce castings free from harmful imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.7.3 When specified, castings shall be subjected to fluorescent penetrant
(R) inspection in accordance with AMS 2645.

3.7.4 Fluorescent penetrant and other quality standards shall be established purchaser. Unless otherwise specified, radiographic acceptance standards shall meet requirements of MIL-STD-2175, Grade D.

3.7.5 Castings shall not be reworked by peening, plugging, welding, or other methods without written permission from purchaser.

3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings reworked by welding in accordance with AMS 2694.

3.7.6 Castings shall not be impregnated, chemically treated, or coated to prevent leakage unless specified or allowed by written permission of purchaser designating the method to be used.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

(R)

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests for

(R) composition (3.1), tensile properties of separately-cast specimens (3.6.1.1), and quality (3.7) are acceptance tests and shall be performed to represent each master heat or lot as applicable.

4.2.1.1 Tensile properties of specimens cut from castings or from integrally-

(R) cast coupons shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings or from integrally-cast coupons are determined.

4.2.2 Preproduction Tests: Tests for all technical requirements are preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material and/or processing requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, contracting officer, or request for procurement.

4.3 Sampling and Testing:
(R)

Shall be in accordance with the following; a lot shall be not more than 800 pounds (363 kg) of cast metal, including gates, sprues, and risers, produced in not more than eight consecutive hours from a single master heat, solution and precipitation heat treated as a single heat treatment batch, and presented for vendor's inspection at one time:

4.3.1 One chemical analysis specimen in accordance with 3.4.1 from each master heat, a casting from each lot, or both.
(R)

4.3.2 One separately-cast tensile specimen in accordance with 3.4.2 from each lot except when properties of specimens machined from castings or from integrally-cast coupons are required.
(R)

4.3.3 Two preproduction castings in accordance with 4.4.1 of each part number; one casting for dimensional evaluation and the other for property and quality evaluations as required for approval as in 4.4.1.
(R)

4.3.4 Except as permitted by 4.3.4.1, one or more castings from each lot when tensile properties are required from specimens machined from castings. Specimens shall conform to ASTM B 557 or ASTM B 557M and shall be either 0.250 inch (6.35 mm) diameter at the reduced parallel gage section, subsize specimens proportional to the standard, or standard sheet-type specimens. For determining conformance to the requirements of 3.6.1.2, if specimen locations are not shown on the drawing, not less than two tensile specimens, one from the thickest section and one from the thinnest section, shall be cut from a casting or castings representing each lot.
(R)

4.3.4.1 When permitted by purchaser, tensile specimens conforming to ASTM B 557 or ASTM B 557M excised from integrally-cast coupons may be used in lieu of separately-cast specimens (4.3.2) or specimens cut from a casting or castings (4.3.4). Size, number, and location of integrally-cast coupons shall be specified by purchaser.
(R)

4.4 Approval:

4.4.1 Sample castings from new or reworked master patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall establish, separately for tensile specimens used for master heat qualification and for production of sample castings of each part number, parameters for the process control factors which will produce tensile specimens meeting master heat qualification requirements and acceptable castings; these shall constitute the approved casting procedure and shall be used for producing subsequent master heat qualification specimens and production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested by purchaser, test specimens, sample castings, or both. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.

4.4.2.1 Control factors for producing test specimens and castings include, but are not limited to, the following:

- Type of furnace and its capacity
- Type and size of furnace charge
- Time molten metal is in furnace
- Furnace atmosphere
- Fluxing or deoxidation procedure
- Number of ladles used in pour
- Mold refractory formulation
- Gating practices
- Mold preheat and metal pouring temperatures; variations of ± 25 F (± 14 C) degrees are permissible
- Solidification and cooling procedures
- Solution and precipitation heat treatment cycles
- Cleaning operations
- Methods of inspection

4.4.2.1.1 Any of the above process control factors, for which parameters are considered proprietary by the vendor, may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.

4.5
(R)

Reports:

The vendor of castings shall furnish with each shipment a report showing the results of tests for chemical composition of at least one casting, or of specimens as in 3.4.1 cast in a mold with the parts, from each master heat represented, the results of tests for tensile properties of separately-cast specimens or integrally-cast coupons representing each lot or of specimens cut from castings from each lot, and stating that the castings conform to the other technical requirements. This report shall include the purchase order number, lot number, AMS 4455D, part number, and quantity.