

AEROSPACE MATERIAL SPECIFICATION



AMS 4501D

Issued NOV 1967
Revised JUN 2000
Reaffirmed APR 2006

Superseding AMS 4501C

Copper Sheet, Strip, and Plate
Oxygen-Free, Light Cold Rolled

UNS C10200

1. SCOPE:

1.1 Form:

This specification covers one type of copper in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for parts requiring high electrical or thermal conductivity, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order form a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been canceled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2222 Tolerances, Copper and Copper Alloy Sheet, Strip, and Plate

MAM 2222 Tolerances, Metric, Copper and Copper Alloy Sheet, Strip, and Plate

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM B 193	Resistivity of Electrical Conductor Materials
ASTM B 248	General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar
ASTM B 248M	General Requirements for Wrought Copper and Copper-Alloy Plate, Sheet, Strip, and Rolled Bar (Metric)
ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 53	Chemical Analysis of Copper
ASTM E 290	Semi-Guided Bend Test for Ductility of Metallic Materials

3. TECHNICAL REQUIREMENTS:

3.1 Material:

Shall be oxygen-free copper containing not less than 99.95% by weight copper (including silver), determined by wet chemical methods in accordance with ASTM E 53, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

3.2 Condition:

Cold rolled, light cold rolled (eighth hard (H00)) temper (see 8.2).

3.3 Properties:

The product shall conform to the following requirements:

- 3.3.1 Ultimate Tensile Strength: Shall be 32.0 to 40.0 ksi (221 to 276 MPa), determined in accordance with ASTM E 8 or ASTM E 8M.
- 3.3.2 Bending: Product 0.188 inch (4.78 mm) and under in nominal thickness shall withstand, without cracking, bending in accordance with ASTM E 290 at room temperature through an angle of 180 degrees around a diameter equal to the nominal thickness of the product with axis of bend parallel to the direction of rolling. Bending requirements for product over 0.188 inch (4.78 mm) in nominal thickness shall be agreed upon by purchaser and vendor.
- 3.3.3 Electrical Resistivity: Shall be not greater than $0.15775 \Omega \cdot \text{g}/\text{m}^2$ at $20^\circ\text{C} \pm 2$ ($68^\circ\text{F} \pm 4$), determined in accordance with ASTM B 193.
- 3.3.4 Embrittlement: Product 0.188 inch (4.78 mm) and under in nominal thickness, after heating as in 3.3.4.1, shall withstand, without fracture, not less than four 90-degree reverse bends. Product over 0.188 inch (4.78 mm) in nominal thickness shall not show evidence of gassing or open-grain structure characteristic of embrittlement after heating as in 3.3.4.1.

3.3.4.1 Specimens from the product shall be heated to 800 to 875 °C (1472 to 1607 °F) in a furnace containing a hydrogen atmosphere, held at heat for not less than 20 minutes, and cooled to prevent oxygen absorption during cooling. Specimens from product 0.188 inch (4.78 mm) and under in nominal thickness shall be clamped between jaws having edge radii equal to 2.5 times the nominal thickness of the specimen, bent through an angle of 90 degrees over one edge of the jaws, and returned to its original position; this constitutes one bend. Specimens shall then be bent through an angle of 90 degrees in the reverse direction and returned to its original position; this constitutes a second bend. Each successive bend shall be made in the opposite direction from the previous bend. Specimens from product over 0.188 inch (4.78 mm) in nominal thickness shall be polished, etched if desired, and examined at 75 to 200X magnification.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to AMS 2222 or MAM 2222 as applicable to nonrefractory alloys.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each lot.

4.3 Sampling and Testing:

Shall be in accordance with ASTM B 248 or ASTM B 248M and the following:

4.3.1 Specimens for tensile testing shall be taken with axis of specimen parallel to the direction of rolling.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for composition, tensile properties, and electrical resistivity of each lot and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, lot number, AMS 4501D, size, and quantity.

4.5 Resampling and Retesting:

If any specimen used in the above tests fails to meet the specified requirements, disposition of the product may be based on the results of testing three additional specimens for each original nonconforming specimen. Failure of any retest specimen to meet the specified requirements shall be cause for rejection of the product represented. Results of all tests shall be reported.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

The product shall be identified as in 5.1.1 unless line marking as in 5.1.2 is specified by purchaser.

5.1.1 Each sheet, strip, and plate shall be marked near one end, coils being marked near the outside end, with AMS 4501D, manufacturer's identification, and nominal thickness, using any suitable marking fluid. As an alternate method, individual pieces or bundles shall have attached a durable tag marked with the above information or shall be boxed and the box marked with the same information.

5.1.2 When specified by purchaser, each sheet, strip, and plate shall be legibly marked on one face, in the respective location indicated below, with AMS 4501D, lot number, manufacturer's identification, and nominal thickness. The characters shall be applied using a marking fluid removable in hot alkaline cleaning solution without rubbing. The markings shall have no deleterious effect on the product or its performance and shall be sufficiently stable to withstand normal handling. The specification number, manufacturer's identification, and nominal thickness shall be continuously line marked; the lot number may be included in the line marking or may be marked at one location on each piece.

5.1.2.1 Flat Strip 6 Inches (152 mm) and Under in Width: Shall be marked in one or more lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm).

5.1.2.2 Flat Sheet, Flat Strip Over 6 Inches (152 mm) in Width, and Plate: Shall be marked in lengthwise rows of characters recurring at intervals not greater than 3 feet (914 mm), the rows being spaced not more than 6 inches (152 mm) apart and alternately staggered.

5.1.2.3 Coiled Sheet and Strip: Shall be marked near both the outside and inside ends of the coil; the markings shall be applied as in 5.1.2 or shall appear on a durable tag or label attached to the coil and marked with the information of 5.1.2. When the product is wound on cores, the tag or label may be attached to the core.

5.2 Packaging:

The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.