

AEROSPACE MATERIAL SPECIFICATION

SAE AMS4534

REV. B

Issued 1991-07
Revised 2003-12
Reaffirmed 2012-04

Superseding AMS4534A

Copper-Beryllium Alloy, Bars and Rods
98Cu - 1.9Be
Solution Heat Treated, Cold Worked, and
Precipitation Heat Treated (TH04, formerly HT)
(Composition similar to UNS C17200)

RATIONALE

AMS4534B has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE:

1.1 Form:

This specification covers a copper-beryllium alloy in the form of bars and rods.

1.2 Application:

These products have been used typically for parts requiring a combination of high strength, wear resistance, and corrosion resistance, and where thermal conductivity, electrical conductivity, and low magnetic susceptibility may be important, but usage is not limited to such applications.

1.3 Safety - Hazardous Materials:

While the materials, methods, applications, and processes described or referenced in this specification may involve the use of hazardous materials, this specification does not address the hazards which may be involved in such use. It is the sole responsibility of the user to ensure familiarity with the safe and proper use of any hazardous materials and to take necessary precautionary measures to ensure the health and safety of all personnel involved.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER:
Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
<http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4534B>**

SAE WEB ADDRESS:

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2221 Tolerances, Copper and Copper Alloy Bars and Rods
AMS 2750 Pyrometry

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM B 249 General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, and Shapes
ASTM B 249M General Requirements for Wrought Copper and Copper-Alloy Rod, Bar, and Shapes (Metric)
ASTM E 3 Preparation of Metallographic Specimens
ASTM E 8 Tension Testing of Metallic Materials
ASTM E 8M Tension Testing of Metallic Materials (Metric)
ASTM E 18 Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
ASTM E 112 Determining Average Grain Size
ASTM E 478 Chemical Analysis of Copper Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 478, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element (3.1.1)	min	max
Beryllium	1.80	2.00
Nickel + Cobalt	0.20	--
Nickel + Cobalt + Iron	--	0.6
Aluminum	--	0.20
Silicon	--	0.20
Copper (3.1.2)	remainder	
Sum of Named Elements (3.1.3)	99.5	--

- 3.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier and purchaser.

3.1.2 Copper may be reported as “remainder”, or as the difference between the sum of results for all elements and 100%, or as the result of direct analysis.

3.1.3 When all the elements in the table are analyzed, the sum shall be 99.5% minimum, but such determination is not required for routine acceptance of each lot.

3.2 Condition:

Hot reduced or hot and cold reduced, solution heat treated, cold worked, and precipitation heat treated, TH04 temper; (See 8.2).

3.3 Heat Treatment:

Product shall be heat treated as follows; pyrometry shall be in accordance with AMS 2750:

3.3.1 Solution: Heat within the range 1400 to 1475 °F (760 to 802 °C), hold at heat for 30 to 60 minutes, and water quench.

3.3.2 Precipitation: Heat to 600 to 675 °F (316 to 357 °C), hold at heat for 2 to 3 hours, and air cool.

3.4 Properties:

Product shall conform to the following requirements (See 8.3):

3.4.1 Tensile Properties: Shall be in accordance with Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2A - Minimum Tensile Properties, Inch-Pound Units

Nominal Diameter or Least Distance Between Parallel Sides, Inches	Tensile Strength ksi	Yield Strength at 0.2% Offset ksi	Elongation in 2 Inches %
Up to 0.375, incl	182	157	3
Over 0.375 to 1.000, excl	180	154	3
Over 1.000 to 2.000, excl	177	150	3
Over 2.000 to 2.500, excl	175	147	3
Over 2.500 to 3.000, incl	172	145	3

TABLE 2B - Minimum Tensile Properties, SI Units

Nominal Diameter or Least Distance Between Parallel Sides, Millimeters	Tensile Strength MPa	Yield Strength at 0.2% Offset MPa	Elongation in 50.8 mm %
Up to 9.52, incl	1255	1082	3
Over 9.52 to 25.40, excl	1241	1062	3
Over 25.40 to 50.80, excl	1220	1034	3
Over 50.80 to 63.50, excl	1207	1014	3
Over 63.50 to 76.20, incl	1186	1000	3

- 3.4.2 Hardness: Bars and rods 0.188 to 2.0 inches (4.78 to 50.8 mm), inclusive, in nominal diameter or least distance between parallel sides shall have hardness of 37 to 45 HRC, or equivalent (See 8.4) determined in accordance with ASTM E 18.
- 3.4.3 Average Grain Size: The product shall have average grain size not larger than shown in Table 3, determined in accordance with ASTM E 112.

TABLE 3 - Maximum Average Grain Size

Nominal Diameter or Least Distance Between Parallel Sides, Inches	Nominal Diameter or Least Distance Between Parallel Sides, Millimeters	Maximum Average Grain Size Millimeter
Up to 1.000, incl	Up to 25.40, incl	0.050
1.000 to 1.500, incl	25.40 to 38.10, incl	0.075
1.500 to 2.000, incl	38.10 to 50.80, incl	0.100
2.000 to 3.000, incl	50.80 to 76.20, incl	0.125

- 3.4.4 Microstructure: Product shall contain not more than 6% beta phase constituent, determined at 100X magnification on specimens prepared in accordance with ASTM E 3.

3.5 Quality:

Product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.6 Tolerances:

Shall conform to AMS 2221 as applicable to refractory alloys.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.