

AEROSPACE MATERIAL SPECIFICATION



AMS 4544F

Issued MAY 1948
Revised MAY 1999
Reaffirmed JAN 2007

Superseding AMS 4544E

Nickel-Copper Alloy, Corrosion Resistant, Sheet, Strip, and Plate
67Ni - 30Cu
Annealed

UNS N04400

RATIONALE

This document has been reaffirmed to comply with the SAE 5-year Review policy.

1. SCOPE:

1.1 Form:

This specification covers a corrosion-resistant nickel-copper alloy in the form of sheet, strip, and plate.

1.2 Application:

These products have been used typically for formed or moderately-drawn parts requiring corrosion resistance, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2262	Tolerances, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
MAM 2262	Tolerances, Metric, Nickel, Nickel Alloy, and Cobalt Alloy Sheet, Strip, and Plate
AMS 2269	Chemical Check Analysis Limits, Nickel, Nickel Alloys, and Cobalt Alloys
AMS 2371	Quality Assurance Sampling and Testing, Corrosion and Heat Resistant Steels and Alloys, Wrought Products and Forging Stock
AMS 2807	Identification, Carbon and Low-Alloy Steels Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959.

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
ASTM E 76	Chemical Analysis of Nickel-Copper Alloys
ASTM E 290	Semi-Guided Bend Test for Ductility of Metallic Materials

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 76, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Nickel	63.0	70.0
Iron	--	2.5
Manganese	--	2.0
Cobalt	--	1.0
Silicon	--	0.50
Carbon	--	0.30
Sulfur	--	0.024
Copper	remainder	

3.1.1 Check Analysis: Composition variations shall meet the requirements of AMS 2269.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Sheet and Strip: Cold rolled, annealed, and, unless annealing is performed in an atmosphere yielding a bright finish, descaled having a surface appearance comparable to 3.2.1.1 or 3.2.1.2 as applicable (See 8.2).

3.2.1.1 Sheet: No. 2D finish.

3.2.1.2 Strip: No. 1 finish.

3.2.2 Plate: Hot rolled and annealed; when so ordered, plate shall be descaled.

3.3 Properties:

The product shall conform to the following requirements:

3.3.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M.

TABLE 2 - Tensile Properties

Property	Value
Tensile Strength	70.0 to 85.0 ksi (483 to 586 MPa)
Elongation in 2 Inches (50.8 mm) or 4D, minimum	35%

3.3.2 Bending: Product 0.250 inch (6.35 mm) and under in nominal thickness shall withstand, without cracking, bending in accordance with ASTM E 290 through an angle of 180 degrees around a diameter equal to the nominal thickness of the product with axis of bend parallel to the direction of rolling.

3.3.3 Hardness: Shall be as shown in Table 3, or equivalent (See 8.3), determined in accordance with ASTM E 18; for thin gages where superficial hardness testing is impractical, microhardness testing in accordance with ASTM E 384 may be used. Product shall not be rejected on the basis of hardness if the tensile properties of Table 2, determined on specimens taken from the same sample as that with nonconforming hardness or from another sample with similar nonconforming hardness, are acceptable.

TABLE 3 - Hardness

Nominal Thickness Inch	Nominal Thickness Millimeter	Hardness
Up to 0.250, incl	Up to 6.35, incl	73 HRB, maximum
Over 0.250	Over 6.35	69 to 80 HRB

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2262 or MAM 2262.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

All technical requirements are acceptance tests and shall be performed on each heat or lot, as applicable.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2371.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile properties, bending, and hardness of each lot, and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 4544F, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2371.

5. PREPARATION FOR DELIVERY:

Shall be in accordance with AMS 2807.

5.1 Identification:

5.2 Packaging:

The product shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the product to ensure carrier acceptance and safe delivery.