

AEROSPACE MATERIAL SPECIFICATION

SAE AMS4553

REV. C

Issued 1990-07
Revised 2004-04
Reaffirmed 2012-02

Superseding AMS4553B

Brass, Seamless, Tubing
85Cu - 15Zn
Annealed (061)

(Composition similar to UNS C23000)

RATIONALE

AMS4553C has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE:

1.1 Form:

This specification covers a copper alloy (brass) in the form of seamless tubing.

1.2 Application:

This tubing has been used typically for parts requiring resistance to corrosion by salt, fresh water, salt air, or gases, but usage is not limited to such applications.

1.3 Classification:

Tubing is classified by nominal working pressures as follows:

- Type I - Nominal working pressure 100 psi (689 kPa)
- Type II - Nominal working pressure 200 psi (1379 kPa)
- Type III - Nominal working pressure 300 psi (2068 kPa)
- Type IV - Nominal working pressure 450 psi (3103 kPa)

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent supplied herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4553C>**

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2223 Tolerances, Copper and Copper Alloy Seamless Tubing

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM B 153	Expansion (Pin Test) of Copper and Copper-Alloy Pipe and Tubing
ASTM B 154	Mercurous Nitrate Test for Copper and Copper Alloys
ASTM B 251	General Requirements for Wrought Seamless Copper and Copper-Alloy Tube
ASTM B 251M	General Requirements for Wrought Seamless Copper and Copper-Alloy Tube (Metric)
ASTM B858	Ammonia Vapor Test for Determining Susceptibility to Stress Corrosion Cracking in Copper Alloys
ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 243	Electromagnetic (Eddy-Current) Examination of Copper and Copper-Alloy Tubes
ASTM E 478	Chemical Analysis of Copper Alloys

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 478, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element (3.1.1)	min	max
Copper	84.0	86.0
Lead	--	0.05
Iron	--	0.05
Zinc (3.1.2)	remainder	
Sum of Named Elements (See 3.1.3)	99.8	--

- 3.1.1 These composition limits do not preclude the presence of other elements. Limits may be established and analysis required for unnamed elements by agreement between the manufacturer or supplier and purchaser.

- 3.1.2 Zinc may be reported as “remainder”, as the difference between the sum of results for all elements and 100%, or as the result of direct analysis.
- 3.1.3 When all of the named elements in the table are analyzed, the sum shall be 99.8% minimum, but such determination is not required for routine acceptance of each lot.

3.2 Condition:

Fully recrystallized in the soft annealed (061) temper (See 8.3). Tubing shall be acid cleaned after final annealing when specified.

3.3 Fabrication:

Tubing shall be produced by a seamless process. The external and internal surface finishes shall be produced by any method which will result in surfaces free from laps, folds, tears, and extraneous materials and which show no oxide discoloration. Processing shall not affect limits of wall thickness or corrosion resistance.

3.4 Properties:

Shall conform to the following requirements:

- 3.4.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M:

TABLE 2 - Minimum Tensile Properties

Property	Value
Tensile Strength	40.0 ksi (276 MPa)
Yield Strength, 0.5% Extension under Load	12.0 ksi (83 MPa)
Elongation in 8 Inches (203.2 mm)	30%

- 3.4.1.1 Tensile specimens shall be of the full section of tube and shall conform to the requirements of ASTM E 8 or ASTM E 8M, unless limitations of the testing machine preclude the use of such specimen; in which case longitudinal specimens cut from tube shall be tested.
- 3.4.2 Embrittlement: Specimens of tubing, nominally 6 inches (152 mm) in length or twice the diameter, whichever is greater, shall withstand, without cracking, the mercurous nitrate test performed in accordance with ASTM B 154, Procedure A, or the Ammonia Vapor Test in accordance with ASTM B 858.
- 3.4.3 Flarability (Expansion Test): Tube specimens shall withstand 20% expansion of the tube original outside diameter, determined in accordance with ASTM B 153.

- 3.4.4 Hydrostatic Pressure: Tubing shall withstand an internal hydrostatic pressure (P) based on Equation 1, without developing leaks and without an increase in mean diameter of more than 0.2%. The tube need not be tested at a pressure of over 1000 psi (6.90 MPa).

$$P = \frac{2 St}{D - 0.8t} \quad (\text{Eq. 1})$$

where:

P= Internal pressure at minimum yield, ksi (MPa)
S= Allowable yield stress (7.0 ksi [48.3 MPa])
t = Wall thickness, inches (mm)
D= Nominal OD, inches (mm)

3.5 Quality:

- 3.5.1 Visual Imperfections: Tubing, as received by purchaser, shall be uniform in quality and condition and shall have a finish conforming to the best practice for high quality aircraft tubing. It shall be smooth and free from heavy scale, oxide, burrs, seams, tears, grooves, laminations, slivers, pits, and other surface imperfections detrimental to usage of the tubing.
- 3.5.2 Surface Imperfections: Slight surface imperfections, such as handling marks, straightening marks, light mandrel and die marks, shallow pits, and scale patterns, are acceptable provided the imperfections are removable within tolerances specified for wall thickness.
- 3.5.3 Cleanliness: Tubing shall be free from grease or other foreign matter. Metallic flakes or particles shall not be collected by a clean white cloth drawn through the bore of a sample tube. Discoloration of the cloth, without the presence of flakes or particles, is acceptable.
- 3.5.4 Eddy-Current Examination: Tubing, under 2.5 inches (64 mm) in OD, shall be tested in accordance with ASTM E 243 is not acceptable. Discontinuity indications exceeding the discontinuity indication of a single artificial defect as defined in ASTM E 243 and appendix.

3.6 Tolerances:

Shall be as follows:

- 3.6.1 Diameter, Wall Thickness, and Length: Shall be in accordance with AMS 2223.
- 3.6.2 Weight: For any lot of tubing, the tolerance for overweight shall be 10% maximum. For calculating weight, the density shall be 0.316 pounds per cubic inch (8.75 kg/m³).

3.7 Sizes and Weights:

Shall be as shown in Tables 3 through 7.

TABLE 3A - Sizes and Weights - Type I Tubing, Inch/Pound Units

Nominal OD Inches	Minimum Wall Thickness Inch	Nominal ID Inches	Nominal Weight Pounds/Foot
2.875	0.065	2.745	2.176
3.500	0.065	3.370	2.660
4.000	0.065	3.870	3.047
4.500	0.065	4.370	3.434
5.563	0.068	5.427	4.451
6.625	0.081	6.463	6.315
8.625	0.105	8.145	10.657
10.750	0.131	10.488	16.573

TABLE 3B - Sizes and Weights - Type I Tubing, SI Units

Nominal OD Millimeters	Minimum Wall Thickness Millimeters	Nominal ID Millimeters	Nominal Weight kg/m
73.02	1.65	69.72	3.24
88.90	1.65	85.60	3.96
101.60	1.65	98.30	4.53
114.30	1.65	111.00	5.11
141.30	1.73	137.85	6.62
168.28	2.06	164.16	9.40
219.08	2.67	206.88	15.86
273.05	3.33	266.40	24.66

TABLE 4A - Sizes and Weights - Type II Tubing, Inch/Pound Units

Nominal OD Inches	Minimum Wall Thickness Inch	Nominal ID Inches	Nominal Weight Pounds/Foot
1.900	0.065	1.770	1.421
2.375	0.065	2.245	1.789
2.875	0.068	2.739	2.274
3.500	0.083	3.334	3.378
4.000	0.095	3.810	4.420
4.500	0.107	4.286	5.600
5.563	0.132	5.299	8.540
6.625	0.158	6.309	12.172
8.625	0.205	8.215	20.563
10.750	0.256	10.238	32.004

TABLE 4B - Sizes and Weights - Type II Tubing, SI Units

Nominal OD Millimeters	Minimum Wall Thickness Millimeters	Nominal ID Millimeters	Nominal Weight kg/m
48.26	1.65	44.96	2.11
60.32	1.65	57.02	2.66
73.02	1.73	69.57	3.38
88.90	2.11	84.68	5.03
101.60	2.41	96.77	6.58
114.30	2.72	108.86	8.33
141.30	3.35	134.59	12.71
168.28	4.01	160.25	18.11
219.08	5.21	208.66	30.60
273.05	6.50	260.04	47.63

TABLE 5A - Sizes and Weights - Type III Tubing, Inch/Pound Units

Nominal OD Inches	Minimum Wall Thickness Inch	Nominal ID Inches	Nominal Weight Pounds/Foot
1.375	0.065	1.245	0.968
1.660	0.065	1.530	1.235
1.900	0.066	1.768	1.442
2.375	0.083	2.209	2.266
2.875	0.100	2.675	3.306
3.500	0.122	3.256	4.910
4.000	0.140	3.720	6.436
4.500	0.157	4.186	8.123
5.563	0.194	5.175	12.408
6.625	0.231	6.163	17.596
8.625	0.301	8.023	29.848
10.750	0.375	10.000	46.349

TABLE 5B - Sizes and Weights - Type III Tubing, SI Units

Nominal OD Millimeters	Minimum Wall Thickness Millimeters	Nominal ID Millimeters	Nominal Weight kg/m
34.92	1.65	31.62	1.44
42.16	1.65	38.86	1.84
48.26	1.68	44.91	2.15
60.32	2.11	56.11	3.37
73.02	2.54	67.94	4.92
88.90	3.10	82.70	7.31
101.60	3.56	94.49	9.58
114.30	3.99	106.32	12.09
141.30	4.93	131.44	18.47
168.28	5.87	156.54	26.19
219.08	7.64	203.78	44.42
273.05	9.52	254.00	68.97

TABLE 6A - Sizes and Weights - Type IV Tubing, Inch/Pound Units

Nominal OD Inches	Minimum Wall Thickness Inch	Nominal ID Inches	Nominal Weight Pounds/Foot
0.405	0.062	0.281	0.253
0.540	0.065	0.410	0.368
0.675	0.065	0.545	0.472
0.840	0.065	0.710	0.600
1.050	0.065	0.920	0.763
1.315	0.066	1.183	0.982
1.660	0.084	1.492	1.577
1.900	0.096	1.709	2.053
2.375	0.120	2.135	3.224
2.875	0.145	2.585	4.716
3.500	0.177	3.146	7.006
4.000	0.202	3.596	9.139
4.500	0.228	4.044	11.603
5.563	0.281	5.001	17.681
6.625	0.335	5.955	25.102
8.625	0.436	7.753	42.534
10.750	0.544	9.662	66.142

TABLE 6B - Sizes and Weights - Type IV Tubing, SI Units

Nominal OD Millimeters	Minimum Wall Thickness Millimeters	Nominal ID Millimeters	Nominal Weight kg/m
10.29	1.57	7.14	0.38
13.72	1.65	10.41	0.55
17.14	1.65	13.84	0.70
21.34	1.65	18.03	0.89
26.67	1.65	23.37	1.14
33.40	1.68	30.05	1.46
42.16	2.13	37.90	2.35
48.26	2.44	43.41	3.06
60.32	3.65	54.23	4.80
73.02	3.68	65.66	7.02
88.90	4.50	79.91	10.43
101.60	5.13	91.34	13.60
114.30	5.79	102.72	17.27
141.30	7.14	127.02	26.31
168.28	8.51	151.26	37.36
219.08	11.07	196.93	63.30
273.05	13.82	245.41	98.43

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of tubing shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the tubing conforms to specified requirements.