

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS4725 A

Issued 12-1-47

Revised 6-1-51

COPPER-BERYLLIUM ALLOY WIRE

98Cu - 1.9Be

Solution Treated

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for parts requiring high strength with good electrical conductivity or lack of magnetic susceptibility.
3. COMPOSITION:

Beryllium	1.8 - 2.05
Nickel + Cobalt	0.20 min
Nickel + Cobalt + Iron	0.60 max
Copper + Total Named Elements	99.5 min

4. CONDITION: Cold drawn or rolled and solution heat treated, in a suitable condition for precipitation heat treatment.

5. TECHNICAL REQUIREMENTS:

5.1 Tensile Properties:

Tensile Strength, psi	58,000 - 78,000
Elongation, % in 2 in.	35 min

- 5.2 Tensile Properties After Precipitation Heat Treatment: Wire after being heated at 600 F $\pm$ 5 for 3 hr and cooling in air shall conform to the following requirements:

Tensile Strength, psi	160,000 min
Elongation, % in 2 in.	1.5 min

6. QUALITY: Wire shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and internal and external defects detrimental to fabrication or to performance of parts..
7. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2224 as applicable. Diameter, thickness and width tolerances shall be as specified below:
 - 7.1 Rounds, Hexagons and Octagons: Table II, Refractory.
 - 7.2 Squares: Table III, Refractory.
 - 7.3 Rectangles, Thickness: Table III, Refractory.
 - 7.4 Rectangles, Width: Table IV, Refractory.

7C of the SAE Technical Board rules provides that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."