

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 4845 D

Issued 12-5-39

Revised 6-1-51

BRONZE CASTINGS 88Cu - 10Sn - 2Zn

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. APPLICATION: Primarily for bearings.

3. COMPOSITION:

Copper	86.0 - 89.0
Tin	9.0 - 11.0
Zinc	1.0 - 3.0
Lead	0.30 max
Iron	0.15 max
Phosphorus	0.05 max
Total Named Elements	99.7 min

4. CONDITION: As cast.

5. TECHNICAL REQUIREMENTS:

5.1 Casting: A melt shall be the metal withdrawn from a batch furnace charge of 2000 pounds or less as melted for pouring castings.

5.2 Hardness:

5.2.1 Sand Castings: Shall have hardness not lower than Rockwell F 70 or equivalent.

5.2.2 Chill and Centrifugal Castings: Shall have hardness not lower than Rockwell F 80 or equivalent.

5.3 Fracture Test: When castings are broken for fracture test, the fracture shall have uniform color and be substantially free from oxides, blowholes, porosity and other defects. Castings shall be sufficiently ductile to show some bending before rupture.

6. QUALITY:

6.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned.

6.2 Inspection standards and procedures shall be as agreed upon by purchaser and vendor.

6.3 Castings shall not be repaired by plugging, welding or other methods, without written permission from purchaser.

Sec. 1 of the SAE Technical Board rules provides that: "All technical reports, including standards, are advisory only. Their use in industry or trade is entirely voluntary. There is no agreement to adhere to a standard or recommended practice, and no commitment to conduct or be guided by any technical report. In formulating and approving technical reports, the board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."