

**AEROSPACE
MATERIAL
SPECIFICATION****SAE AMS4892****REV. C**

Issued	1959-01
Revised	2006-09
Reaffirmed	2012-02
Superseding AMS4892B	

Alloy Castings, Corrosion and Heat-Resistant
66Ni - 29Cu - 4.0Si
As Cast

(Composition similar to UNS N04019)

RATIONALE

AMS4892C has been reaffirmed to comply with the SAE five-year review policy.

1. SCOPE**1.1 Form**

This specification covers a nickel-copper alloy in the form of castings.

1.2 Application

These castings have been used typically for parts requiring resistance to wear and galling under light-to-medium loads against dissimilar materials of higher hardness, and retention of hot hardness up to 1000 °F (538 °C), but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2175	Castings, Classification and Inspection of
AMS 2694	Repair Welding of Aerospace Castings
AMS 2804	Identification, Castings

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2012 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
SAE WEB ADDRESS: <http://www.sae.org>

**SAE values your input. To provide feedback
on this Technical Report, please visit
<http://www.sae.org/technical/standards/AMS4892C>**

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 10	Brinell Hardness of Metallic Materials
ASTM E 76	Chemical Analysis of Nickel-Copper Alloys
ASTM E 272	Reference Radiographs for High-Strength Copper-Base and Nickel-Copper Alloy Castings
ASTM E 1417	Liquid Penetrant Inspection
ASTM E 1742	Radiographic Examination

3. TECHNICAL REQUIREMENTS

3.1 Composition

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 76, by spectrochemical methods or by other analytical methods acceptable to purchaser.

TABLE 1 - COMPOSITION

Element	min	max
Nickel	60.0	--
Copper	27.0	31.0
Silicon	3.5	4.5
Iron	--	2.5
Manganese	--	1.5
Cobalt	--	1.0
Carbon	--	0.25
Sulfur	--	0.015

3.2 Condition

As cast.

3.2.1 Centrifugal Castings

Shall be rough turned and bored.

3.2.2 Sand Castings

Solid round bars shall be rough turned.

3.3 Casting

Castings shall be produced in lots from metal conforming to 3.1. A lot shall be all castings produced from one furnace melt or crucible melt. When two or more furnace melts or crucible melts or combination thereof are used to charge a ladle for pouring, the castings therefrom shall constitute a lot. A lot shall be not more than 2000 pounds (907 kg) of castings.

3.4 Chemical Analysis Specimens

Shall be cast from each melt and shall be of any convenient size, shape, and form. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

3.5 Properties

Castings shall conform to the following requirements:

3.5.1 Hardness

Shall be as follows, determined in accordance with ASTM E 10:

3.5.1.1 Castings over 0.25 inch (6.25 mm) in nominal cross-section shall have hardness not lower than 277 HB or equivalent (See 8.4).

3.5.1.2 Response to Heat Treatment

Castings 0.25 inch (6.35 mm) and under in nominal cross-section shall meet the requirements of 3.5.1.1 after being precipitation heat treated by heating to $1100\text{ }^{\circ}\text{F} \pm 25$ ($593\text{ }^{\circ}\text{C} \pm 14$), holding at heat for 4 to 6 hours and air or furnace cooling.

3.6 Quality

3.6.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.6.1.1 Castings shall have smooth surfaces and shall be sufficiently cleaned to permit fluorescent penetrant inspection. Metallic shot or grit shall not be used for final cleaning.

3.6.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of castings in accordance with ASTM E 1742 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.6.3 Castings, when specified, shall be subjected to fluorescent penetrant inspection in accordance with ASTM E 1417.

3.6.4 Acceptance standards for radiographic, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. AMS 2175 may be used to specify acceptance standards (casting grade) and frequency of inspection (casting class).

3.6.4.1 When acceptance standards are not specified, Grade C of AMS 2175 shall apply for each applicable method of inspection.

3.6.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.6.5.1 When permitted in writing by purchaser, defects in castings may be repaired by welding in accordance with AMS 2694.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1.1) and hardness of castings over 0.25 inch (6.35 mm) in nominal cross-section (3.5.1.1) are acceptance tests and shall be performed on each heat or lot as applicable.

4.2.2 Periodic Tests

Hardness of castings 0.25 inch (6.35 mm) and under in nominal cross-section after precipitation heat treatment (3.5.1.2) and radiographic soundness (3.6.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests

All technical requirements are preproduction tests and shall be performed on sample castings (4.3.2), when a change in control factors occurs (4.4.2.1), and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing

The minimum testing performed by vendor shall be in accordance with the following:

4.3.1 One chemical analysis specimen in accordance with 3.4 from each melt or a casting from each lot.

4.3.2 One preproduction casting in accordance with 4.4 shall be tested to the requirements of the casting drawing and to all technical requirements.

4.4 Approval

4.4.1 Sample castings from new or reworked patterns or molds and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall establish for production of sample castings of each part number, parameters for the process control factors which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, test specimens and/or sample castings. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.

4.4.2.1 Control factors for producing castings include, but are not limited to, the following:

- Type of furnace
- Furnace atmosphere
- Fluxing or deoxidation procedure
- Gating and risering practices
- Metal pouring temperature; variation of ± 50 °F (± 10 °C) from the established limit is permissible
- Mold setup, parting agent and rotational speed for centrifugal castings
- Solidification and cooling procedures
- Cleaning operations
- Methods of inspection

4.4.2.1.1 Any of the above process control factors for which parameters are considered proprietary by the vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.