

AEROSPACE MATERIAL SPECIFICATION

SAE

AMS 4982B

Issued 15 DEC 1974
Revised 1 OCT 1993

Superseding AMS 4982A

Submitted for recognition as an American National Standard

TITANIUM ALLOY WIRE 44.5 Cb

UNS R58450

1. SCOPE:

1.1 Form:

The specification covers a titanium alloy in the form of wire.

1.2 Application:

This wire has been used typically for parts, such as fasteners, where cold formability is desirable or necessary and which requires a high strength-to-weight ratio up to 800 °F (427 °C), but usage is not restricted to such applications.

1.3 Classification:

This specification covers two types of wire based upon condition supplied, as follows:

- a. Type 1: Annealed
- b. Type 2: As drawn

1.3.1 Type 1 shall be supplied unless Type 2 is specified.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2241 Tolerances, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS 2241 Tolerances, Metric, Corrosion and Heat Resistant Steel, Iron Alloy, Titanium, and Titanium Alloy Bars and Wire

AMS 2249 Chemical Check Analysis Limits, Titanium and Titanium Alloys

AMS 2809 Identification, Titanium and Titanium Alloy Wrought Products

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 8 Tension Testing of Metallic Materials

ASTM E 8M Tension Testing of Metallic Materials (Metric)

ASTM E 112 Determining the Average Grain Size

ASTM E 120 Chemical Analysis of Titanium and Titanium Alloys

ASTM E 1409 Determination of Oxygen in Titanium and Titanium Alloys by the Inert Gas Fusion Technique

ASTM E 1447 Determination of Hydrogen in Titanium and Titanium Alloys by the Inert Gas Fusion Thermal Conductivity Method

2.3 U.S. Government Publications:

Available from DODSSP, Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163 Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:**3.1 Composition:**

(R)

Shall conform to the percentages by weight shown in Table 1, determined by analytical methods in accordance with ASTM E 120, ASTM E 1409 or ASTM E 1447, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	Min	Max
Columbium	42.00	47.00
Oxygen	--	0.16
Carbon	--	0.04
Silicon	--	0.03
Nitrogen	--	0.03 (300 ppm)
Iron	--	0.03
Chromium	--	0.02
Magnesium	--	0.01
Manganese	--	0.01
Hydrogen	--	0.0035 (35 ppm)
Residual Elements, total (3.1.1)	--	0.40
Titanium	remainder	

3.1.1 Determination not required for routine acceptance.

3.1.2 Check Analysis:

Composition variations shall meet the requirements of AMS 2249 except that no check analysis limits apply for columbium.

3.2 Melting Practice:

(R) Alloy shall be multiple melted. Melting cycle(s) prior to the final melting cycle shall be made using consumable electrode, nonconsumable electrode, electron beam, or plasma arc melting practice(s). The final melting cycle shall be made under vacuum using consumable electrode practice with no alloy additions permitted.

3.2.1 The atmosphere for nonconsumable electrode melting shall be vacuum or shall
(R) be argon and/or helium at an absolute pressure not higher than 1000 mm of mercury.

3.2.2 The electrode tip for nonconsumable electrode melting shall be water-cooled
(R) copper.

3.3 Condition:

3.3.1 Type 1 Wire: Cold finished and annealed.

3.3.2 Type 2 Wire: Cold finished, with drawing lubricant removed, unless
(R) otherwise specified by purchaser.

3.4 Heat Treatment:**(R)**

Type 1 wire shall be annealed by heating in vacuum (less than 0.1 μm mercury) to a temperature within the range 1450 to 1600 °F (788 to 871 °C), holding at heat for sufficient time to produce a recrystallized structure which will meet the requirements of 3.5, and cooling as required.

3.5 Properties:

Wire shall conform to the following requirements:

3.5.1 Type 1 Annealed Wire:

3.5.1.1 Tensile Properties: Shall be as shown in Table 2, determined in accordance with ASTM E 8 or ASTM E 8M as applicable, with the rate of strain maintained at 0.003 to 0.007 inch/inch per minute (0.003 to 0.007 mm/mm per minute) through the yield strength and then increased so as to produce failure in approximately one additional minute. When a dispute occurs between purchaser and vendor over the yield strength values, a referee test shall be performed on a machine having a strain rate pacer using a rate of 0.005 inch/inch per minute (0.005 mm/mm per minute) through the yield strength and a minimum cross-head speed of 0.10 inch per minute (0.04 mm/s) above the yield strength.

TABLE 2 - Minimum Tensile Properties

Properties	Value
Tensile Strength	65.0 ksi (448 MPa)
Yield Strength at 0.2% Offset	60.0 ksi (414 MPa)
Elongation in 2 Inches (50.8 mm) or 4D	10%
Reduction of Area	50%

3.5.1.1.1 Yield strength and reduction of area requirements do not apply to wire under 0.125 inch (3.18 mm) in diameter.

3.5.1.2 Grain Size: Shall be ASTM No. 5 or finer with occasional fields as large as ASTM No. 4 permitted, determined by comparison of a polished and etched sample with the chart in ASTM E 112.

3.5.2 Type 2 As-Drawn Wire: Shall be as agreed upon by purchaser and vendor except that Type 2 wire annealed as in 3.4 shall also meet the requirements of 3.5.1.1 and 3.5.1.2.

3.6 Quality:**(R)**

Wire, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the wire.

3.7 Tolerances:

Shall conform to all applicable requirements of AMS 2241 or MAM 2241.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

- (R) The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Tests for the following requirements are acceptance tests and shall be performed on each heat or lot as applicable:

4.2.1.1 Type 1:

4.2.1.1.1 Composition (3.1) of each heat.

4.2.1.1.2 Hydrogen content (3.1), tensile properties (3.5.1), grain size (3.5.2) and tolerances (3.7) of each lot.

4.2.1.2 Type 2:

4.2.1.2.1 Composition (3.1) of each heat.

4.2.1.2.2 Tolerances (3.7) of each lot.

4.2.2 Periodic Tests: Tests of Type 2 wire to demonstrate ability to develop required properties (3.5.2) are periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.

4.3 Sampling and Testing:

- (R) Shall be in accordance with the following; a lot shall be all wire of the same nominal size from the same heat processed at the same time:

4.3.1 For Acceptance Tests:

4.3.1.1 Type 1:

4.3.1.1.1 Composition: One or more samples from each heat, except that for hydrogen determinations one sample from each lot obtained after thermal and chemical processing is completed.

4.3.1.1.2 Tensile Properties and Grain Size: At least one sample from each lot.