

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5010C

Issued 1-22-40

Revised 3-1-51

STEEL Screw Stock (SAE 1112)

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

2. FORM: Bars.

3. COMPOSITION:

		Check Analysis	
		Under	Min or Over Max
Carbon	0.13 max	--	0.02
Manganese	0.70 - 1.00	0.06	0.06
Phosphorus	0.07 - 0.12	--	0.01
Sulphur	0.16 - 0.23	--	--

4. CONDITION: Cold finished.

5. TECHNICAL REQUIREMENTS: Bars in the following size ranges shall have hardness within the respective limits.

Nominal Diameter or Distance between parallel sides Inches	Hardness, Brinell
1.00 and under	170 - 255
Over 1.00 to 2.25, incl	156 - 201

6. QUALITY: Material shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects, consistent with the type of steel involved, detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2231 as applicable. Diameter and thickness tolerances shall conform to Table I, column headed "0.28 and under".

8. REPORTS:

- 8.1 Unless otherwise specified, the vendor of bars shall furnish with each shipment three copies of a report of the results of tests for chemical composition. This report shall include the purchase order number, material specification number, size and quantity.

7C of the SAE Technical Board rules provides that: "All technical reports, including standards, approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."