



AEROSPACE MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
TWO PENNSYLVANIA PLAZA, NEW YORK, N.Y. 10001

AMS 5027

Issued 5-1-70
Revised

STEEL WIRE, WELDING
1.05Cr - 0.55Ni - 1.0Mo - 0.07V (0.26 - 0.32C)
Vacuum Melted, Environment Controlled

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for gas tungsten-arc welding structural assemblies requiring heat treatment response to high strength levels.
3. COMPOSITION:

	min	max
Carbon	0.26	0.32
Manganese	0.60	0.90
Silicon	0.15	0.30
Phosphorus	--	0.010
Sulfur	--	0.010
Chromium	0.90	1.20
Nickel	0.40	0.70
Molybdenum	0.90	1.10
Vanadium	0.05	0.10
Copper	--	0.35
Hydrogen	--	0.0010 (10 ppm)
Oxygen	--	0.0025 (25 ppm)
Nitrogen	--	0.0050 (50 ppm)

- 3.1 Check Analysis: Composition variations shall meet the requirements of the latest issue of AMS 2259, paragraph titled "Low Alloy Steels."
4. CONDITION: Unless otherwise specified, wire shall be formed from bar descaled by a process which does not affect the composition of the material. Surface irregularities inherent with a forming process which does not tear the wire surface are acceptable provided the wire conforms to the tolerances of Section 7 and the irregularities are free from contaminants.
 - 4.1 Temper: Unless otherwise specified, wire shall be in the as-drawn temper.
 - 4.2 Drawing compounds, oxides, and dirt shall be removed from the surface of the wire.
5. TECHNICAL REQUIREMENTS:
 - 5.1 Welding: Melted wire shall flow smoothly and evenly during welding and shall be capable of producing acceptable welds by a method agreed upon by purchaser and vendor.
 - 5.2 Spooled Wire: Shall conform to the following unless otherwise agreed upon by purchaser and vendor.
 - 5.2.1 Cast: Wire shall have imparted to it a curvature such that a specimen sufficient in length to form one loop, when cut from the spool and laid on a flat surface, shall form a circle not less than 15 in. and not greater than 30 in. in diameter.
 - 5.2.2 Helix: The specimen on which cast was determined, when laid on a flat surface and measured between adjacent turns, shall show a vertical separation not greater than 1 inch.

SAE Technical Board rules provide that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against infringement of patents."