

**AEROSPACE
MATERIAL
SPECIFICATION**

AMS 5032D
Superseding AMS 5032C

Issued 10-1-43
Revised 7-1-84

STEEL WIRE
0.18 - 0.23C (SAE 1020)

UNS G10200

1. SCOPE:

1.1 Form: This specification covers a low-carbon steel in the form of wire.

1.2 Application: Primarily for use as lockwire.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels

AMS 2350 - Standards and Test Methods

AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock

2.2 ASTM Publications: Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products

ASTM E350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

AMS 5032D

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.3 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

- 3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E350, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.18	0.23
Manganese	0.30	0.60
Phosphorus	--	0.040
Sulfur	--	0.050
Copper	--	0.15

- 3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

- 3.2 Condition: Cold drawn and bright annealed.

- 3.3 Properties: Wire shall conform to the following requirements:

- 3.3.1 Tensile Properties: Shall be as follows, determined in accordance with ASTM A370:

Tensile Strength	50,000 - 75,000 psi (345 - 515 MPa)
Elongation in 10 in. (250 mm), min	15%

- 3.3.2 Bending: A length of wire not less than 12 in. (300 mm) long shall withstand, without splitting or breaking, being wrapped in a closed helix for at least six complete turns around a cylindrical mandrel having a diameter equal to the nominal diameter of the wire and then unwrapped.

- 3.4 Quality: Wire, as received by purchaser, shall be uniform in quality and condition, sound, cylindrical, and free from kinks, twists, scrapes, splits, laps, seams, and other imperfections detrimental to usage of the wire.

- 3.4.1 The surface of the wire shall have a bright, smooth finish free from pits, abrasions, and other surface defects.

- 3.5 Tolerances: Unless otherwise specified, diameter tolerances shall conform to Table I.

TABLE I

Nominal Diameter Inch	Tolerance, Inch plus and minus
Up to 0.076, excl	0.001
0.076 to 0.249, incl	0.002

TABLE I (SI)

Nominal Diameter Millimetres	Tolerance, Millimetre plus and minus
Up to 1.90, excl	0.02
1.90 to 6.25, incl	0.05

4. QUALITY ASSURANCE PROVISIONS:

- 4.1 Responsibility for Inspection: The vendor of wire shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the wire conforms to the requirements of this specification.
- 4.2 Classification of Tests: Tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each heat or lot as applicable.
- 4.3 Sampling: Shall be in accordance with AMS 2370.
- 4.4 Reports:
- 4.4.1 The vendor of wire shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and for tensile and bending properties of each lot. This report shall include the purchase order number, heat number, AMS 5032D, size, and quantity from each heat.
- 4.4.2 The vendor of finished or semi-finished parts shall furnish with each shipment a report showing the purchase order number, AMS 5032D, contractor or other direct supplier of wire, part number, and quantity. When wire for making parts is produced or purchased by the parts vendor, that vendor shall inspect each lot of wire to determine conformance to the requirements of this specification and shall include in the report either a statement that the wire conforms or copies of laboratory reports showing the results of tests to determine conformance.

AMS 5032D

4.5 Resampling and Retesting: Shall be in accordance with AMS 2370.

5. PREPARATION FOR DELIVERY:

5.1 Identification: Wire shall be identified as follows:

5.1.1 Coils or reels of wire shall each be identified by a durable tag marked with the purchase order number, AMS 5032D, nominal size, quantity, and manufacturer's identification or shall be boxed and the box marked with the same information.

5.1.2 Straight lengths shall be bundled or boxed and shall have attached to each bundle or box a durable tag marked with the information of 5.1.1.

5.2 Protective Treatment: Wire, prior to shipment, shall be coated with a suitable corrosion-preventive compound.

5.3 Packaging:

5.3.1 Wire shall be furnished in coils, unless otherwise ordered. Each coil shall be one continuous length, properly coiled, and firmly tied.

5.3.2 Packaging shall be accomplished in such a manner as to ensure that the wire, during shipment and storage, will be protected against mechanical injury and exposure to moisture.

5.3.3 Packages of wire shall be prepared for shipment in accordance with commercial practice and in compliance with applicable rules and regulations pertaining to the handling, packaging, and transportation of the wire to ensure carrier acceptance and safe delivery. Packaging shall conform to carrier rules and regulations applicable to the mode of transportation.

5.3.4 For direct U.S. Military procurement, packaging shall be in accordance with MIL-STD-163, Level A or Level C, as specified in the request for procurement. Commercial packaging as in 5.3.1, 5.3.2, and 5.3.3 will be acceptable if it meets the requirements of Level C.

6. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.

7. REJECTIONS: Wire not conforming to this specification or to modifications authorized by purchaser will be subject to rejection.

8. NOTES:

8.1 Marginal Indicia: The phi (ϕ) symbol is used to indicate technical changes from the previous issue of this specification.