



AEROSPACE MATERIAL SPECIFICATION

AMS5042™**REV. N**

Issued	1940-03
Revised	2003-12
Noncurrent	2009-08
Reaf. Nonc.	2013-09
Stabilized	2017-08

Superseding AMS5042M

Steel, Sheet and Strip
0.15 Carbon, Maximum
Forming Grade

RATIONALE

AMS5042N has been stabilized as mature technology that has similar specifications.

STABILIZED NOTICE

AMS5042N has been declared "STABILIZED" by SAE AMS Carbon and Low Alloy Steels Committee E. This document will no longer be updated and may no longer represent standard industry practice. This document was stabilized because other documents contain similar but not necessarily equivalent requirements. Previously this document was reaffirmed non-current. The last technical update of this document occurred in December 2003. Users of this document should refer to the cognizant engineering organization for disposition of any issues with reports/certifications to this specification; including exceptions listed on the certification.

NOTE: In many cases, the purchaser may represent a sub tier supplier and not the cognizant engineering organization.

AMS Committee E recommends that the following similar but not identical specifications may be considered for future procurement. This listing does not constitute authority to substitute these specifications for the "STABILIZED" specification.

ASTM A109/A109M Steel, Strip, Carbon (0.25 Maximum Percent), Cold-Rolled

ASTM A1008/A1008M Steel, Sheet, Cold-Rolled, Carbon, Structural, High-Strength Low-Alloy, High-Strength Low-Alloy with Improved Formability, Solution Hardened, and Bake Hardenable

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be revised, reaffirmed, stabilized, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2017 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
Tel: +1 724-776-4970 (outside USA)
Fax: 724-776-0790
Email: CustomerService@sae.org
http://www.sae.org

SAE WEB ADDRESS:

**SAE values your input. To provide feedback on this
Technical Report, please visit
<http://standards.sae.org/AMS5042N>**

1. SCOPE:

1.1 Form:

This specification covers a carbon steel in the form of sheet and strip.

1.2 Application:

These products have been used typically for drawn and formed parts requiring a steel of moderate ductility, but usage is not limited to such applications.

2. APPLICABLE DOCUMENTS:

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001 or www.sae.org.

AMS 2232	Tolerances, Carbon Steel Sheet, Strip, and Plate
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat-Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing

SAENORM.COM : Click to view the full PDF of ams5042

2.2 ASTM Publications:

Available from ASTM, 100 Barr Harbor Drive, West Conshohocken, PA 19428-2959 or www.astm.org.

ASTM A 370 Mechanical Testing of Steel Products
 ASTM E 350 Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	min	max
Carbon	--	0.15
Manganese	0.30	0.60
Phosphorus	--	0.035
Sulfur	--	0.040

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

Product shall be supplied skin rolled.

3.3 Properties:

The product shall conform to the following requirements; hardness and bend tests shall be performed in accordance with ASTM A 370:

3.3.1 Hardness: Shall be as shown in Table 2, or equivalent (See 8.2).

TABLE 2 - Hardness

Nominal Thickness Inch	Nominal Thickness Millimeters	Hardness
0.009 to 0.014, incl	0.23 to 0.36, incl	95 to 115 HV (1 kg load)
Over 0.014 to 0.027, incl	Over 0.36 to 0.69, incl	77 to 82 HR15T
Over 0.027 to 0.059, incl	Over 0.69 to 1.50, incl	51 to 60 HR30T
Over 0.059 to 0.089, incl	Over 1.50 to 2.26, incl	86 to 94 HRF
Over 0.089 to 0.187, incl	Over 2.26 to 4.75, incl	52 to 64 HRB
Over 0.187	Over 4.75	45 to 64 HRB

3.3.2 Bending: The product shall withstand, without cracking, bending at room temperature flat on itself with axis of bend parallel to the direction of rolling.

3.4 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.5 Tolerances:

Shall conform to all applicable requirements of AMS 2232.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to specified requirements.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be in accordance with AMS 2370.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for composition of each heat and the hardness of each lot and stating that the product conforms to the other technical requirements. This report shall include the purchase order number, heat and lot numbers, AMS 5042N, size, and quantity.

4.5 Resampling and Retesting:

Shall be in accordance with AMS 2370.

5. PREPARATION FOR DELIVERY:

5.1 Identification:

Shall be in accordance with AMS 2807.