

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5061

Issued 9-1-48

Revised

STEEL - LOW CARBON

1. **ACKNOWLEDGMENT:** A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. **FORM:** Rod and wire not exceeding 3/4 in. in diameter.
3. **APPLICATION:** Primarily for manufacture of cold-headed threaded parts.
4. **COMPOSITION:**

		Check Analysis	
		Under Min	or Over Max

Carbon	0.08 - 0.20	0.01	0.01
Manganese	0.40 - 0.80	0.03	0.03
Phosphorus	0.040 max	—	0.008
Sulfur	0.050 max	—	0.008

5. **CONDITION:** Cold drawn.

6. **TECHNICAL REQUIREMENTS:**

- 6.1 **Physical Properties:** Material shall conform to the following requirements:

Tensile Strength, psi	70,000 min
Elongation, % in 4D	10 min
Hardness, Rockwell	B85-102

7. **QUALITY:** Material shall be uniform in quality and condition, clean, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts.

8. **TOLERANCES:** Unless otherwise specified, tolerances shall conform to the latest issue of AMS 2231 as applicable. Diameter tolerances shall conform to Table I, column headed "Mean of Carbon .30% and less".

9. **REPORTS:**

- 9.1 Unless otherwise specified, the vendor of the product shall furnish with each shipment three copies of a notarized report of the results of tests for chemical composition of each lot in the shipment. This report shall include the purchase order number, material specification number, size, and quantity.

Section of the SAE Technical Board rules provides that: "All technical reports, including standards, revised and practices recommended, are advisory only. Their use is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report, in formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."