

AEROSPACE MATERIAL SPECIFICATION



AMS 5062F

Issued SEP 1948
Revised JUL 1994
Reaffirmed SEP 2000

Superseding AMS 5062E

Steel, Low Carbon
Bars, Forgings, Tubing, Sheet, Strip, and Plate
0.25 Carbon, Maximum

UNS K02508

1. SCOPE:

1.1 Form:

This specification covers low-carbon steel in the form of bars, forgings, mechanical tubing, sheet, strip, plate, and forging stock.

1.2 Application:

These products have been used typically for parts for which a wide latitude in composition is permissible and requiring no particular strength or hardness other than that inherent in steel of this type, but usage is not limited to such applications.

1.2.1 Care is required in welding in the event that carbon and manganese approach the maximum limits.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be the issue in effect on the date of the purchase order.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright 2000 Society of Automotive Engineers, Inc.
All rights reserved.

Printed in U.S.A.

QUESTIONS REGARDING THIS DOCUMENT:
TO PLACE A DOCUMENT ORDER:
SAE WEB ADDRESS:

(724) 772-7161
(724) 776-4970
<http://www.sae.org>

FAX: (724) 776-0243
FAX: (724) 776-0790

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096-0001.

AMS 2231	Tolerances, Carbon Steel Bars
MAM 2231	Tolerances, Metric, Carbon Steel Bars
AMS 2232	Tolerances, Carbon Steel Sheet, Strip, and Plate
MAM 2232	Tolerances, Metric, Carbon Steel Sheet, Strip, and Plate
AMS 2253	Tolerances, Carbon and Alloy Steel Tubing
MAM 2253	Tolerances, Metric, Carbon and Alloy Steel Tubing
AMS 2259	Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2370	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Wrought Products and Forging Stock
AMS 2372	Quality Assurance Sampling and Testing, Carbon and Low-Alloy Steel Forgings
AMS 2806	Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Heat and Corrosion Resistant Steels and Alloys
AMS 2807	Identification, Carbon and Low-Alloy Steels, Corrosion and Heat Resistant Steels and Alloys, Sheet, Strip, Plate, and Aircraft Tubing
AMS 2808	Identification, Forgings

2.2 ASTM Publications:

Available from ASTM, 1916 Race Street, Philadelphia, PA 19103-1187.

ASTM E 350	Chemical Analysis of Carbon Steel, Low-Alloy Steel, Silicon Electrical Steel, Ingot Iron, and Wrought Iron
------------	--

2.3 U.S. Government Publications:

Available from DODSSP Subscription Services Desk, Building 4D, 700 Robbins Avenue, Philadelphia, PA 19111-5094.

MIL-STD-163	Steel Mill Products, Preparation for Shipment and Storage
-------------	---

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser.

TABLE 1 - Composition

Element	max
Carbon	0.25
Manganese	1.00
Phosphorus	0.040
Sulfur	0.050

3.1.1 Check Analysis: Composition variations shall meet the applicable requirements of AMS 2259.

3.2 Condition:

The product shall be supplied in the following condition:

3.2.1 Bars and Mechanical Tubing 2.50 Inches (63.5 mm) and Under in Nominal OD or Distance Between Parallel Sides: Cold finished.

3.2.2 Bars and Mechanical Tubing Over 2.50 Inches (63.5 mm) in Nominal OD or Distance Between Parallel Sides: Hot finished and normalized or otherwise heat treated to produce optimum machinability.

3.2.3 Forgings: Normalized or otherwise heat treated to produce optimum machinability.

3.2.4 Sheet, Strip, and Plate: As rolled.

3.2.5 Forging Stock: As ordered by the forging manufacturer.

3.3 Quality:

The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4 Tolerances:

Shall be as follows:

3.4.1 Bars: Shall conform to all applicable requirements of AMS 2231 or MAM 2231.

3.4.2 Mechanical Tubing: Shall conform to all applicable requirements of AMS 2253 or MAM 2253.

3.4.3 Sheet, Strip, and Plate: Shall conform to all applicable requirements of AMS 2232 or MAM 2232.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 Classification of Tests:

Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 Sampling and Testing:

Shall be as follows:

4.3.1 Bars, Mechanical Tubing, Sheet, Strip, Plate, and Forging Stock: In accordance with AMS 2370.

4.3.2 Forgings: In accordance with AMS 2372.

4.4 Reports:

The vendor of the product shall furnish with each shipment a report showing the results of tests for chemical composition of each heat. This report shall include the purchase order number, lot number, AMS 5062F, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.5 Resampling and Retesting:

Shall be as follows:

4.5.1 Bars, Mechanical Tubing, Sheet, Strip, Plate, and Forging Stock: In accordance with AMS 2370.

4.5.2 Forgings: In accordance with AMS 2372.

5. PREPARATION FOR DELIVERY:

5.1 Sizes:

Except when exact lengths or multiples of exact lengths are ordered, straight bars and tubing will be acceptable in mill lengths of 6 to 20 feet (1.8 to 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).