

SAE-AMS5069

ADOPTION NOTICE

SAE-AMS5069, "Bars, Forgings, and Tubing, 0.15-0.23C," was adopted on October 3, 1994, for use by the Department of Defense (DoD). Proposed changes by DoD activities must be submitted to the DoD Adopting Activity: Commander, Defense Industrial Supply Center, Attn: DISC-E, Philadelphia, PA 19111-5096. DoD activities may obtain copies of this standard from the Standardization Document Order Desk, 700 Robbins Avenue, Building 4D, Philadelphia, PA 19111-5094. The private sector and other Government agencies may purchase copies from the Society of Automotive Engineers, Inc., 400 Commonwealth Drive, Warrendale, PA 15096.

Custodians:

Army - ER
Navy - AS
Air Force - 99
DLA - IS

Adopting Activity
DLA - IS

FSG 95G

DISTRIBUTION STATEMENT A. Approved for public release;
distribution is unlimited.

AEROSPACE MATERIAL SPECIFICATION

Submitted for recognition as an American National Standard

AMS 5069E

Issued 1-15-59
Revised 1-1-90

Superseding AMS 5069D

STEEL BARS, FORGINGS, AND TUBING 0.15 - 0.20C (SAE 1018)

UNS G10180

1. SCOPE:

- 1.1 Form: This specification covers a low-carbon steel in the form of bars, forgings, mechanical tubing, and forging stock.
- 1.2 Application: Primarily for parts requiring low strength and high ductility.

2. APPLICABLE DOCUMENTS: The following publications form a part of this specification to the extent specified herein. The latest issue of SAE publications shall apply. The applicable issue of other publications shall be as specified in AMS 2350.

- 2.1 SAE Publications: Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

- AMS 2231 - Tolerances, Carbon Steel Bars
MAM 2231 - Tolerances, Metric, Carbon Steel Bars
AMS 2253 - Tolerances, Carbon and Alloy Steel Tubing
MAM 2253 - Tolerances, Metric, Carbon and Alloy Steel Tubing
AMS 2259 - Chemical Check Analysis Limits, Wrought Low-Alloy and Carbon Steels
AMS 2350 - Standards and Test Methods
AMS 2370 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Wrought Products Except Forgings and Forging Stock
AMS 2372 - Quality Assurance Sampling of Carbon and Low-Alloy Steels, Forgings and Forging Stock
AMS 2806 - Identification, Bars, Wire, Mechanical Tubing, and Extrusions, Carbon and Alloy Steels and Corrosion and Heat Resistant Steels and Alloys
AMS 2808 - Identification, Forgings

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS documents are protected under United States and international copyright laws. Reproduction of these documents by any means is strictly prohibited without the written consent of the publisher.

2.2 ASTM Publications: Available from ASTM, 1916 Race Street, Philadelphia, PA 19103.

ASTM E 10 - Brinell Hardness of Metallic Materials
ASTM E 350 - Chemical Analysis of Carbon Steel, Low-Alloy Steel,
Silicon Electrical Steel, Ingot Iron, and Wrought Iron

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-163 - Steel Mill Products, Preparation for Shipment and Storage

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E 350, by spectrochemical methods, or by other analytical methods acceptable to purchaser:

	min	max
Carbon	0.15	0.20
Manganese	0.60	0.90
Silicon	0.15	0.35
Phosphorous	--	0.040
Sulfur	--	0.050

3.1.1 Check Analysis: Composition variations shall meet the applica requirements of AMS 2259.

3.2 Condition: The product shall be supplied in the following condition; hardness shall be determined in accordance with ASTM E 10:

3.2.1 Bars: Hot finished and annealed having hardness not higher than 229 HB, or equivalent, except that bars ordered cold finished may have hardness as high as 241 HB, or equivalent.

3.2.2 Forgings: As ordered.

3.2.3 Mechanical Tubing: Cold finished having hardness not higher than 241 HB, or equivalent.

3.2.4 Forging Stock: As ordered by the forging manufacturer.

3.3 **Quality:** The product, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the product.

3.4 **Sizes:** Except when exact lengths or multiples of exact lengths are ordered, straight bars and tubing will be acceptable in mill lengths of 6 - 20 feet (1.8 - 6.1 m) but not more than 10% of any shipment shall be supplied in lengths shorter than 10 feet (3 m).

3.5 **Tolerances:** Shall conform to all applicable requirements of the following:

3.5.1 **Bars:** AMS 2231 or MAM 2231.

3.5.2 **Mechanical Tubing:** AMS 2253 or MAM 2253.

4. QUALITY ASSURANCE PROVISIONS:

4.1 **Responsibility for Inspection:** The vendor of the product shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.4. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the product conforms to the requirements of this specification.

4.2 **Classification of Tests:** Tests for all technical requirements are acceptance tests and shall be performed on each heat or lot as applicable.

4.3 **Sampling and Testing:** Shall be in accordance with the following; the number of specimens to be sampled shall be the minimum number of specimens tested:

4.3.1 **Bars and Mechanical Tubing:** AMS 2370.

4.3.2 **Forgings and Forging Stock:** AMS 2372.

4.4 **Reports:**

4.4.1 The vendor of bars, forgings, and mechanical tubing shall furnish with each shipment a report showing the results of tests for chemical composition of each heat and stating that the product conforms to the other technical requirements of this specification. This report shall include the purchase order number, AMS 5069E, size, and quantity. If forgings are supplied, the part number and the size and melt source of stock used to make the forgings shall also be included.

4.4.2 The vendor of forging stock shall furnish with each shipment a report showing the results of tests for chemical composition of each heat. This report shall include the purchase order number, heat number, AMS 5069E, size, and quantity.