

AEROSPACE MATERIAL SPECIFICATIONS

SOCIETY OF AUTOMOTIVE ENGINEERS, Inc. 485 Lexington Ave., New York 17, N.Y.

AMS 5225A

Issued 8-15-55
Revised 7-15-63

ALLOY STRIP

Iron Base - 5.2Cr - 42Ni - 2.3Ti - 0.50Al
Cold Rolled, 50% Reduction

1. ACKNOWLEDGMENT: A vendor shall mention this specification number and its revision letter in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for diaphragms, leaf springs, and helical springs, requiring a precipitation-hardening alloy with a coefficient of modulus of elasticity of -20 to $+20 \times 10^{-6}$ per deg Fahr from -50 to $+150$ F (-36 to $+36 \times 10^{-6}$ per deg Cent from -45 to $+65$ C) after suitable heat treatment.

3. COMPOSITION:

Carbon	0.06 max
Manganese	0.8 max
Silicon	1.0 max
Phosphorous	0.04 max
Sulfur	0.04 max
Chromium	4.90 - 5.75
Nickel + Cobalt	41.0 - 43.5
Cobalt, if determined	1.0 max
Titanium	2.2 - 2.75
Aluminum	0.30 - 0.8
Chromium + (Titanium - 4xCarbon)	7.1 - 8.1
Iron	remainder

4. CONDITION: Solution heat treated at 1750 F ± 25 (954.4 C ± 14) for 15 to 30 min. at temperature and cold rolled with approximately 50% reduction in thickness.

5. TECHNICAL REQUIREMENTS:

- 5.1 Tensile Properties: Material 0.020 to 0.250 in., incl, in thickness shall meet the following requirements. Properties of material of other thicknesses shall be as agreed upon by purchaser and vendor:

Tensile Strength, psi	125,000 - 140,000
Elongation, % in 2 in.	3 min

- 5.2 Hardness: Shall be Rockwell C 24 - 32 or equivalent.

- 5.3 Grain Size: Predominantly 5 or finer with occasional grains as large as 3 permissible, determined in accordance with the issue of ASTM E112 listed in the latest issue of AMS 2350.

5.4 Properties After Precipitation Heat Treatment: Material 0.020 to 0.0250 in., incl, in thickness shall be capable of meeting the following requirements after being heated to 1350 F + 15 (732.2 C + 8.3), held at heat for 3 hr, and cooled in air. Properties of material of other thicknesses shall be as agreed upon by purchaser and vendor.

5.4.1 Tensile Properties:

Tensile Strength, psi	190,000 min
Yield Strength at 0.2% Offset or at 0.0162 in. in 2 in. Extension Under Load (E = 27,000,000), psi	165,000 min
Elongation, % in 2 in.	5 min

5.4.2 Hardness: Shall be Rockwell C 39 - 46 or equivalent.

6. QUALITY: Material shall be uniform in quality and condition, clean, sound, smooth, and free from foreign materials and from internal and external imperfections detrimental to fabrication or to performance of parts.

7. TOLERANCES: Unless otherwise specified, the following tolerances shall apply:

7.1 Thickness:

ø	Nominal Thickness (T) Inch	Thickness Tolerance, Inch, Plus and Minus Width Ranges, Inches	
		Up to 4.00, incl	Over 4.00 to 5.00, incl
	Up to 0.015, incl	0.0005	0.0006
	Over 0.015 to 0.025, incl	0.00075	0.0008
	Over 0.025 to 0.040, incl	0.001	0.001
	Over 0.040	0.025xT	0.025xT

7.1.1 When premium tolerances are specified on the purchase order, material shall conform to the following:

ø	Nominal Thickness (T) Inch	Thickness Tolerance, Inch, Plus and Minus Width Ranges, Inches	
		Up to 4.00, incl	Over 4.00 to 5.00, incl
	Up to 0.005, incl	0.0002	0.0003
	Over 0.005 to 0.010, incl	0.0003	0.0004
	Over 0.010 to 0.015, incl	0.0004	0.0005
	Over 0.015 to 0.025, incl	0.0005	0.0005
	Over 0.025	0.02xT	0.02xT