

AEROSPACE MATERIAL SPECIFICATION

AMS 5344E

Issued JUL 1963
Reaffirmed SEP 2000
Revised JUN 2006

Superseding AMS 5344D

Steel, Corrosion-Resistant, Investment Castings
16Cr - 4.1Ni - 0.28Cb - 3.2Cu
Homogenization, Solution, and Precipitation Heat Treated (H900)
180 ksi (1241 MPa) Tensile Strength

(Composition similar to UNS J92180 and J92200)

RATIONALE

AMS 5344E has been revised to remove the requirement to test for and certify tantalum, allowing to cool to room temperature after homogenization heat treatment, remove contradictory statements that implied tensile property evaluations were to be conducted on a master heat basis, perform non-destructive inspection and special processes in accordance with applicable ASTM or AMS in lieu of the previously required MIL specs, update reporting requirements and add new provisions for serialization, and is a Five Year Review and update of this specification.

1. SCOPE

1.1 Form

This specification covers a corrosion-resistant steel in the form of investment castings.

1.2 Application

These castings have been used typically for parts requiring good corrosion resistance and strength up to 600 °F (316 °C), but usage is not limited to such applications (See 8.4).

1.2.1 Certain processing procedures and service conditions may cause these castings to become subject to stress-corrosion cracking; ARP1110 recommends practices to minimize such conditions.

2. APPLICABLE DOCUMENTS

The issue of the following documents in effect on the date of the purchase order forms a part of this specification to the extent specified herein. The supplier may work to a subsequent revision of a document unless a specific document issue is specified. When the referenced document has been cancelled and no superseding document has been specified, the last published issue of that document shall apply.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2006 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)

Tel: 724-776-4970 (outside USA)

Fax: 724-776-0790

Email: CustomerService@sae.org

<http://www.sae.org>

SAE WEB ADDRESS:

2.1 SAE Publications

Available from SAE International, 400 Commonwealth Drive, Warrendale, PA 15096-0001, Tel: 877-606-7323 (inside USA and Canada) or 724-776-4970 (outside USA), www.sae.org.

AMS 2175	Castings, Classification and Inspection of
AMS 2248	Chemical Check Analysis Limits, Corrosion and Heat-Resistant, Steels and Alloys, Maraging, and Other Highly-Alloyed Steels, and Iron Alloys
AMS 2360	Room Temperature Tensile Properties of Castings
AMS 2694	Repair Welding of Aerospace Castings
AMS 2804	Identification, Castings
AMS-H-6875	Heat Treatment of Steel, Process for
AMS-QQ-P-35	Passivation Treatments for Corrosion-Resistant Steel
ARP1110	Minimizing Stress Corrosion Cracking in Wrought Forms of Steel and Corrosion-Resistant Steels and Alloys

2.2 ASTM Publications

Available from ASTM International, 100 Barr Harbor Drive, P.O. Box C700, West Conshohocken, PA 19428-2959, Tel: 610-832-9585, www.astm.org.

ASTM E 8	Tension Testing of Metallic Materials
ASTM E 8M	Tension Testing of Metallic Materials (Metric)
ASTM E 18	Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials
ASTM E 353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E 1444	Magnetic Particle Examination
ASTM E 1742	Radiographic Examination

2.3 U.S. Government Publications

Available from the Document Automation and Production Service (DAPS), Building 4/D, 700 Robbins Avenue, Philadelphia, PA 19111-5094, Tel: 215-697-6257, <http://assist.daps.dla.mil/quicksearch/>.

MIL-STD-453	Inspection, Radiographic (superseded by ASTM E 1742)
MIL-STD-2073-1	DOD Materiel, Procedures for Development and Application of Packaging Requirements
MIL-STD-6866	Inspection, Liquid Penetrant

3. TECHNICAL REQUIREMENTS

3.1 Composition

Castings shall conform to the percentages by weight shown in Table 1, determined by wet chemical methods in accordance with ASTM E 353, by spectrochemical methods, or by other analytical methods acceptable to purchaser (See 8.2.1 and 8.2.2).

TABLE 1 - COMPOSITION

Element	min	max
Carbon	--	0.06
Manganese	--	0.70
Silicon	0.50	1.00
Phosphorus	--	0.025
Sulfur	--	0.025
Chromium	15.50	16.70
Nickel	3.60	4.60
Columbium	0.15	0.40
Copper	2.80	3.50
Tantalum	--	0.05
Aluminum	--	0.05
Tin	--	0.02
Nitrogen	--	0.05

3.1.1 Vendor may test for any element not otherwise listed in Table 1 and include this analysis in the report of 4.5. Limits of acceptability may be specified by purchaser (See 8.2.3).

3.1.2 Check Analysis

Composition variations shall meet the applicable requirements of AMS 2248.

3.2 Melting Practice

Castings and specimens shall be poured at the casting vendor's facility either from a melt (See 8.2.4) of a master heat or directly from a master heat (See 8.2.5).

3.2.1 Revert (gates, sprues, risers, and rejected castings) may be used only in the preparation of master heats; revert shall not be remelted directly, without refining, for pouring of castings.

3.2.2 Portions of two or more qualified master heats (See 3.4.2) may be melted together and poured into castings using a procedure authorized by purchaser (See 8.2.6).

3.2.3 If alloy additions or replenishments are made at remelt by the vendor, vendor shall have a written procedure acceptable to purchaser which defines the controls, tests, and traceability criteria for both castings and separately-cast specimens. Control factors of 4.4.2.2 shall apply.

3.3 Condition

Castings shall be homogenization, solution, and precipitation heat treated, except as specified in 3.3.1 or 3.3.2.

3.3.1 When specified by purchaser, castings shall be solution and precipitation heat treated, omitting homogenization heat treatment.

3.3.2 When specified by purchaser, castings shall be solution heat treated twice and precipitation heat treated, omitting homogenization heat treatment.

3.4 Test Specimens

Specimens shall be either separately-cast, integrally-cast (See 8.2.7), or machined from castings, and shall conform to 3.2.

3.4.1 If specimens are separately-cast, vendor shall have a written procedure acceptable to purchaser. Control factors of 4.4.2.2 shall apply.

3.4.2 Each master heat shall be qualified by evaluation of chemical and tensile specimens.

3.4.2.1 If alloy additions or replenishments are made at remelt as in 3.2.3, the frequency of sampling and testing used by the vendor for qualification to 3.4.2 shall be acceptable to purchaser.

3.4.2.2 The tensile qualification tests of 3.4.2 are not required if these tests are conducted using integrally-cast specimens (4.3.3.2) or specimens machined from castings (4.3.3.3).

3.4.3 Chemical Analysis Specimens

Shall be of any convenient size and shape.

3.4.4 Tensile Specimens

Shall be of standard proportions in accordance with ASTM E 8 or ASTM E 8M (See 8.3) with 0.250 inch (6.35 mm) diameter at the reduced parallel gage section.

3.4.4.1 Separately-cast and integrally-cast specimens may be either cast to size, or cast oversize and subsequently machined to 0.250 inch (6.35 mm) diameter.

3.4.4.2 When integrally-cast specimens and specimens machined from castings are specified, specimen size and location shall be agreed upon by purchaser and vendor. (See 8.2.8 and 8.6.)

3.5 Heat Treatment

Castings and representative tensile specimens shall be heat treated in accordance with MIL-H-6875 except as specified in 3.5.1.

3.5.1 Castings and Tensile Specimens

3.5.1.1 Homogenization Heat Treatment

Heat to 2100 °F $\pm$ 25 (1149 °C $\pm$ 14), hold at heat for not less than 90 minutes, and cool as required to below 70 °F (21 °C).

3.5.1.2 Solution Heat Treatment

Heat to 1900 °F $\pm$ 25 (1038 °C $\pm$ 14), hold at heat for 1 hour per inch (25 mm) of section thickness but not less than 30 minutes, and cool as required to below 70 °F (21 °C).

3.5.1.3 Precipitation Heat Treatment

Heat to a temperature within the range 900 to 925 °F (482 to 496 °C), hold at the selected temperature within $\pm$ 10 °F ($\pm$ 6 °C) for not less than 90 minutes, and cool in air to room temperature.

3.5.2 Tensile specimens used for master heat qualification may be heat treated separately from castings.

3.6 Properties

Conformance shall be based upon testing of separately-cast specimens unless purchaser specifies integrally-cast specimens or specimens machined from castings.

3.6.1 Room Temperature Tensile Properties

Shall be as specified in 3.6.1.1 or 3.6.1.2, determined in accordance with ASTM E 8 or ASTM E 8M (See 8.3). Properties other than those listed may be defined as specified in AMS 2360.

3.6.1.1 Separately-Cast Specimens

Shall be as shown in Table 2.

TABLE 2 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	180 ksi (1241 MPa)
Yield Strength at 0.2% Offset	160 ksi (1103 MPa)
Elongation in 4D	6%
Reduction of Area	15%

3.6.1.2 Integrally-Cast Specimens or Specimens Machined from Castings

Shall be as shown in Table 3.

TABLE 3 - MINIMUM TENSILE PROPERTIES

Property	Value
Tensile Strength	180 ksi (1241 MPa)
Yield Strength at 0.2% Offset	160 ksi (1103 MPa)
Elongation in 4D	4%
Reduction of Area	12%

3.6.2 Hardness

Shall be as follows, determined in accordance with ASTM E 18:

3.6.2.1 Castings

Castings, which are heat treated to the condition of 3.3.1, shall be 40 to 46 HRC.

3.6.2.2 Representative Specimens

Hardness not applicable.

3.7 Quality

Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.7.1 Unless otherwise specified by purchaser, the following shall apply:

3.7.1.1 Castings shall be free of cracks, laps, hot tears, and cold shuts.

3.7.1.2 Castings shall be free of scale and other process-induced surface contamination which would obscure defects.

- 3.7.1.3 Cast surfaces shall be sufficiently cleaned such that, after passivation by purchaser, the castings shall meet the corrosion test requirement of AMS-QQ-P-35.
- 3.7.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of each casting part number until foundry manufacturing controls in accordance with 4.4.2 have been established. Additional radiography shall be conducted in accordance with the frequency of inspection specified by purchaser or as necessary to ensure continued maintenance of internal quality.
- 3.7.2.1 Radiographic inspection shall be conducted in accordance with MIL-STD-453 or other method specified by purchaser.
- 3.7.3 When specified, additional nondestructive testing shall be performed as follows:
- 3.7.3.1 Fluorescent penetrant inspection in accordance with MIL-STD-6866 or other method specified by purchaser.
- 3.7.3.2 Magnetic particle inspection in accordance with ASTM E 1444 or other method specified by purchaser.
- 3.7.4 Acceptance standards for radiographic, magnetic particle, fluorescent penetrant, visual, and other inspection methods shall be as agreed upon by purchaser and vendor (See 8.2.8). AMS-STD-2175 may be used to specify acceptance standards (casting grade) and frequency of inspection (casting class).
- 3.7.4.1 When acceptance standards are not specified, Grade C of AMS-STD-2175 shall apply.
- 3.7.5 Castings shall not be peened, plugged, impregnated, or welded unless authorized by purchaser.
- 3.7.5.1 When authorized by purchaser, welding in accordance with AMS 2694 or other welding program acceptable to purchaser may be used.

4. QUALITY ASSURANCE PROVISIONS

4.1 Responsibility for Inspection

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for the performance of all required tests. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to specified requirements.

4.2 Classification of Tests

4.2.1 Acceptance Tests

Composition (3.1), tensile properties (3.6.1), hardness of castings (3.6.2.1), and quality (3.7) are acceptance tests and shall be performed as specified in 4.3.

4.2.2 Periodic Tests

Corrosion resistance (3.7.1.3) and radiographic soundness (3.7.2) are periodic tests and shall be performed at a frequency selected by vendor unless frequency of testing is specified by purchaser.

4.2.3 Preproduction Tests

All technical requirements are preproduction tests and shall be performed on sample castings (4.3.2), when a change in control factors occurs (4.4.2.2), and when purchaser deems confirmatory testing to be required.

4.3 Sampling and Testing

The minimum testing performed by vendor shall be in accordance with the following:

- 4.3.1 One chemical analysis specimen or a casting from each master heat shall be tested for conformance with Table 1, unless 3.4.2.1 applies in which case test frequency shall be acceptable to purchaser.
- 4.3.2 One preproduction casting in accordance with 4.4 shall be tested to the requirements of the casting drawing and to all technical requirements.
 - 4.3.2.1 Dimensional inspection sample quantity shall be as specified by purchaser.
- 4.3.3 Tensile tests shall be conducted to determine conformance with 3.6.1. Sampling and test frequency is dependent upon the type and origin of specimen specified by purchaser (See 3.6) or selected by vendor (See 4.3.3.4). When 3.4.2.1 applies, test frequency shall be acceptable to purchaser.
 - 4.3.3.1 For separately-cast specimens in the fully heat treated condition (See 3.3 and 3.5.1), one or more specimens from each lot shall be tested for conformance to 3.6.1.1.
 - 4.3.3.2 For integrally-cast specimens in the fully heat treated condition (See 3.3 and 3.5.1), two or more specimens from each lot shall be randomly selected and tested for conformance to 3.6.1.2.
 - 4.3.3.3 For specimens machined from castings, one or more castings shall be randomly selected from each lot and tested after full heat treatment (See 3.3 and 3.5.1) at each location shown on the engineering drawing for conformance to 3.6.1.2.
 - 4.3.3.3.1 When size and location of specimens are not shown, two or more test specimens shall be tested, one from the thickest section and one from the thinnest section. Once established under 4.4.2.2, test locations may be changed only as agreed upon by purchaser and vendor.
 - 4.3.3.4 When acceptable to purchaser, specimens machined from castings may be used in lieu of both separately-cast and integrally-cast specimens, and integrally-cast specimens may be used in lieu of separately-cast specimens. In each case, the resultant properties must conform to requirements of 3.6 for separately-cast specimens or to alternate requirements specified by purchaser.
 - 4.3.3.4.1 When specimens are selected for test as in 4.3.3.4 from an origin other than that specified by purchaser, vendor shall include in the report of 4.5 a description of the origin of the specimen that was tested.
 - 4.3.3.5 When casting size, section thickness, gating method, or other factors do not permit conformance with 4.3.3.2 or 4.3.3.3, sampling and testing shall be agreed upon by purchaser and vendor.
- 4.3.4 Castings shall be inspected in accordance with 3.7 to the methods, frequency, and acceptance standards specified by purchaser.
- 4.3.5 Castings shall be tested for hardness to determine conformance with 3.6.2.1. Unless otherwise specified by purchaser, the number of castings sampled from each lot shall be in accordance with Table 4.
 - 4.3.5.1 In the event that a lot fails to meet the specified accept/reject number of Table 4, the entire lot shall be 100% inspected or reheat treated in accordance with 4.6.2.
 - 4.3.5.2 Castings shall not be rejected on the basis of low hardness if tensile property requirements of 3.6.1.2 are met.
- 4.4 Approval
 - 4.4.1 Sample casting(s) from new or reworked master patterns produced under the casting procedure of 4.4.2 shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

TABLE 4- HARDNESS TEST SCHEDULE OF HEAT TREATED CASTINGS

Lot Size	Sample Size	Accept/Reject	
1 to 8	All	0	1
9 to 50	8	0	1
51 to 90	13	0	1
91 to 150	20	0	1
151 to 280	32	0	1
281 to 500	50	0	1
501 to 1200	80	0	1
1201 to 3200	125	0	1
3201 and over	200	0	1

4.4.2 For each casting part number, vendor shall establish parameters for process control factors that will consistently produce castings and test specimens meeting the requirements of the casting drawing and this specification. These parameters shall constitute the approved casting procedure and shall be used for production of subsequent castings and test specimens. If necessary to make any change to these parameters, vendor shall submit a statement of the proposed change for purchaser reapproval. When requested, vendor shall also submit test specimens, sample castings, or both to purchaser for reapproval.

4.4.2.1 Production castings produced prior to receipt of purchaser's approval shall be at vendor's risk.

4.4.2.2 Control factors for producing castings and separately-cast tensile specimens include, but are not limited to, the following factors. Supplier's procedures shall identify tolerances, ranges, and/or control limits, as applicable. Control factors for separately-cast test specimens must generally represent, but need not be identical to, those factors used for castings (See 3.2.3 and 3.4.1):

Composition of ceramic cores, if used

Arrangement and number of patterns in the mold (including integrally-cast specimens if applicable)

Size, shape, and location of gates and risers

Mold refractory formulation

Grain refinement methods, if applicable

Mold back up material (weight, thickness, or number of dips)

Type of furnace, atmosphere, and charge for melting

Mold preheat and metal pouring temperatures

Fluxing or deoxidation procedure

Replenishment and alloy addition procedure, if applicable

Time that molten metal is in the furnace

Solidification and cooling procedures

Cleaning operations (mechanical and chemical)

Heat treatment

Straightening

Final inspection methods

Location of specimens machined from castings, if applicable

4.4.2.2.1 Any of the control factors for which parameters are considered proprietary by vendor may be assigned a code designation. Each variation in such parameters shall be assigned a modified code designation.

4.4.2.2.1.1 Unless otherwise agreed upon by purchaser and vendor, purchaser shall be entitled to review proprietary control factor details and coding at vendor's facility.

4.5 Reports

The vendor of castings shall furnish with each shipment a report showing the results of tests to determine conformance to the acceptance test requirements. This report shall include the purchase order number, master heat identification, heat treat/lot identification, AMS 5344E, part number, quantity, and source of tensile specimens (See 4.3.3.4.1).