

SAE The Engineering
Resource For
Advancing Mobility

400 COMMONWEALTH DRIVE, WARRENDALE, PA 15096

**AEROSPACE
MATERIAL
SPECIFICATION****AMS 5353B**

Superseding AMS 5353A

Issued 9-15-57
Revised 1-1-84STEEL CASTINGS, INVESTMENT, CORROSION RESISTANT
16Cr - 1.8Ni - 0.08N
As Cast

UNS J91651

1. SCOPE:

1.1 **Form:** This specification covers a corrosion-resistant steel in the form of investment castings.

1.2 **Application:** Primarily for small parts, such as rotors, requiring moderate corrosion resistance and strength up to 800°F (425°C).

2. **APPLICABLE DOCUMENTS:** The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications (AMS) shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 **SAE Publications:** Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 **Aerospace Material Specifications:**

AMS 2350 - Standards and Test Methods
AMS 2360 - Room Temperature Tensile Properties of Castings
AMS 2635 - Radiographic Inspection
AMS 2640 - Magnetic Particle Inspection
AMS 2645 - Fluorescent Penetrant Inspection
AMS 2694 - Repair Welding of Aerospace Castings
AMS 2804 - Identification, Castings

2.2 **ASTM Publications:** Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A370 - Mechanical Testing of Steel Products
ASTM E192 - Reference Radiographs of Investment Steel Castings for Aerospace Applications
ASTM E353 - Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys

SAE Technical Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

AMS 5353B

2.3 U.S. Government Publications: Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Federal Standards:

Federal Test Method Standard No. 151 - Metals; Test Methods

2.3.2 Military Standards:

MIL-STD-794 - Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Composition: Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353, by spectrographic methods in accordance with Federal Test Method Standard No. 151, Method 112, or by other analytical methods approved by purchaser:

	min	max
Carbon	0.08	0.15
Manganese	--	1.00
Silicon	--	1.00
Phosphorus	--	0.04
Sulfur	--	0.04
Chromium	15.00	17.00
Nickel	1.50	2.20
Nitrogen	0.03	0.12
Carbon + Nitrogen	--	0.22
Molybdenum	--	0.50
Copper	--	0.50

3.2 Condition: As cast.

3.3 Casting: Castings shall be poured either from remelted metal from a master heat or directly from a master heat. In either case, metal for casting shall be qualified as in 3.4.

3.3.1 A master heat is refined metal of a single furnace charge or is metal blended as in 3.3.2. Gates, sprues, risers, and rejected castings shall be used only in preparation of master heats; they shall not be remelted directly, without refining, for pouring of castings.

3.3.2 Unless prohibited by purchaser, metal from two or more master heats may be blended provided that the composition of each master heat to be blended is within the limits of 3.1 and that the total weight of metal blended does not exceed 15,000 lb (6800 kg). Ingot and pig may be blended together, shot may be blended, but shot shall not be blended with ingot or pig. When two or more master heats are blended, the resultant blend shall be considered a master heat.

AMS 5353B

- 3.4 Master Heat Qualification: Each master heat shall be qualified by evaluation of chemical analysis and tensile specimens conforming to 3.4.1 and 3.4.2, respectively. A master heat may be considered conditionally qualified if vendor's test results show conformance to all applicable requirements of this specification. However, except when purchaser waives confirmatory testing, final qualification shall be based on purchaser's test results. Conditional qualification of a master heat shall not be construed as a guarantee of acceptance of castings poured therefrom.
- 3.4.1 Chemical Analysis Specimens: Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.
- 3.4.2 Tensile Specimens: Shall be cast from remelted metal from each master heat except when castings are poured directly from a master heat, in which case the specimens shall also be poured directly from the master heat. Specimens shall be of standard proportions in accordance with ASTM A370 with 0.250 in. (6.25 mm) diameter at the reduced parallel gage section. They shall be cast to size or shall be cast oversize and subsequently machined to 0.250 in. (6.25 mm) diameter. Center gating may be used.
- 3.5 Properties: Castings and representative tensile specimens produced in accordance with 3.4.2 shall conform to the following requirements; hardness and tensile testing shall be performed in accordance with ASTM A370:
- 3.5.1 After Normalizing, Sub-Zero Cooling, and Tempering: Castings and representative tensile specimens shall have hardness of 24 - 34 HRC or equivalent after being normalized by heating to $1875^{\circ}\text{F} \pm 25$ ($1025^{\circ}\text{C} \pm 15$), holding at heat for not less than 60 min. per inch (25 mm) of maximum cross-section but not less than 30 min., and cooling in air; cooling to $-100^{\circ}\text{F} \pm 10$ ($-75^{\circ}\text{C} \pm 5$), holding at $-100^{\circ}\text{F} \pm 10$ ($-75^{\circ}\text{C} \pm 5$) for not less than 60 min., and warming in air to room temperature; and tempered by heating to $1125^{\circ}\text{F} \pm 25$ ($605^{\circ}\text{C} \pm 15$), holding at heat for 2 - 4 hr, and cooling to room temperature.
- 3.5.2 After Hardening, Sub-Zero Cooling, and Tempering: Castings and representative tensile specimens, normalized, sub-zero cooled, and tempered as in 3.5.1, shall meet the requirements of 3.5.2.1 and 3.5.2.2 after being hardened by heating to $1850^{\circ}\text{F} \pm 25$ ($1010^{\circ}\text{C} \pm 15$), holding at heat for not less than 60 min. per inch (25 mm) of maximum cross-section but not less than 30 min., and quenching in oil; cooling to $-100^{\circ}\text{F} \pm 10$ ($-75^{\circ}\text{C} \pm 5$), holding at $-100^{\circ}\text{F} \pm 10$ ($-75^{\circ}\text{C} \pm 5$) for not less than 60 min., and warming to room temperature; and double tempered by heating to $600^{\circ} - 700^{\circ}\text{F}$ ($315^{\circ} - 370^{\circ}\text{C}$), holding at heat for 2 hr ± 0.25 , cooling to room temperature, cooling to $-100^{\circ}\text{F} \pm 10$ ($-75^{\circ}\text{C} \pm 5$), holding at $-100^{\circ}\text{F} \pm 10$ ($-75^{\circ}\text{C} \pm 5$) for not less than 60 min., and warming to room temperature, and reheating to $600^{\circ} - 700^{\circ}\text{F}$ ($315^{\circ} - 370^{\circ}\text{C}$), holding at heat for 2 hr ± 0.25 , and cooling to room temperature.

AMS 5353B

3.5.2.1 Hardness of Castings: 38 - 49 HRC or equivalent.

3.5.2.2 Tensile Properties:

3.5.2.2.1 Separately-Cast Specimens:

Tensile Strength, min	170,000 psi (1170 MPa)
Yield Strength at 0.2% Offset, min	130,000 psi (895 MPa)
Elongation in 1 in. (25 mm) or 4D, min	2.0%

3.5.2.2.2 Specimens Cut from Castings: When specified on the drawing or when agreed upon by purchaser and vendor, tensile specimens as in 4.3.4 conforming to ASTM A370 shall be machined from locations indicated on the drawing from a casting or castings selected at random from each lot. Property requirements for such specimens shall be as specified on the drawing or as agreed upon by purchaser and vendor and may be defined as specified in AMS 2360.

3.6 Quality:

3.6.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external imperfections detrimental to usage of the castings.

3.6.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning, unless otherwise permitted by purchaser.

3.6.2 Castings shall be produced under radiographic control, unless otherwise specified. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.6.3 When specified, castings shall be subjected to magnetic particle inspection in accordance with AMS 2640 or to fluorescent penetrant inspection in accordance with AMS 2645, or both.

3.6.4 Radiographic, magnetic particle, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E192 may be used to define radiographic acceptance standards.

3.6.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.6.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.

AMS 5353B**4. QUALITY ASSURANCE PROVISIONS:**

4.1 Responsibility for Inspection: The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

4.2.1 Acceptance Tests: Except as specified in 4.2.1.1, tests to determine conformance to all technical requirements of this specification are classified as acceptance tests and shall be performed on each master heat or lot as applicable.

4.2.1.1 Tensile properties of specimens cut from castings after hardening, sub-zero cooling, and tempering shall be determined only when specified by purchaser or when separately-cast specimens are not available. Tensile properties of separately-cast specimens need not be determined when tensile properties of specimens cut from castings are determined.

4.2.2 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material or processing, or both, requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.

4.2.2.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling: Shall be in accordance with the following; a lot shall be all castings from a single master heat presented for vendor's inspection at one time:

4.3.1 Two chemical analysis specimens in accordance with 3.4.1 or a casting from each master heat.

4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.

4.3.3 Three tensile specimens in accordance with 3.4.2 from each master heat.

AMS 5353B

4.3.4 One or more castings from each lot when properties of specimens machined from castings are required. Size, location, and number of specimens machined from castings shall be as specified on the drawing or as agreed upon by purchaser and vendor. When size, location, and number of specimens are not specified, not less than two tensile specimens, one from the thickest section and one from the thinnest section, shall be cut from a casting or castings from each lot.

4.4 Approval:

4.4.1 Sample castings from new or reworked master patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.

4.4.2 Vendor shall establish separately for tensile specimens used for master heat qualification and for production of sample castings of each part number parameters for the process control factors which will produce tensile specimens meeting master heat qualification requirements and acceptable castings; these shall constitute the approved casting procedure and shall be used for producing subsequent master heat qualification specimens and production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, sample test specimens, castings, or both. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.

4.4.2.1 Control factors for producing test specimens and castings include, but are not limited to, the following:

Ø

Type of furnace and its capacity
 Type and size of furnace charge
 Time molten metal is in furnace
 Furnace atmosphere
 Fluxing or deoxidation procedure
 Number of ladles used in pour
 Mold refractory formulation
 Mold back-up material
 Gating practices
 Mold preheat and pouring temperatures (variations of $\pm 25^{\circ}\text{F}$ ($\pm 15^{\circ}\text{C}$) from established limits are permissible)
 Solidification and cooling procedures
 Cleaning operations
 Methods of inspection