

AEROSPACE MATERIAL SPECIFICATION



AMS 5371E

Issued	MAR 1955
Revised	APR 1987
Noncurrent	NOV 1994
Reaf. Noncur.	NOV 2000
Cancelled	MAR 2007
Superseding	AMS 5371D

Steel Castings, Sand, Corrosion and Heat Resistant
19.5Cr - 9.5Ni (Low Carbon) (304L)
Solution Heat Treated

UNS J92620

RATIONALE

AMS 5371D has been cancelled because survey of aerospace users and producers indicated that this product is not produced to this specification.

CANCELLATION NOTICE

This specification has been declared "CANCELLED" by the Aerospace Materials Division, SAE, as of March 2007. By this action, this document will remain listed in the Numerical Section of the Index of Aerospace Material Specifications indicating that it has been "CANCELLED".

Cancelled specifications are available from SAE.

SAE Technical Standards Board Rules provide that: "This report is published by SAE to advance the state of technical and engineering sciences. The use of this report is entirely voluntary, and its applicability and suitability for any particular use, including any patent infringement arising therefrom, is the sole responsibility of the user."

SAE reviews each technical report at least every five years at which time it may be reaffirmed, revised, or cancelled. SAE invites your written comments and suggestions.

Copyright © 2007 SAE International

All rights reserved. No part of this publication may be reproduced, stored in a retrieval system or transmitted, in any form or by any means, electronic, mechanical, photocopying, recording, or otherwise, without the prior written permission of SAE.

TO PLACE A DOCUMENT ORDER: Tel: 877-606-7323 (inside USA and Canada)
 Tel: 724-776-4970 (outside USA)
 Fax: 724-776-0790
 Email: CustomerService@sae.org
SAE WEB ADDRESS: http://www.sae.org

NONCURRENT NOTICE

This specification has been declared "NONCURRENT" by the Aerospace Materials Division, SAE, as of November 1994. It is recommended, therefore, that this specification not be specified for new designs.

"NONCURRENT" refers to those materials which have previously been widely used and which may be required on some existing designs in the future. The Aerospace Materials Division, however, does not recommend these as standard materials for future use in new designs. Each of these "NONCURRENT" specifications is available from SAE.

SAENORM.COM : Click to view the full PDF of ams5371e

1. SCOPE:

1.1 Form:

This specification covers a corrosion and heat resistant steel in the form of sand castings.

1.2 Application:

Primarily for parts requiring both corrosion and heat resistance up to 800°F (425°C), especially where such parts are welded during fabrication; for parts requiring oxidation resistance up to 1500°F (815°C) but useful at the higher temperatures only when stresses are low; and for parts requiring resistance to fuming nitric acid.

2. APPLICABLE DOCUMENTS:

The following publications form a part of this specification to the extent specified herein. The latest issue of Aerospace Material Specifications shall apply. The applicable issue of other documents shall be as specified in AMS 2350.

2.1 SAE Publications:

Available from SAE, 400 Commonwealth Drive, Warrendale, PA 15096.

2.1.1 Aerospace Material Specifications:

AMS 2350	Standards and Test Methods
AMS 2635	Radiographic Inspection
AMS 2645	Fluorescent Penetrant Inspection
AMS 2694	Repair Welding of Aerospace Castings
AMS 2804	Identification, Castings

2.2 ASTM Publications:

Available from American Society for Testing and Materials, 1916 Race Street, Philadelphia, PA 19103.

ASTM A262	Detecting Susceptibility to Intergranular Attack in Stainless Steels
ASTM E10	Brinell Hardness of Metallic Materials
ASTM E353	Chemical Analysis of Stainless, Heat-Resisting, Maraging, and Other Similar Chromium-Nickel-Iron Alloys
ASTM E446	Reference Radiographs for Steel Castings up to 2 in. (51 mm) in Thickness

2.3 U.S. Government Publications:

Available from Commanding Officer, Naval Publications and Forms Center, 5801 Tabor Avenue, Philadelphia, PA 19120.

2.3.1 Military Standards:

MIL-STD-794 Parts and Equipment, Procedures for Packaging and Packing of

3. TECHNICAL REQUIREMENTS:

3.1 Composition:

Shall conform to the following percentages by weight, determined by wet chemical methods in accordance with ASTM E353 or by spectrographic or other analytical methods approved by purchaser:

	min	max
Carbon	--	0.050
Manganese	1.00	2.00
Silicon	0.75	1.50
Phosphorus	--	0.04
Sulfur	--	0.04
Chromium	18.00	21.00
Nickel	8.00	11.00
Molybdenum	--	0.75
Copper	--	0.75

3.2 Condition:

Solution heat treated free from continuous carbide network.

3.3 Casting:

A melt shall be the metal poured from a single furnace charge of 15,000 lb (6800 kg) or less. A lot shall be all castings of the same part number poured from a single melt in not more than eight consecutive hours and heat treated together as a batch.

3.4 Chemical Analysis Specimens:

Shall be of any convenient size, shape, and form for vendor's tests. When chemical analysis specimens are required by purchaser, specimens shall be cast to a size, shape, and form agreed upon by purchaser and vendor.

3.5 Heat Treatment:

Castings shall be solution heat treated by heating to $2000^{\circ}\text{F} \pm 50$ ($1095^{\circ}\text{C} \pm 30$), holding at heat for not less than 30 min. per inch (25 mm) of maximum section thickness but in no case less than 30 min., and cooling in air.

3.6 Properties:

Castings shall conform to the following requirements:

3.6.1 Hardness: Not higher than 170 HB, or equivalent, determined in accordance with ASTM E10.

3.6.2 Embrittlement: Specimens cut from castings, after sensitizing treatment, shall show no evidence of intercrystalline surface attack when examined microscopically after being exposed to the copper/copper sulfate/sulfuric acid test in accordance with ASTM A262, Practice E.

3.7 Quality:

3.7.1 Castings, as received by purchaser, shall be uniform in quality and condition, sound, and free from foreign materials and from imperfections detrimental to usage of the castings.

3.7.1.1 Castings shall have smooth surfaces and shall be well cleaned. Metallic shot or grit shall not be used for final cleaning.

3.7.2 Castings shall be produced under radiographic control. This control shall consist of radiographic examination of castings in accordance with AMS 2635 until proper foundry technique, which will produce castings free from harmful internal imperfections, is established for each part number and of production castings as necessary to ensure maintenance of satisfactory quality.

3.7.3 When specified, castings shall be subjected to fluorescent penetrant inspection in accordance with AMS 2645.

3.7.4 Radiographic, fluorescent penetrant, and other quality standards shall be as agreed upon by purchaser and vendor. ASTM E446 may be used to define radiographic acceptance standards.

3.7.5 Castings shall not be repaired by peening, plugging, welding, or other methods without written permission from purchaser.

3.7.5.1 When permitted in writing by purchaser, defects in castings may be removed and the castings repaired by welding in accordance with AMS 2694.

4. QUALITY ASSURANCE PROVISIONS:

4.1 Responsibility for Inspection:

The vendor of castings shall supply all samples for vendor's tests and shall be responsible for performing all required tests. Results of such tests shall be reported to the purchaser as required by 4.5. Purchaser reserves the right to sample and to perform any confirmatory testing deemed necessary to ensure that the castings conform to the requirements of this specification.

4.2 Classification of Tests:

- 4.2.1 Acceptance Tests: Tests to determine conformance to requirements for composition (3.1), hardness (3.6.1), and quality (3.7) are classified as acceptance tests and shall be performed on each melt or lot as applicable.
- 4.2.2 Periodic Tests: Tests to determine conformance to requirements for embrittlement (3.6.2) are classified as periodic tests and shall be performed at a frequency selected by the vendor unless frequency of testing is specified by purchaser.
- 4.2.3 Preproduction Tests: Tests to determine conformance to all technical requirements of this specification are classified as preproduction tests and shall be performed prior to or on the first-article shipment of a casting to a purchaser, when a change in material, processing, or both requires reapproval as in 4.4.2, and when purchaser deems confirmatory testing to be required.
- 4.2.3.1 For direct U.S. Military procurement, substantiating test data and, when requested, preproduction test material shall be submitted to the cognizant agency as directed by the procuring activity, the contracting officer, or the request for procurement.

4.3 Sampling:

Shall be in accordance with the following:

- 4.3.1 Two chemical analysis specimens in accordance with 3.4. from each melt or a casting from each lot.
- 4.3.2 Two preproduction castings in accordance with 4.4.1 of each part number.

4.4 Approval:

- 4.4.1 Sample castings from new or reworked patterns and the casting procedure shall be approved by purchaser before castings for production use are supplied, unless such approval be waived by purchaser.
- 4.4.2 Vendor shall establish for production of sample castings of each part number parameters for the process control factors which will produce acceptable castings; these shall constitute the approved casting procedure and shall be used for producing production castings. If necessary to make any change in parameters for the process control factors, vendor shall submit for reapproval a statement of the proposed changes in processing and, when requested, sample castings. Production castings incorporating the revised operations shall not be shipped prior to receipt of reapproval.