

AERONAUTICAL MATERIAL SPECIFICATION

Society of Automotive Engineers, Inc.
29 West 39th Street
New York City

AMS 5372

Issued 3-1-55

Revised

STEEL CASTINGS, SAND, CORROSION RESISTANT 15.8Cr - 1.9Ni

1. ACKNOWLEDGMENT: A vendor shall mention this specification number in all quotations and when acknowledging purchase orders.
2. APPLICATION: Primarily for small parts such as air valve components requiring corrosion resistance and strength up to 800 F.
3. COMPOSITION:

Carbon	0.12 - 0.20
Manganese	1.0 max
Silicon	1.0 max
Phosphorus	0.04 max
Sulfur	0.04 max
Chromium	14.5 - 17.0
Nickel	1.5 - 2.25
Molybdenum	0.50 max
Copper	0.50 max
4. CONDITION: Normalized and tempered, unless otherwise specified.
5. TECHNICAL REQUIREMENTS:
 - 5.1 Casting: A melt shall be the metal poured from a single ladle of 5000 lb or less.
 - 5.2 Test Specimens:
 - 5.2.1 Tensile Test Coupons: Shall be attached to castings, if practicable, or shall be standard keel blocks as shown in Figure 1, unless purchaser permits use of cast to size specimens. Coupons shall be cast with each melt of metal for castings and, when requested, shall be supplied with the castings. Keel blocks shall be cast in molds made of suitable core sand, shall be poured directly after pouring the castings, and shall be left in the mold until black. Metal for the coupons shall be part of the melt which is used for the castings.
 - 5.2.2 Chemical Analysis Specimens: When required by purchaser, shall be of size and shape agreed upon by purchaser and vendor.
 - 5.3 Heat Treatment: All castings and tensile test specimens representing them shall be heat treated as follows:
 - 5.3.1 Tensile test specimens from each melt, together with production castings, shall be normalized by heating to 1825 F $\pm$ 25, holding at heat for 1 hr per inch of section but in no case less than 30 min., and cooled in air. They shall then be tempered by heating to not lower than 1100 F, holding at heat for not less than 2 hr, and cooled in air.
 - 5.4 Hardness: Shall be Brinell 255-311 or equivalent.

Section 7C of the SAE Technical Board rules provides that: "All technical reports, including standards approved and practices recommended, are advisory only. Their use by anyone engaged in industry or trade is entirely voluntary. There is no agreement to adhere to any SAE standard or recommended practice, and no commitment to conform to or be guided by any technical report. In formulating and approving technical reports, the Board and its Committees will not investigate or consider patents which may apply to the subject matter. Prospective users of the report are responsible for protecting themselves against liability for infringement of patents."

- 5.5 Properties After Heat Treatment: Tensile test specimens produced in accordance with 5.2 and heat treated in accordance with 5.3 shall be capable of meeting the following requirements after hardening and tempering by heating to $1900\text{ F} \pm 25$, holding at heat for 30 min., and quenching in oil, followed by heating to $675\text{ F} \pm 25$, holding at heat for 3 hr, and cooling in air.

5.5.1 Tensile Properties:

Tensile Strength, psi	180,000 min
Yield Strength at 0.2% Offset or at 0.0137 in. in 2 in. Extension Under Load ($E = 29,000,000$), psi	140,000 min
Elongation, % in 4D	8 min

- 5.5.2 Hardness: Shall be not lower than Rockwell C 38 or equivalent.

6. QUALITY:

- 6.1 Castings shall be uniform in quality and condition, sound, and free from foreign materials and from internal and external defects detrimental to fabrication or to performance of parts. Castings shall have smooth surfaces and shall be well cleaned. Unless otherwise specified, metallic shot or grit shall not be used for final cleaning.
- 6.2 When castings are broken for fracture test, the fracture shall have uniform color and be substantially free from oxides and other defects.
- 6.3 Radiographic and other quality standards shall be as agreed upon by purchaser and vendor.
- 6.4 Unless otherwise specified, castings shall be produced under radiographic control. This shall consist of radiographic examination of castings until proper foundry technique, which will produce castings free from harmful internal defects, is established for each part number, and of production castings as necessary to ensure maintenance of satisfactory quality.
- 6.5 Castings shall not be repaired by plugging, welding, or other methods, without written permission from purchaser.

7. REPORTS:

- 7.1 Unless otherwise specified, the vendor of castings shall furnish with each shipment three copies of a report of the results of tests for chemical composition of each melt. This report shall include the purchase order number, melt number, material specification number, part number, and quantity from each melt.
- 7.2 Unless otherwise specified, the vendor of finished or semi-finished parts shall furnish with each shipment three copies of a report showing the purchase order number, material specification number, contractor or other direct supplier of castings, part number, and quantity. When castings for making parts are produced or purchased by the parts vendor, that vendor shall inspect castings from each melt represented to determine conformance to the requirements of this specification, and shall include in the report a statement that the castings conform, or shall include copies of laboratory reports showing the results of tests to determine conformance.

8. IDENTIFICATION: Castings shall be identified in accordance with the latest issue of AMS 2804.